Tesis Doctoral

DEVELOPMENT AND OPTIMIZATION OF THE PROPERTIES OF γ/γ' Co-BASED SUPERALLOYS FOR HIGH TEMPERATURE APPLICATIONS

Marta Cartón Cordero

en cumplimiento parcial de los requisitos para el grado de Doctor en

Ciencia e Ingeniería de Materiales

Universidad Carlos III de Madrid

Director(es):

Dra. Mónica Campos Gómez

Dr. José Manuel Torralba Castelló

Tutora

Dra. Mónica Campos Gómez

Leganés, Diciembre de 2018

Esta tesis se distribuye bajo licencia “**Creative Commons Reconocimiento – No Comercial – Sin Obra Derivada**”.

*A Carlos y Mercedes
a Carla
y a mi familia*

AGRADECIMIENTOS

Llegando al fin de esta etapa de mi vida, solo me queda agradecer a todas aquellas personas que han sido parte activa y pasiva de este proceso. Son muchas las personas que me han ayudado, y seguro que me olvido de nombrar a alguien, pero no significa que no se lo agradezca. Al revés, gracias a todas aquellas personas que durante estos años han invertido su tiempo conmigo.

Quisiera empezar los agradecimientos por las dos personas que han estado al pie del cañón desde el inicio, sacándome de bloqueos y ayudándome en todo lo que han podido con eterna paciencia, mis dos directores Mónica Campos y José Manuel Torralba. Gracias por darme la oportunidad de llevar a cabo esta investigación a vuestro lado, he aprendiendo mucho de vuestra sabiduría y de cada consejo que me habéis regalado. Me habéis ayudado a crecer en el ámbito laboral, pero lo que es más importante a crecer personalmente. Siempre habéis estado disponibles para resolver dudas y escuchar mis ideas locas. Gracias por aportarme la coherencia y la tranquilidad que en muchas ocasiones no he tenido.

Agradecer al Instituto IMDEA Materiales por permitir el desarrollo de mi tesis con total acceso y buenas condiciones de equipamiento. También agradecer a todos los jefes de IMDEA que me han ayudado en todo lo que he necesitado. Agradezco a todos mis compañer@s de IMDEA, aquellos con los que empecé y los que seguimos aún juntos, muchos de ellos ya amig@s, por todos los momentos vividos. Esos debates en el café y en la comida, por las risas que nos hemos echado juntos y sobre todo el apoyo que me habéis dado cada día. Debería mencionaros a todos, pero sois tantos que los agradecimientos ocuparían más que la tesis.

Gracias a mis técnicos de IMDEA, espero que sigáis así y no cambies nunca, Vanesa, Jose Luis, Miguel de la Cruz, Pepe, Amalia, Ángel y Miguel Castillo. Sin vosotros esta tesis no hubiese sido posible, me ayudasteis en infinidad de problemas y me disteis millones de soluciones con mucho ingenio y una gran experiencia. ¡Sois unos cracks! Por supuesto no puedo olvidarme de dar las gracias a los que se fueron, Juan Carlos Rubalcaba por enseñarme a utilizar los microscopios y por su gran paciencia, aunque se fue, le seguimos recordando. Gracias a Antón por esas largas conversaciones y por tu ayuda.

De este tiempo en IMDEA me llevo muy buenos amig@s. Entre ellas a Andrea García-Junceda, compañera de batallas y amiga, gracias por los buenos momentos que hemos pasado, por ayudarme en todo y apoyarme en los momentos de bajón. Almu y Miguel Herraiez, empezamos juntos esta etapa y ha sido un placer compartirla con vosotros, gracias por vuestro apoyo, paciencia, comprensión y sobre todo por los buenos momentos, me llevo dos grandes amigos. Paqui, que aunque coincidí muy poco contigo hicimos una gran amistad, gracias por tus consejos y ayudarme incluso desde la distancia. Gracias también a Alex por tu paciencia y ayudarme en lo que has podido. Gracias también a Anna por poner ese punto de locura y ayudarme.

Por otro lado quisiera dar las gracias también al departamento de materiales de la Universidad Carlos III de Madrid y en especial al Grupo de Tecnología de polvos (GTP) el cual me ha tratado como uno más y he aprendido cosas de cada compañera. Gracias a todas las jefas del grupo por ser accesibles y ayudarme cuando he tenido que realizar ensayos en la universidad, así como en los congresos compartidos. A todos los compañer@s del grupo, los que ya se fueron, los que están y los que vienen nuevos, por hacerme sentir una más, ayudarme y facilitarme el trabajo al máximo.

No puedo dejar de agradecer a Estela, María y Amaya, que siempre llegan en el momento que las necesitas, os adoro y me llevo tres amigas. Por esas noches de cena por Getafe... Millones de

gracias mi Eriquiño, ya sabes que eres mi favorito, que te voy a decir, compañero de tesis y sobre todo amigo. Debo darte las gracias, y lo haré toda la vida, por todo lo que me has ayudado durante estos años, que hubiese hecho yo sin ti, eres una gran persona.

Tengo que agradecer al centro Centro de Investigación en Nanomateriales y Nanotecnología (CINN) en Asturias por permitirme consolidar mis piezas allí. En especial a Luis Antonio Díaz, que me acogió y enseñó todo sobre la consolidación por SPS. Después de la corta estancia allí pude avanzar y entender mucho mejor el proceso.

La mención internación y parte de esta tesis se la debo agradecer a la beca DAAD y sobre todo a la universidad FAU Nuremberg-Erlangen por acogerme como una más y permitirme hacer todos los ensayos en sus instalaciones. A Mathias Göken por aceptarme en su grupo y permitir que fuese una más. Agradecer a Steffen Neumeier por incluirme en el grupo como a un miembro más, gracias a él pude aprender mucho sobre las superaleaciones de Co. Gracias a Lisa Freund por acompañarme los tres meses y ayudarme con todo, me hiciste sentir como en casa. Gracias a los compañeros que me explicaron y ayudaron con los ensayos realizados, Martin, Markus y Steffen Lamm.

Gracias a mis Kalakissas por resetear mi cabeza cada miércoles por la noche, que haría yo sin esas risas incontroladas, esos pasos imposibles y sin vosotras, que sois las ¡mejores!

Gracias a mis casta química y agregados, que aunque no he podido verlos estos meses los llevo siempre conmigo. Gracias a Ana, que me escucha y comprende a las mil maravillas y siempre está pendiente. Gracias a Yoli, Mario, Mariu, Javi, Marta, Leo, Sergio, Chiqui, Eva, Nuri, Laurita y Richy, por esas quedadas maravillosas que espero no dejemos de hacer nunca.

Y por último y así quedarme con el mejor sentimiento quiero agradecer a mi familia el apoyo incondicional que me dan, sin ellos este no hubiese sido posible. Gracias infinitas a mis padres, Carlos y Mercedes, sin ellos y su educación no podría haber llegado a ser la persona que soy. No tendré vidas para agradecer a mis padres lo que han hecho por mí, su paciencia, comprensión, apoyo, buen hacer... Gracias también a mi hermano Carlos Miguel, por darme buenos consejos y su apoyo. Gracias a Sonia, por apoyarme y darme ánimos.

Gracias a mis tíos, Julián y Rosi, por ser como unos padres y apoyarme en todas mis decisiones. Por acogerme en vuestra casa cada vez que la voy a ocupar y escucharme cuando os cuento mis cosas. Gracias a mis primos, Jorge y Pablo, por su apoyo y ánimo. A mis tíos Miguel Ángel, Juan y Conchi, y a mis primas Laura y Ángela, gracias por vuestro apoyo y cariño.

Que voy a decir a mi pequeño bichito, mi Carla, gracias por hacerme disfrutar de tu compañía, de los juegos, de volverme a ser niña a tu lado y hacerme olvidar los problemas. Gracias por quererme incondicionalmente, aunque menos de lo que te quiero yo a ti, eres la niña de mis ojos y espero poder devolverte un poquito de lo que me has dado.

CONTENIDOS PUBLICADOS Y PRESENTADOS

Published papers:

El contenido de estas publicaciones ha sido incluido en esta tesis. Los capítulos en los que aparecen son el 1, 3, 4, 6 y 7 debido al uso de los datos para la explicación de los resultados obtenidos en diferentes apartados. Además, el material de estas fuentes incluido en la tesis no está señalado por medios tipográficos ni referencias.

- *“On the role of processing parameters in sintered new Co-based (W,Al) alloys”*

M. Cartón-Cordero, B. Srinivasarao, M. Campos, A. García-Junceda, J.M. Torralba

Publisher: Journal of Alloys and Compounds (Elsevier), Volume 674, 25 July 2016, Pages 406-412

DOI: <https://doi.org/10.1016/j.jallcom.2016.03.077>

- *“Microstructure and compression strength of Co-based superalloys hardened by γ' and carbide precipitation”*

Marta Cartón-Cordero, Mónica Campos, Lisa P. Freund, Markus Kolb, Steffen Neumeier, Mathias Göken, José M. Torralba

Publisher: Materials Science and Engineering: A (Elsevier), Volume 734, 12 September 2018, Pages 437-444

DOI: <https://doi.org/10.1016/j.msea.2018.08.007>

Congress Contributions:

Todas las contribuciones a congresos han sido incluidas en esta tesis. Los capítulos en los que aparecen son el 1, 3, 4, 6 y 7 debido al uso de los datos para la explicación de los resultados obtenidos en diferentes apartados. Además, el material de estas fuentes incluido en la tesis no está señalado por medios tipográficos ni referencias.

- **M. Cartón-Cordero**, B. Srinivasa Rao, M. Campos, J. M. Torralba, "Microstructure and mechanical properties of Co-base $\gamma - \gamma'$ composites by mechanical alloying and field assisted hot pressing", Intermetallics 2013, Educational Center Kloster Banz, Germany. (Oral Presentation)
- Bonta Srinivasa Rao, **Marta Cartón-Cordero**, Mónica Campos, Jose Manuel Torralba Castelló, "On the role of alloying composition and processing parameters in Co-Base $\gamma - \gamma'$ composites", 2014 TMS Annual Meeting and Exhibition, USA. (Oral Presentation)
- **Marta Cartón-Cordero**, Bonta Srinivasa Rao, Andrea García-Junceda, Mónica Campos, Jose Manuel Torralba Castelló, "Development of new Co-bas superalloys by milling process and

consolidation by Field-Assisted Hot Pressing", 2014 Sintering, Dresden, Germany. (Oral Presentation)

- **Marta Cartón-Cordero**, Mónica Campos, Bonta Srinivasa Rao, Jose Manuel Torralba, *"Primera aproximación en la obtención de las nuevas aleaciones base Co por vía pulvimetalúrgica"*, 2015 National PM, Gerona, Spain. (Oral Presentation)
- **Marta Cartón-Cordero**, Mónica Campos, Jose Manuel Torralba, *"Mechanical Behaviour at high temperature of novel sintered Co-Al-W alloys"*, 2016 World PM, Hamburg, Germany. (Oral Presentation)
- **Marta Cartón-Cordero**, Mónica Campos, Luis Antonio Díaz, Jose Manuel Torralba, *"Desarrollo de aleaciones de Co-Al-W sinterizadas por SPS"*, 2016 Materials, Oviedo, Spain. (Oral Presentation)
- **Marta Cartón-Cordero**, Mónica Campos, Eric Macia-Rodríguez, Luis Antonio Díaz, Jesús Cano, Andrea García-Junceda, José M. Torralba, *"Estudio microestructural de aleaciones de Co-9Al-9W producidas por SPS con Ti Ta como aleantes"*, 2017 Materials, Ciudad Real, Spain. (Oral Presentation)
- **Marta Cartón-Cordero**, Mónica Campos, José M. Torralba, *"Microstructural changes on Co-9Al-9W alloy produced by SPS and Ti and Ta additions"*, 2017 Sintering, San Diego, USA. (Oral Presentation)
- **Marta Cartón-Cordero**, Mónica Campos, SJ Hong, José M. Torralba, *"Performance of Co-base Superalloys depending on alloying method"*, 2018 EuroPM, Bilbao, Spain, (Oral presentation)

OTROS MÉRITOS DE INVESTIGACIÓN

- ***“Effect of Zirconium on the Microstructure and Mechanical Properties of an Al-Alloyed ODS Steel Consolidated by FAHP”***

García-Junceda, A., García-Rodríguez, N., Campos, M., Cartón-Cordero, M., Torralba

J.M.Publisher: Journal of the American Ceramic Society (Special Issue: SINTERING 2014), Volume 28, Issue 11, 23 June 2015, Pages 3582-3587

DOI: <https://doi.org/10.1111/jace.13691>

Abstract

Nowadays, aircraft industry demands new efficient and clean engines to move the new generation airplanes. The engineering developments passes through improving the properties of the material at high temperature, especially in engine blades localized on the first step on high pressure turbine and on the structural material disposed on combustion chambers. Rises the resistance to temperature is going to improve directly the final engine efficiency and consequently reduce the costs per flight.

During the last decades, the Ni γ/γ' superalloys have been used thanks to their outstanding properties under those rough conditions. Thermal and dimensional stability, higher performance under creep conditions and oxidation resistance are the main requirements. However, Nickels monopoly was interrupted thanks to the irruption of Co-based alloys. Traditionally, those alloys were hardened by solid solution and carbides precipitation. However, Sato et al [1] developed in 2006 a ternary system Co-Al-W in which it was possible to develop a γ/γ' microstructure. This phase was found to be similar to the γ' in Ni-based superalloys, since both provides stable and $L1_2$ structure which is coherent with the fcc- γ matrix.

The main counter back was founded on W content in γ' phases whose hardening promoted induced poorer creeps' behaviour. As a solution, Ta was used for Suzuki et al. [2] to rise the mechanical properties under compression at high temperature. Thanks to the alloying elements and their anomalous flow stress behaviour at high temperature, leading into a material, which could even overcome Ni-based superalloys.

Commonly, Co-based superalloys were produced by conventional ingot metallurgy in order to avoid the inherent defects (such as macrosegregation, microsegregation, porosity, shrinkage

solidification and second-phase inclusions). This Thesis proposed an alternative route based on **powder metallurgy (PM)** as new proposal to manufacture the Co-based superalloys.

Co-based superalloys development passed through two different PM routes, studied in this research. The first one is based on elemental powders mechanical alloyed by high-energy milling and consolidated by FAHP (Field assisted hot pressing). The second one is focus in gas atomized powders followed by SPS (Spark Plasma Sintering). To realize both studies, two compositions were selected according to the Co-Al-W ternary diagram [1], **Co-9Al-9W and Co-8Al-8W** (both in at.%). Besides, using the gas atomized powder, Ti and Ta, were added by high energy milling to promote γ' precipitation.

Both routes resulting in a massive precipitation of γ' phase after solubilisation or homogenisation at 1250 °C during 24 h and ageing at 900°C during 24 h treatments. Controlling γ' amount, size and shape passes through optimize the thermal treatments.

In case of Superalloys consolidated from the atomized powder, the γ' precipitation was revealed during consolidation process without subsequent heat treatments. The γ' precipitation without heat treatments has not been reported until the publication of this research. The γ' precipitation, grain size reduction, solid solution, carbides precipitation or intermetallics formation are the different hardening mechanisms found in the Co-based superalloys obtained by PM, which contributed to keep the properties at high temperature.

Evaluating mechanical properties at high temperature were performed by compression tests. The reported results for the composition Co-9Al-9W obtained by PM routes reported three times higher values than the alloys produced by ingot metallurgy [2].

Resumen

Actualmente, la industria aeroespacial demanda el desarrollo de nuevos motores, más eficientes y más limpios para las nuevas generaciones de aeronaves. La demanda ingenieril pasa por la investigación de nuevos materiales destinados a piezas expuestas a alta temperatura, sobre todo en la primera etapa de turbina y en materiales estructurales para la cámara de combustión. Incrementar la temperatura de funcionamiento del motor desemboca directamente en una mejora de la eficiencia y por lo tanto en una reducción de costes por vuelo.

En las últimas décadas, debido a sus destacadas propiedades bajo condiciones extremas las superaleaciones de Ni con estructura γ/γ' han sido las grandes protagonistas en el sector. Entre ellas cabe destacar la estabilidad térmica y dimensional, buen comportamiento a fluencia y buena resistencia a corrosión. Sin embargo, esta distinción se ha visto interrumpida por la aparición de nuevas composiciones de superaleaciones en base Co, tradicionalmente endurecidas por solución sólida y precipitación de carburos. Fue en 2006 cuando Sato et al. [1], estudiando el diagrama ternario de Co-Al-W, encontraron que era posible obtener la microestructura γ/γ' en las nuevas superaleaciones en base Co. La fase γ' encontrada por Sato et al [1] era similar a la fase γ' de las superaleaciones de Ni, con estructura tipo L_{12} coherente con la matriz γ -fcc y estables con la temperatura.

Sin embargo, la principal limitación en estas aleaciones (Co-Al-W) residía en el contenido de W en la fase γ' , cuyo endurecimiento producía peores propiedades a fluencia. Suzuki et al. [2] encontraron la solución añadiendo Ta a la aleación, mejorando las propiedades a compresión del material a alta temperatura. Además, gracias a los elementos de aleación, el comportamiento anómalo a alta temperatura llega a superar incluso los valores de límite elástico alcanzados por las superaleaciones de base Ni consiguiendo así una superaleación muy competitiva.

A día de hoy, las **superalaciones en base Co** se siguen produciendo por colada. Sin embargo, estos métodos conllevan ciertos defectos como macro- y micro-segregaciones, porosidad, cambios de volumen o precipitación de fases secundarios. Esta tesis propone una alternativa a esas rutas basada en la **ruta pulvimetalúrgica (PM)**.

Para ello se han desarrollado dos vías pulvimetalúrgicas estudiadas paralelamente. En la primera, se parte de polvos elementales aleados por molienda mecánica de alta energía y posteriormente consolidados por FAHP (Field assisted hot pressing). En la segunda, se parte de polvos prealeados atomizados por gas y posteriormente consolidados por SPS (Spark Plasma Sintering). En ambos estudios se utilizaron dos composiciones; **Co-9Al-9W and Co-8Al-8W** (at.%) atendiendo el área de estabilidad de γ' en el diagrama ternario de Co-Al-W [1]. Además, se añadió Ti y Ta al polvo atomizado por gas por molienda mecánica de alta energía con el objetivo de favorecer la precipitación de γ' .

El resultado de ambas rutas fue la precipitación masiva de la fase γ' después de los tratamientos térmicos de solubilización (u homogeneización) a 1250 °C durante 24 h seguido de maduración a 900 °C durante 24 h. Controlar la cantidad, tamaño y forma de la fase γ' pasa por la optimización de dichos tratamientos térmicos.

En el caso de la segunda vía, en la que se usa polvo atomizado como precursor, la precipitación de γ' se consiguió durante el proceso de consolidación sin la necesidad de tratamientos térmicos posteriores. Hasta la fecha, no se han encontrado publicaciones que describan la precipitación de la fase γ' sin tratamientos térmicos. Además, las rutas pulvimetalúrgicas proporcionan sistemas de endurecimiento a la carta, como la precipitación de γ' , la reducción de tamaño de grano, solución sólida, precipitación de carburos o intermetálicos, los cuales contribuyen a mantener las propiedades de la aleación a altas temperaturas.

Para concluir el trabajo, se evaluaron las propiedades mecánicas a compresión de las superaleaciones en base Co producida por vía pulvimetalúrgica obteniendo muy buenos resultados. Además, para la aleación Co-9Al-9W dichos valores son tres veces superiores a aquellos obtenidos para aleaciones con la misma composición y fabricadas por inducción [2].

Preface

This thesis have been carried out at the Madrid Institute for Advanced Studies in Materiales (IMDEA Materials Institute) and at the Department of Material Science and Engineering and Chemical Engineering of the Carlos III University of Madrid. This research work has been founded by European project PilotManu under the EU FP7 programme.

To get the mention of International PhD, (following the “*artículo 15 del Real Decreto 99/2011*”), part of this work has been developed in close collaboration with Friedrich-Alexander-Universität Erlangen-Nürnberg (FAU) at General Materials Properties Department (High Temperatures Materials subgroup) and with the DAAD award for 3 months. Furthermore, two international experts have been reviewed the current manuscript: Dr. Cinzia Menapace from Trento University (Italy) and Dr. Ana Senos from Aveiro University (Portugal).

The results of this work have been presented and well received at International and National Conferences as an oral contributions, some of them published on peer reviewed proceedings. Besides, the results during the development of this Thesis have been published in top International Journal of the first quartile, such as Journal of Alloys and Compounds and Materials Science and Engineering A.

Contents

Chapter 1: Introduction	23
1.1. Superalloys.....	23
1.1.1. Hardening Mechanisms.....	24
1.2. State of the art of dual γ/γ' Co based superalloys	29
1.2.1. New dual phase Co-based superalloys.....	30
1.2.2. Alloying elements	31
1.2.3. Mechanical behaviour	32
1.2.4. Powder Metallurgy processing.....	34
1.2.5. Last developments.	35
Chapter 2: Motivation & Objectives	39
2.1. Motivation	39
2.2. Objectives	41
Chapter 3: Experimental procedure	45
3.1. Materials.....	46
3.2. Processing	47
3.2.1. Mechanical milling	47
3.2.2. Consolidation	48
3.2.3. Heat treatments	50
3.3. Characterization techniques	50
3.3.1. X-Ray Diffraction analysis (XRD).....	51
3.3.2. Thermogravimetric analysis (TGA)	52
3.3.3. Chemical analysis	53
3.3.4. Metallographic preparation	53
3.3.5. Microstructural characterization	54
3.4. Mechanical properties.....	56
3.4.1. Tests at microstructural level.....	56
3.4.2. Compression tests.....	57
Chapter 4: Results	61
4.1. Manufacturing of Co based alloys	63
4.1.1. Mechanical alloyed Co based powders.....	63
4.1.2. Gas atomised Co based powders	67
4.1.3. Partial remarks	72
4.2. Microstructural features of Co-based superalloys	73
4.2.1. Designing γ/γ' from MA powders.....	73

4.2.2. Designing γ/γ' from Atomised powders	82
4.2.3. Partial remarks.	94
4.3. Mechanical Behaviour	95
4.3.1. γ' precipitation hardening mechanism.	95
4.3.2. Carbides and high deformation hardening mechanisms.	99
4.3.3. Ti and Ta effect on the hardening mechanism.....	102
4.3.4. Partial remarks	105
Chapter 5: Conclusions	109
Chapter 6: Annex I	115
6.1.1. Optimization study of Co based composition and mechanical parameters	115
6.1.2. SS-Alloys: Influence of milling time and alloying system.	116
6.1.3. SS-Alloys vs. HM Alloys: Effect of grinding media.	120
Chapter 7: Annex II	125
7.1.1. Optimization parameters study of consolidation process by FAHP and SPS	125
7.1.2. Consolidation by FAHP	125
7.1.3. Microstructural analysis: phase determination and distribution	127
Chapter 8: Papers and Congress	143
8.1. Papers.....	143
8.2. Congress Contributions.....	144

Chapter 1: Introduction

Chapter 1: Introduction

1.1. Superalloys

“A superalloy is an alloy developed for elevated-temperature service, usually based on group VIIIA elements, where relatively severe mechanical stressing is encountered, and where high surface stability is frequently required”.

T.Sims in The superalloys book [3]

In case of structural metals, the material application is determined by the strengthening mechanisms being the high temperature application the main objective of this research. For this reason, the main theme of this section is to know the evolution of the strengthening mechanisms in the high temperature materials that could help to understand the current work.

On one hand, the surface should be stable from room temperature up to high temperature as well as the stability of the microstructure. Some phase transformations can promote volume changes that could modify the dimensions of the parts causing a dramatic failure. In addition, the oxidation behaviour is important due to the extreme environmental conditions in which those materials work.

Additionally, the mechanical response is function of the working temperature due to the different deformation mechanisms that are activated at room temperature (RT) or at high temperature. At low temperature the plasticity is limited by discrete obstacles. The dislocation

slip determines the material plastic deformation. But as T rise, three other mechanisms start to play, the dislocation climbing, the grain boundary sliding and the diffusion flow caused by vacancies.

The evolution of the strengthening mechanism developed for superalloys is drawn for the Ni based ones from the 30's to the 90's in Figure 1-1, those alloys are the most used and developed materials for aircraft high temperature applications. The precipitates displayed on the top of the Figure 1-1 (γ' , $M_{23}C_6$, MC, etc.) are the ones that help to get good fatigue and creep resistance, increasingly the strength at high temperature. On the other hand, the precipitates displayed on the bottom (η plates, cellular $M_{23}C_6$, Sigma, etc.) are the precipitates that cause brittleness and/or lowered the strength reducing the performance of the alloy.

Figure 1-1. Evolution of nickel Superalloys microstructure from 1940 to 1990, detailing the beneficial and the adverse phases [4].

The next section will explain the effect of the precipitates explained below in the hardening mechanism in the superalloys.

1.1.1. Hardening Mechanisms

In general, the hardening mechanisms are combined due to the difficulty of insulating some of them. The monocrystal manufacturing is an example where the hardening mechanisms are well controlled. In this case, the grains size could be avoid with manufacturing a monocrystal, which is produced with a slow and strict control of alloy growth. Due to the production costs and its properties, the monocrystal materials are used in critical pieces, like aircraft blades.

It is true that the creep performance of monocrystals is incomparable, but the production costs are very high. Even knowing that the replacement of monocrystal alloys is difficult, the control of hardening mechanisms in superalloys could get close properties to that structure.

1.1.1.1. Grain boundary strengthening.

In a solid metal, grain boundaries connect two different crystal orientation in a few nanometres where there is a gap or a misalignment of atoms. That border is an insuperable barrier for dislocations, so they are forced to pile up in the grain Figure 1-2. Then the dislocations are held in the grain and increases of the dislocation density impeding the plasticity.

As the grain size decreases, the larger area of grain boundaries impede higher is the obstacle for the dislocation movement. Hall-Petch described the grain size effect on the yield strength [6], where varies with grain size $-d$ according to the Equation 1-1.

Equation 1-1. Hall-Petch equation.

$$\sigma_y = \sigma_0 + \frac{k_y}{\sqrt{d}}$$

where the σ_y is the yield strength, σ_0 is the force required to slip the dislocations in the material (or the resistance of the lattice to dislocation motion), k_y is the strengthened constant that depends on the material and d is the average diameter of the grains.

As infinitely strong metal does not exist, this strengthening mode has a limit. When the size of dislocation begins to approach the size of the grains, it is not possible to promote the dislocation pile-up, and in this scenario, the sliding of grain boundaries is activated [7].

The grain size control in superalloys were carried out with the addition of alloying elements, such as B, Zr or Hf. This elements promotes a precipitates in the grain boundary preferentially, which avoid the grain growth and strengthen the boundary [8].

1.1.1.2. Strain Hardening.

The dislocations generate a stress field around them; throughout the material the interaction between the stress fields intersect each other's impeding the dislocation movement making the material stronger. This interaction could be attractive or repulsive depending on the dislocation sign. Therefore, there is a correlation between the dislocation density and the yield strength of the material (Equation 1-2). As the dislocation number is increased, the amount of stress necessary to plastically deform the material increases.

Equation 1-2. Relation between Yield strength and dislocation density.

$$\Delta\sigma_y = G \cdot b \cdot \sqrt{\rho_{\perp}}$$

G is the shear modulus, b is the Burgers vector, and $\rho_{\perp}$ is the dislocation density

Figure 1-2. Schematically picture of grain boundary strengthening [5].

1.1.1.3. Solid solution hardening.

Solid solution is formed when a small amount of guest element occupy positions into the host lattice. These positions could be interstitial positions, which is occupied by atoms smaller than the host ones, and reticular position that is occupied by bigger or similar atoms than the host lattice elements.

Figure 1-3. Scheme of interstitial (up) and reticular (bottom) solid solution atoms [9].

Particularly in superalloys, the most hardened used elements are the bigger ones, such as W, Mo or Ta, among others. Their big size and hardness strengthened the alloy due to the lattice distortion. On the other hand, their high melting temperature and low dissolution into the host lattice, make difficult the completely solid solution formation.

The external atoms produce a build-up of energy in that area that distort the lattice increasing the material hardness. Those forces are in opposite direction, the force for bigger atoms puts an outward strain in that vicinity instead smaller atoms produce inward strain (Figure 1-3). The guest atoms could form a cluster due to the dislocation movement or the atom movement activation working like a precipitate.

Also, those clusters could be formed due to the limit of dissolution of the host lattice has for the guest elements. When the lattice gets the maximum, the distortion and the energy in the lattice is high making it unstable. At that point, the material tries to reduce this energy, and consequently the hardness of the material, finding more stable states that could be precipitates or clusters.

When the precipitates have been formed, the alloying elements have a preference for one phase due to the reactivity or the phase structure. This preference could produce a hardened precipitated regarding the type of element. For example, Mo, W or Nb precipitated as carbides preferentially. On the other side, Y, Al or Cr form oxides in order to improve the oxidation behaviour.

The alloying element selection is important in order to adjust the properties of the material to the application. Because of depending of their preference phase, could stay at solid solution or form a precipitate.

1.1.1.4. High temperature precipitation hardening.

The hardening precipitates used in superalloys are carbides, intermetallics and γ' precipitates mainly, also it is possible to precipitate nano-oxide well dispersed throughout the matrix pinning the dislocation. Each precipitate activates different hardening mechanisms.

The main hardening precipitated used for strengthening the material at high temperature is the γ' phase. This phase has a $L1_2$ structure and is semi-coherent with the fcc- γ matrix. The stoichiometry of this phase depends on the alloy composition, for example for Ni based superalloys is Ni_3Al . The stoichiometry could change when the alloy has γ' stabilisers alloying elements, that is the case of $Co_3(Al,W)$ in Co-based superalloys.

In the case of Ni-based superalloys, γ' precipitate when the matrix reach the limit of Al dissolution. Before reaching the dissolution limit, the Al atoms occupy position in the Ni lattice randomly. In this moment, the Al atoms are in a specific positions, the new phase (γ') precipitated.

The γ' precipitates are semi-coherent with the matrix due to both lattice has a cubic structure and have similar parameters (Figure 1-4). The semi-coherent precipitates promote distortion in the matrix lattice around them. This coherency and consequently the grade distortion are measured with δ parameter, which is called hereinafter misfit, in the following equation:

Equation 1-3. Misfit equation

$$\delta = \frac{2(a_{i'} - a_i)}{a_{i'} + a_i}$$

where $a_{i'}$ and a_i are the lattice of the precipitate and the matrix respectively. When this parameter is big, the coherency between the precipitate and the matrix is small. Then, the distortion in the boundary is bigger and hinder the dislocation movements. This semi-coherent precipitates are strengthened effective than the incoherent precipitates.

Figure 1-4. Precipitation hardening from semi-coherent γ' precipitate [10].

The γ' precipitate throughout the matrix forming horizontal and vertical γ channels. It is through these channels where the dislocation movement take place, and the γ lattice distortion, induced by γ' precipitates, impedes them.

Also, the coherency is related with the size of the γ' , the coherency decreases when the precipitate grows. In order to control the size and shape of the γ' , there are two ways and the most of the time they are combined. The first one is the heat treatments control, where the temperature, time and cooling and heating rates play an important role.

The temperature favours the atoms movement in order to get the minimum amount of the element that form the precipitate. In the γ' case, two steps, the solubilisation and the ageing compose the heat treatments. The solubilisation temperature should be close to the precipitation temperature to promote the nucleation of the precipitate. And the ageing temperature should be enough to promote the precipitates growth.

The holding time at both steps should be studied in order to control the precipitate growth. In general, the precipitate shape evolution is drawn in Figure 1-5, where the temperature and holding time increase on the left hand. When the time or the temperature are high, the atom movements is longer growing the precipitate and losing the coherency with the matrix. On the contrary, at lower temperature, the energy is not enough for growing and the shape is rounded with high coherency.

Then, the γ' precipitates are more strengthened effective when the shape of the precipitate is cuboidal and maintain the semi-coherency with the matrix.

On the other hand, the second way is to alloy the material with γ' stabilisers elements (Ti, Ta...) that reduce the γ' solidus temperature and increase the stable area. Besides, the shape of the γ' is more cuboidal due to the stability of the phase increase.

Figure 1-5. Shapes of growth precipitates according to the coherency with the matrix [11].

Additionally, the precipitation of carbides or intermetallic with rounded shape and well dispersed throughout the matrix increase the material strengthened. For example, the MC carbides or the $M_{23}C_6$ in the grain boundaries increase the hardness of the material.

1.2. State of the art of dual γ/γ' Co based superalloys

Temperature tolerance is one of the most significant limitations in the evolution of many engineering systems. One clear example is the altitude at which airplanes can fly, which is

Figure 1-6. TEM image of γ - γ' microstructure in Co-9Al-9W alloy (A) and the diffraction pattern of both phases (B) [1].

directly linked to the working temperature of the engine turbines. Another example is the limitation in the development of materials used for fusion reactors. As the working temperature for one specific working environment becomes more limited, the number of materials that can be used in these conditions is strongly reduced. High temperature materials primarily include ceramics and ceramic matrix composites, such as carbon-carbon composites.

However, the family of ceramic materials suffers from poor reliability and lack of ductility, issues that are even more problematic than their cost, which impede their general use in many engineering applications that

require materials that can be designed via the ductile fracture mode.

In the ranking of high temperature materials, after the ceramics, we find the so-called superalloys, the titanium alloys, and, more recently, the intermetallics. In all of these materials, the structural mechanisms that enable satisfactory behaviour at high temperatures are similar: microstructures consisting of two phases with specific morphologies and the dispersion of fine precipitates produced via a well-designed heat treatment.

Some examples of phase morphologies include the “basket” morphology observed in Ti-based alloys, cuboid-shaped secondary phases observed in some Ni-based superalloys, and the “lamellar” morphology observed in some intermetallics. In all of these materials, the dispersion of fine precipitates produced with a well-defined heat treatment that inhibit the movement of dislocations is a key factor in the development of the alloy.

Figure 1-7. Isothermal section diagrams of the Co-Al-W ternary system in the Co-rich portion at (A) 1173 K and (B) 1273 K. [1]

Focusing on the primary family of metallic materials for high-temperature applications, the Ni-based superalloys, and their good behaviour under high-temperature conditions is due to the existence of an fcc matrix with fine intermetallic precipitates of well-controlled structures and

morphologies. From the study of some of these precipitates in a separate context, a new family of high-temperature materials, “the intermetallics”, has been developed. The titanium aluminides are one example of these materials.

1.2.1. New dual phase Co-based superalloys.

Similar to nickel, cobalt exhibits fcc structure at high temperatures. Though the melting temperature of cobalt is higher than that of nickel (1495 °C versus 1455 °C), the potential of nickel-based to function at high temperatures is much greater due to the specific microstructure observed in these alloys, which is based on the precipitation of an ordered phase, γ' , onto the fcc matrix (γ). This type of microstructure is referred to as the γ/γ' structure. The γ' ordered phase exhibits stoichiometry of the type A_3B , as in $Ni_3(Al,Ti)$, which has an $L1_2$ structure. Traditionally, cobalt-based superalloys used in high-temperature applications are formed by the precipitation of secondary carbides or from solid solutions of some refractory metals.

It was in 1971 when Charles Samuel Lee [12] studied the Co-Al-X systems, where he founded two Cu_3Au structures in the Co-Al-W system. After some years, in 2006, Sato et al. [1] found the $L1_2$ structure in the Co-Al-W ternary diagram at 900 and 1000 °C (Figure 1-6 and Figure 1-7). This structure, which precipitates with the Cu_3Au structure reported by Chalses Samuel, has a similar microstructure than the Ni_3Al in Ni based superalloys. Those precipitates have $Co_3(Al,W)$ stoichiometry with cubic structure coherent with the fcc-matrix, here in after, those precipitates will be denominated γ' . Suzuki et al. [2] measured the Yield Stress (Y.S.) of Co-based superalloys at high temperature with similar behaviour of commercial Ni-based superalloys (Waspaloy). Even the Co-based Y.S. surpass the Ni-based superalloys at high temperature when 2% of Ta, which is γ' stabiliser, was added to the Co-9Al-10W (Figure 1-8).

The anomalous behaviour of Co-based superalloys at high temperature was founded in Ni-based superalloys. Where the amount of Al and the alloying elements could modify the temperature in which the Yield stress increases [13]. When T rises and the Yield stress increases, the γ' hardening mechanism is activated avoiding the dislocation movements and some twins could be produced in the γ' precipitates. As Figure 1-8 shows, the addition of Ta to the alloy increase the range in which γ' is the main strengthening mechanism. This is due to the γ' has been stabilise by Ta addition.

These findings opened a new pathway to develop a new superalloy with similar mechanical behaviour as Ni-based superalloys. The similarities between Ni and Co suggest that some Ni-based developing could be used in the new Co-based superalloys. However the γ' area stability in the Co-Al-W ternary diagram is smaller at high temperature [5, 8].

Figure 1-8. Yield stress comparison of commercial Co-based superalloys (wrought alloy: Hayness188 and cast alloy: MarM302) and Ni-based superalloys (MarM247) with Co-9Al-9W and Co-9Al-9W-2Ta [2].

Then, the first aim of the researchers is to increase the stability area of $L1_2$ phase, for that propose it was necessary to run parallel simulation and experimental works in order to understand the phase behaviour [9–11]. Also, Kobayashi et al. [18] studied the Al and W diffusion in Co using Co-Al and Co-W alloys and annealing at different temperatures. Demonstrating that γ' is metastable and γ , CoAl and Co_3W are in equilibrium at 900 °C.

1.2.2. Alloying elements

In the way to increase the γ' area stability, which means the increment of γ' volume fraction, the Al and W amount were modified [14–16]. It is important to take into account that when the amount of W is high, the density and the weight of alloy increases proportionally as well as the

Figure 1-9. γ' volume fraction in Co-based alloys with different compositions [19].

brittleness due to the precipitation of intermetallics such as Co_3W or Co_7W_6 [23–26].

The limitations of Co-based superalloys could be solved by adding alloying elements. For example, the addition of 2 at.%, or even less, of some elements could change and improve the properties considerably.

Due to the good results obtained for Ni-based superalloys, some authors add Ni to Co-based superalloys due to the good dissolution of Ni in Co lattice. Ni stabilises γ phase

and in accordance with the Shinagawa et al. work [27], the amount of Ni could change the element partitioning and consequently the shape of the γ' [18, 28]. When the shape of the precipitate is modify, that is mean that the coherency between γ and γ' (δ) changed.

In order to minimise the Ni effect, it is necessary to add alloying elements that stabilise and increase the γ' area and the solvus temperature. Also, the alloying elements solve the negative effect of Ni on the interdiffusion coefficient [25, 26]. Those elements achieve to increase the γ' stability and therefore the volume fraction of γ' getting higher solvus temperature with an offset of 200 °C [17–20].

Regarding the γ' volume fraction, Ti and Ta were the most effective alloying elements which promotes a high volume of γ' (Figure 1-9 and Figure 1-10) [12, 27–30]. Also, Nb and Hf have a slightly positive effect on the volume and solvus temperature of γ' precipitates. The addition of those elements reduce the density due to the small amount necessary to get a high γ' volume fraction making the used of W as a strengthened element. Additionally, the γ' geometry is closely related with the alloying elements and their amount, where the shape could be from square to rounded, which is the undesirable one. The addition of small amount of alloying elements is the way followed for different research groups to change the properties considerably [12, 22–25].

Figure 1-10. Liquidus, solidus and γ' solvus temperatures of Co-based alloys with different compositions [42].

In addition, different alloying elements solved the limitation of Co-based alloys at high temperature. For example, a 0.02 % (at.%) of B change the fracture behaviour from inter to intragranular improving the strengthened of the Co-based alloy due to the precipitation of borides on the grain boundary [36, 37]. In the same way, those borides block the grain growth making the microstructure more stable during the heating. Also, the B enhanced the oxidation behaviour of Co-based superalloys, likewise, to add Cr or Si has the same effect as B but with better oxidation results [26–28]. It is the formation of a fine oxide line on the surface that protect the alloy against the extreme conditions. In general, the aluminium or chromium oxide are the most protective compounds due to the oxide stability promotes the passivation of the surface [39, 41, 42].

1.2.3. Mechanical behaviour

On the other hand, the mechanical behaviour study is critical to find the correct application, initially the application of those alloys should be for high temperature, where a high yield strength and a good creep resistance are required. When the compression behaviour of Co-based superalloys is compared to Ni-based superalloys, the anomaly behaviour at high temperature that exhibits Co-based superalloys could overcome the Ni-based results (Figure 1-11).

Figure 1-11. Strain rate comparison of different studied alloys [50].

This anomalous behaviour occurs at different temperatures depends on the alloying elements and the microstructure, for example, when Ta was added it happens at higher temperature (Figure 1-8).

Moreover, an important challenge to solve in Co-based superalloys is the low creep values at high temperature compared to Ni-based. This property is important when the material is working under fatigue and extreme conditions, where the γ' could be destabilised. The γ' stabilisation and the extension of working range temperature were solved by adding alloying elements, as it was mentioned previously. Then, those elements that stabilise the γ' phase, such as Ti and Ta, could enhance the mechanical properties [27, 31]. Apart from the Yield stress, Ti improves the minimum strain rate of Co-based superalloys [52].

At this point is where the misfit (δ) is a key factor to explain the creep increment in Co-based alloys (Figure 1-12) [54]. There is an accordance that alloys with a positive δ gets a high deformation resistant than that ones with negative δ . That is due to an external tension creates differential levels of equivalent stress in the vertical and horizontal γ matrix channels. In contrast to Ni-based superalloys, Co-based has a positive δ , which is positive for creep in accordance with different researches. A positive δ activates the rafting parallel to the stress axis that impeded, in the same way, the fatigue cracks propagation because of cutting the hard γ' rafts requires more energy. Also, a rod-like γ' structure in the parallel direction to tensile loading (P-type rafts) is formed by γ' precipitate coalescence. And, it is expected that normal to the compressive loading direction is formed a plate-like γ' structure on the transverse face (N-type raft). It is important to take into account that δ is hard affected by composition, in other words, δ contributes to the microstructure evolution and mechanical properties.

Figure 1-12. Temperature dependence of γ and γ' lattice parameters and misfit of Co-based alloy with 2Ta addition [53].

To be more specific, the relation between lattice parameter affects to the precipitate morphology, the alloy strengthening via coherency strains and precipitates coarsening. Then, the alloying elements play an important role because of if the γ' precipitates precipitate easily and are more stable, the δ value could be small and have less coherency [47–50].

1.2.4. Powder Metallurgy processing.

Heretofore, the manufactured process has not been mentioned yet, being the cast method the most popular manufacturing process to fabricate the Co-based superalloys. In 2012, Zhang et al. [58] precipitated the γ' in the Co-ODS alloys manufactured by powder metallurgical route following the Sato et al. [1] discovers. This alloy has two important advantages: a fine grain size and a fine oxide well dispersed throughout the matrix. These oxides helps to pin the dislocation movements improving the fatigue behaviour whereas the fine grain increase the stress of Co-ODS alloys. Also the powder route gets a better composition and features control.

Figure 1-13 shows the microstructure of Co-ODS alloys produced by Zhang et al. with 9Al-7.5W-1Y2O3-1.5Hf-Co bal (at.%) composition, where the microstructure is composed by γ/γ' matrix. Hf increases the γ' stability and promotes its precipitation, also it could precipitate as oxide increasing the mechanical properties and the oxidation resistance, as it was mentioned previously. Following the previous discovers, the addition of Ni to this alloy [(10-50)Ni-10Al-7.5W-1Y2O3-1.5Hf-Co bal (at.%) [59]] increases the γ' volume fraction and the mechanical behaviour at high temperature as it is depict in Figure 1-14 and compared with a previous Zhang et al. work [60].

Due to the different strengthening mechanisms, the Yield Stress drop drastically at high temperature. The main hardening mechanisms could be nano-oxides, small grain size, secondary precipitates (such as Co_7W_6 or Co_3W), etc, which hide the anomalous behaviour that Co-based superalloys have at high temperature.

Figure 1-13. SEM image of Co-ODS based alloys with 7.5 of W and after solution-treated [58]

Figure 1-14. Co-based ODS alloys: Top. SEM imagen with 50Ni and Yield stress of 40Ni compared to Co-based alloys [59].

1.2.5. Last developments.

In the last three years, the aim of new researchers is to reduce the density of those alloys, increasing the γ' solvus temperature and enhancing the mechanical properties at high temperature. On one hand, the oxidation resistance improvement was studied by Klein et al. [46, 47], where the use of Ni could produce Al_2O_3 that protects the alloy or Ni_3S_2 that to aggravates the oxidation. Besides, the eutectic formation under the oxidation line during the heat treatment activate the oxygen reaction. Following this idea, the oxidation behaviour is being studied in alloys with Ni, where the addition of Cr, Si and Al improve the oxide protect line [61, 62].

And on the other hand, the elimination of W in this alloys reduces the density considerably, that is why it is trying to find γ/γ' Co-based alloys without W. That is the case of Zenk et. al [63], who has γ/γ' microstructure in Co-Ti alloys with a small δ but high γ' volume fraction. They increase the δ with Cr addition and get a good yield values. On contrary, if the W amount is reduced, the γ' solvus temperature and the γ' hardening effect decrease.

At the same time, the simulation works continuing testing the diffusion and γ' morphologies in order to get the best alloy design [44–46]. Also, the alloying elements are studied focusing on Ta and Ti elements but with other additions such us B, Ce or Mo [41, 42]. As well as, the mechanical properties are parallel researched, especially the creep behaviour [43–45].

Chapter 2: Motivation & Objectives

Chapter 2: Motivation & Objectives

2.1. Motivation

The aircraft industry requires a constant improvement of the mechanical properties at high temperature of materials to enhance their service life. Furthermore, the materials are exposed to extreme environmental conditions due to the continuous engineering development. The materials that can achieve the better behaviour at high temperature are ceramics and ceramic matrix composites. However, those families also have poor ductility and reliability, and these facts are a challenge for the use of superalloys.

Superalloys are one of the most frequently materials used at high temperature. They have one of the best compromise between strength and ductility at high temperature. The good behaviour of these families of alloys at high temperature comes from their microstructures that present two phases with a specific morphology and with fine precipitates in the microstructure obtained by heat treatments. This fine precipitates are designed to inhibit the movement of dislocations. In γ base alloys, this secondary phase is usually called γ' , which has Ni_3Al stoichiometry in Ni base superalloys. The γ' precipitates in fcc crystal structure (L1_2) with cuboidal shape and it is coherent with the γ -fcc matrix.

Co-based alloys are conventionally used for cutting tools or wear materials due to its excellent oxidation, corrosion and wear behaviour. Hence, Co-base alloys also have been developed as an alternative materials for high temperature applications instead Ni-base or Fe-base alloys.

Co is, like Ni, Fe and Ti, a transition metal in the periodic table, and as a transition metal it share with them some properties and characteristics such as high melting points, high hardness and good electrical and thermal conductivity. However, Ni and Fe-Ni (usually used for high temperature applications) has fcc structure at room temperature but the more stable structure for Co is hcp. Nevertheless, Co has two allotropic states and the structural change happened at 475 °C, from hcp to fcc. However, stabilizing the Co-fcc structure at room temperature is easy due to the low energy activation of its sliding planes.

Traditionally, Co-base superalloys are hardened by solid solution with refractory metals and carbide precipitation. Owing to Co position in the periodic table, we could expect similar precipitates than Ni-base superalloys. Sato et al. [1] discover in 2006 the γ - γ' structure in some Co-Al-W ternaries alloys. The γ' structure has a $\text{Co}_3(\text{Al,W})$ stoichiometry and L1_2 structure, which is fcc and coherently with the fcc-Co matrix (γ) that has similar structure and properties than Ni-base γ - γ' superalloys. Nevertheless, Co-base superalloys have an anomalous behaviour at high temperature that could be overcome the Ni-base superalloys properties [2] because of the γ' precipitates.

Generally, Co-base superalloys are manufactured by conventional ingot metallurgy, as arc or induction melting, which requires careful control to avoid defects such as macrosegregation, microsegregation, porosity, shrinkage solidification and second-phase inclusions. Additionally, the cost of machining and thermomechanical processing is high.

These drawbacks can be overcome by using a near net shaping technology, such as powder metallurgy (PM), which enables the production of nearly full density products with a minimal amount of material. To understand the potential of this fabrication route, some studies of adding Y_2O_3 particles to Co-Al-W alloy systems have been performed recently. In 2009, Zhang et al. [70] added small amounts of Ti, Zr, Ca, Hf and Al to a Co- Y_2O_3 -based ODS (Oxide dispersion strengthened) alloy by high-energy milling to disperse coherent or semi-coherent oxide nanoparticles uniformly throughout the matrix, thereby improving its high-temperature properties. These ODS alloys were characterized by hot compression and shown to be promising for high-temperature applications [59]; although the alloys produced by PM route could have less density, because of the porosity. Ameyama studied the density enhancement [71, 72] in different alloys (Co-Cr-Mo, Ti-based...) with harmonic structure by PM route. The harmonic structure consists of a core grain surrounded by a connected shell grain, which increases the contact surface to optimise the consolidation process. Furthermore, the mechanical properties have been improved as a result of the bimodal structure, in which the rise in strain is due to the core grains and the rise in stress is due to the shell grains [73–75].

This manufacturing route has not been explored yet and could have many advantages, to name just a few: the flexibility in the selection and development of the alloys compositions (comparing to the melting process), the better control of the microstructural features avoiding segregations and undesirable precipitation of secondary phases, the homogeneous distribution of the fine precipitates, etc. As well as, the PM route allows to produce materials with small grain size, even being nanograin size, with high density of dislocation and microstrain through the net. This high level of deformation in the net after mechanical milling keeps the grain size after consolidation although the technique requires the application of temperature and pressure simultaneously. In fact, the small grain size has an improvement in the final mechanical properties.

2.2. Objectives

The main goal of this research is to design the optimum composition of sintered Co based superalloys and to study the capacity to tailor the microstructural features throughout the consolidation and heat treatments and related them with a good performance at high temperature.

To prepare a collection of microstructures for assessing the mechanical behaviour of processed materials, the research is organized within several partial objectives and milestones:

1. To design the composition range within the Co-Al-W system to achieve the desirable dual γ - γ' microstructure keeping the lower level of W content.
2. To optimize the powder processing (by atomization or high energy milling) to promote the $\text{Co}_3(\text{Al,W})$ precipitates with L1_2 structure after consolidation.
3. To obtain an array of microstructures depending on the powder processing, composition and thermal history. The first step is to consolidate the materials close to full density. Afterwards, to devise proper solubilisation and ageing steps to prompt dual γ - γ' . The relationship between microstructure and mechanical properties according to composition and source material will be also analysed.

Chapter 3:

Experimental procedure

Chapter 3: Experimental procedure

The outline of the process to obtain and characterize the Co-based superalloys is presented in Figure 3-1. The procedure is divided in four sections: materials, processing, heat treatments and mechanical properties. In each step, the obtained material were characterised in order to reveal the microstructural features.

The alloys have been produced by PM route from two sources of materials atomised and mechanical alloyed. The characterization has been done based on XRD, DSC, DTA, LECO, SEM and TEM analysis.

Eventually, to obtain bulk samples to fulfil the characterization of the alloys, powders were consolidated by FAHP (Field Assisted Hot Pressing) and SPS (Spark Plasma Sintering). The heat treatments on some of the samples also were developed to favour the γ - γ' structure.

Figure 3-1. General scheme of Co-based superalloys processing route.

3.1. Materials

Sintered Co based superalloys have been obtained from the starting materials shown in Table 3-1.

Table 3-1. Starting materials used for the development of this work.

Base Powders			
Material	Commercial name	Manufacturer	Features ¹
Co	Co6160 (99.7%Co, 0.6 %O max)	Eurotungstene (France)	Fisher grain size (μm): 3.5 ± 0.5 Scott apparent density (g/cm^3): 1.7 ± 0.25
W	AW4105 99.9%W, 0.02%O	Eurotungstene (France)	Fisher grain size (μm): 20
Al	Al 54NS (99.0%Al)	SultzerMetco (Switzerland).	Fisher grain size (μm): 90 ± 45 Scott apparent density (g/cm^3): 9
γ' Stabilizers			
Ti	>99,6% met. purity	Gfe mbH (Germany).	-
Ta	Tantalum 99,9%	Gfe mbH (Germany).	-

The main characteristics of the base powders are collected in Table 3-2. The cross sections of the powder were studied by SEM and the phases were detected by XRD.

Table 3-2. Basic characterization of powders.

Base Powders		
Cobalt	Aluminium	Tungstene

Additionally, the atomised powder with Co-9Al-9W (at. %) as nominal composition was provided and produced by gas atomization at National University of Kongju. The characteristics of atomised powder are shown in Table 3-3.

¹ *Fisher grain size or Fisher number: Average particle size determined as an average particle diameter. Assuming the particles are monosize, smooth surface, nonporous, spherical particles it is considered the envelope-specific surface area of powders, from which is calculated the "average" particle diameter

Table 3-3. Atomised powder characteristics.

Base Powders		
Material	Description	Features ²
Co-9Al-9W	Gas atomized by Nacional University of Kongju (0.04 %O)	Size (μm): 40 to 150

3.2. Processing

The Co-based superalloys processing starts from powders produced by mechanical alloying or gas atomizing, following by consolidation with FAST (Field Assisted Sintering Techniques) or SPS (Spark Plasma Sintering) to obtain a nearly full dense materials, and according with the chart of Figure 3-2.

Figure 3-2. Scheme of processing Co-based superalloys by PM route.

3.2.1. Mechanical milling

Two types of planetary mills were used to produce the mechanically alloyed powders, Pulverisette 6 classic and Pulverisette 7 premium (Fischer). The operating mechanism of both equipments are the same, where the vessel (that contains the raw powders and grinding balls) rotates around itself axis on a holder which pivots around a central in the opposite direction. The centrifugal force produce the impact of the balls with the powder and vessel walls promoting the alloying powders. The efficiency of planetary mills is the result of the high kinetic energy of grinding media thanks to the planetary orbit that the vessels describe during the milling.

The amount of processing powder was set to keep the ball-to-powder ratio, filling the vessel at 33 % of the total volume.

a. High energy mechanical milling.

The high energy mechanical milling (HEM) was carried out in a planetary Pulverisette 6 classic with the milling parameters gather in Table 3-4.

² *The particle size was measured by Mastersizer 2000 following the standard ISO 13320:2009.

Table 3-4. Parameters of high energy milling process.

Milling media material	Hard Metal – Co-WC
Vessel volume	500 ml
Balls size	10 mm
Ball:Powder Ratio	10:1
Atmosphere	Static Ar
Speed (rpm)	300

b. Low energy mechanical milling.

On the other hand, the low energy mechanical milling (LEM) was performed in a planetary Pulverisette 7 premium setting the milling parameters according the Ameyama works [71–79] (Table 3-5). According this later works, it is obtained an harmonic structure (core-shell type) that compromises a small and deformed grain size at the edge and coarse grain size at the core of the particles. The harmonic structure were produced in the Co-9Al-9W atomised powder.

Table 3-5. Parameters of low energy milling process.

Milling media material	Stainless Steel
Vessel volume	80 ml
Balls size	10 mm
Ball:Powder Ratio	1.8:1
Atmosphere	Static Ar
Speed (rpm)	150

The families of processed powders are shown in Table 3-6.

Table 3-6. Nominal compositions of Co-based alloys produced by PM (at%).

Material composition					Manufactured process	Material tag
Co	Al	W	Ti	Ta		
84	8	8			High energy milling	Co8-8
82	9	9				Co9-9
82	9	9			Gas atomization	Co9-9-At
82	9	9			Gas atomization + low energy milling	Co9-9-At-ar
78	9	9	2	2	Gas atomization + high energy milling	Co9-9-At-Ti/Ta

3.2.2. Consolidation

Both selected FASTs for consolidating the alloys (FAHP and SPS) have been set to obtain fully dense materials form the powders, but they have some technical differences. These techniques apply simultaneously temperature and uniaxial pressure increasing the thermo-efficiency of the process that needs short holding times at maximum Temperature, avoiding the grain size growth and maintaining the structural features of the materials.

Figure 3-3. Scheme of current flow through the powder into the consolidation die.

https://www.researchgate.net/publication/287175102_Challenges_and_Opportunities_for_Spark_Plasma_Sintering_A_Key_Technology_of_a_New_Generation_of_Materials

The powder were poured into a cylindrical graphite die and covered with W foil and closing the set up interring the punches (Figure 3-4 a). Both materials, graphite and W, are excellent electrical conductors in order to heat the die with a current that heats the powder by Joule effect. The current passes through the particles assisting the neck formation supported by mechanical pressure. The high frequency of the electrical current produce a spark between powder particles reaching the boiling temperature in a local point, where the powder surface suffers a localized vaporization or cleaning (Figure 3-3).

Both FASTs have some technical differences that will be explained in the next sections.

a. Field Assisted Hot Pressing (FAHP).

To carry out the consolidation by FAHP, a Gleeble 3800 equipment (Dynamic System Inc., USA) with horizontal design was used. The processes were performed under vacuum ($\sim 10^{-5}$ mBar) controlling temperature and load.

The temperature was achieved by continuous low frequency alternating current (a.c.). It was measured by R and K type thermocouples placed at the punch and matrix (Figure 3-4 a.), respectively, which were glued with a high temperature cement. The die had a cylindrical shape with 10 mm of diameter.

The heating rate was 100 °C/min and the load had been applied in two steps. It was applied 5 MPa up to 600 °C in the first one, and during the second step load was increased to 50 MPa until the process ends (es la 3-4b.). When the punch reach 1250 °C with 50 MPa of load, after 10 min of holding time, temperature and pressure were cut at the same time cooling the sample under Ar atmosphere.

Figure 3-4. Scheme of: a. graphite matrix for FAHP consolidation and b. thermal cycle of FAHP process.

b. Spark Plasma Sintering (SPS).

The SPS consolidation process was performed by a HPD-25 equipment (FCT System GmbH, Germany) at Nanomaterials and Nanotechnology Research Center ("Centro de Investigación en Nanomateriales y Nanotecnología" – CINN, Asturias, Spain).

The design of this equipment is vertical and the current is generated by pulsed DC current. The temperature was measured by a pyrometer, which is more sensitive and accurate than thermocouples. The die had a cylindrical shape with 20 mm of diameter.

The consolidation parameters were selected after optimization (see Annex II) being 1200 °C during 5 min at 80 MPa of pressure (Figure 3-5 b.).

Figure 3-5. Scheme of: a. graphite matrix for SPS consolidation and b. thermal cycle of SPS process.

3.2.3. Heat treatments

To favour the formation of $L1_2$ (γ') structure, the consolidated samples were heat treated in a high vacuum tubular furnace (Carbolite HVT 15/50/450) with heating and cooling rate of 5 °C/min. Prior to the ageing step, it was necessary to perform a solution/homogenization treatment of the as sintered components from milled/atomised powders. For doing this, samples were heated to 1250 °C during 24 h, afterwards ageing was done at 900 °C for 24 h (Figure 3-6).

Figure 3-6. Thermal scheme of heat treatments process.

3.3. Characterization techniques

The samples were characterised by different techniques to get a complete analysis of the microstructure, regarding the processing technique and composition. Each technique is complementary and necessary to have a full assessment of the results.

3.3.1. X-Ray Diffraction analysis (XRD)

The XRD technique is used during the alloying processes, from powder to consolidated samples. The phase identification and the calculation of the structural parameters such as the lattice parameter, the microstrain and the crystallite size were the aim of this technique, which monitor the effect of each manufacturing step.

In order to obtain the diffraction patterns of the samples, the X-ray diffraction equipment (Empyrean, PANalytical) uses a dispersion angle method, which its wavelength is fixed and the X-ray is monochromatic (Cu k_{α} , $\lambda = 1.5105$ Å). The diffraction angle (θ) was measured following the Bragg Law (Equation 3-1). The X-ray tube is fixed meanwhile the ion and the detector rotate symmetrically with a 2θ angular speed; it follows a Bragg-Brentano geometric configuration.

Equation 3-1. Bragg Law of X-ray diffraction.

$$n\lambda = 2d\sin\theta$$

The conditions of the measure were 45 kV tension and 40 mA intensity, 0.0131 ° step size and 438.345 s/step.

a. Phase determination

After the sample diffraction pattern acquisition, the phase determination was carried out by comparison the three more intense peaks of the theoretical pattern in the ICDD and ICSD data bases with the experimental pattern using HighScore programme. A slight peak shift could mean a compositional phase transformation or the formation of a new phase.

b. Lattice parameter (a)

The peak position are closely related to the phase composition and then to the lattice parameter changes. In the current research, “a” cell parameter shows the solid solution formation and the elements dissolution in the matrix. It was calculated with Equation 3-2 due to the present phases in the fcc structure of Co-alloys.

Equation 3-2. FCC lattice parameter equation.

$$\frac{1}{d^2} = \frac{h^2 + k^2 + l^2}{a^2}$$

where d is the distance calculated by Bragg law and (h k l) are the plane index that produces the reflexion at a particular 2θ . In this work, the “a” has been calculated in the (1 1 1) plane, which is the most intense peak of the fcc structure.

c. Misfit (δ)

The relation between the lattice parameter of γ and γ' is denominated misfit (δ), which as it was mentioned in the introduction shows the coherency between both phases (Equation 3-3).

Equation 3-3. Misfit parameter equation.

$$\delta = 2 \cdot \frac{a_{\gamma'} - a_{\gamma}}{a_{\gamma'} + a_{\gamma}}$$

where a_{γ} and $a_{\gamma'}$ are the lattice parameter of γ -fcc and γ' -L1₂ phases respectively. The δ calculations were done with the (111) peak of each fcc phase.

d. Crystallite size (L) and microstrain (ϵ)

The crystallite size is the crystal region with a coherent order, similar to a single crystal, and the microstrain is the reticular position distortion that increases the net tension. Both parameters are

related to the changes produced during mechanical milling. So, the calculation of the microstrain and the crystallite size of the powder is very important to monitor the milling process.

Generally, the microstrain increases and the crystallite size decreases during the milling process. Consequently, the shape of the peaks changed, in other words, the relative intensity and the full width at half maximum (FWHM) of the peaks modifies according to the milling time. Therefore, the crystallite size and the microstrain quantification show the milling evolution.

The crystal features were calculated according to Scherrer method (Equation 3-4) using the most intense peak of fcc phases, which is (111) peak:

Equation 3-4. Scherrer equation.

$$\beta = \frac{\kappa * \lambda_{\alpha_1}}{L * \cos \theta}$$

$$L = 4 * \varepsilon * \tan \theta$$

Where θ is the peak angle, κ is a constant (0.9 rad), λ is the wavelength, L is FWHM, β is the crystallite size and ε is the microstrain. The β values were calculated by X'Pert Data Viewer, this values took into account the instrumental aberration calculated with a Si pattern sample.

3.3.2. Thermogravimetric analysis (TGA)

The TGA measurements were carried out on a thermogravimetric analyses Q50 (TA Instruments) with high-precision balance and platinum sample pan. The equipment was used to calculate the Curie temperature of the powders and it was carefully calibrate with Ni standard, which Curie temperature is known (354 °C, aprox). A magnet was placed outside and under the TGA furnace that is below the sample pan. The attraction of the Nickel to the magnet changes when it goes through its Curie point losing weight apparently. The onset of the curve is adjusted to agree with the material's known Curie point temperature (Figure 3-7 a, where the Ni Curie Temperature is 358 °C, aprox.).

The Curie temperature is the temperature where the material change their magnetic behaviour from ferromagnetic to paramagnetic. The misalignment of the magnetic domains is related with the lattices distortion by deformation by mechanical milling and alloying elements. In this work both Al and W decrease the Curie temperature, additionally, the distortion of the lattice parameters due to the milling effect could increase the Curie temperature. Those lattice stresses impede an easy alignment of the magnetic domains making the Curie point a measurement to evaluate the alloying and milling grade.

The processed samples were heated up to 940 °C with a 10 °C/min rate and the onset of the curves were selected as closely as it was did in the Ni calibration mode (Figure 3-7, b). Even this technique has a high-precision balance, the calculated Curie temperature is an approximation. For this reason, the values were set as an integer number and only was taken into account the variation between the results according to the possible effects that modify the Curie point (as alloying degree, lattice defects density, etc).

Figure 3-7. TGA curves to calculate the Curie temperature: a. Ni calibration curve and b. Pure-Co curve.

3.3.3. Chemical analysis

e. Interstitials elements analysis (O, N, C and S)

Due to the higher risk of contamination, in case of MA powders, the control of the content of interstitial elements is important because they can change the stability of the phases and as a consequence the mechanical properties. Therefore, the interstitials content of the samples were characterized after the milling process (as powders) and after the consolidation step (as near fully dense sample).

The N and O contents were measured with a LECO TC-500 equipment. This equipment uses the fusion technique in inert atmosphere, Ar gas, in an induction furnace. The powder was weighed and was wrapped in a tin foil (this step was not necessary for the consolidated samples), then the pack was set into the graphite crucible. The oxygen released by the powder and consolidated samples reacted with C to form CO and CO₂. The produced gases have been moved by inert gas into the infrared detector.

To measure C and S content a LECO CS-200 equipment was used, which uses the fusion technique with induction furnace in oxygen atmosphere. The furnace needs a radio frequency voltage to melt the samples. The released carbon reacts with oxygen and was led through hatch and catalyst until the infrared detector.

f. Chemical analysis

The quantitative chemical composition was quantified by Optical Emission Spectroscopy with Inductively Coupled Plasma (OES-ICP) in Geochemistry and Environmental analysis laboratory of Complutense University of Madrid. The detector measures the exciting interstitial elements radiation when returned to their ground state. The radiation intensity is proportional to amount of element and it is characteristic of each ones, the elements were Co, Al, W, Fe, Cr and Ni.

3.3.4. Metallographic preparation

The powder and consolidated samples were prepared to analyses their microstructure features. To study the powder surface, a small amount of powder was set on a carbon tape and it was directly observed by microscopy.

In the case of the transversal surface of the samples, powders and consolidated materials, it was necessary to prepare it by the usual procedure to get a mirror surface. The first step is mounting the sample in a conductive resin with a Hitech Europe (EP series) mounting equipment. The surfaces were roughed down with SiC papers, from 320 to 4000, followed by smooth down with diamond past, form 9 to 1 μm. The final smooth step is silica colloidal suspension with 0.04 μm of particles size.

In order to reveal the microstructure, the samples were etched by a solution composed by FeCl_3 5 g, 2 ml of HCl and 99 ml of ethanol, which dissolve the γ phase making visible the γ' precipitates.

3.3.5. Microstructural characterization

A complete microstructural characterization requires, in addition to XRD measurements, an image study of the materials in order to verify the phases and their composition. The morphology, size and place of the precipitates in the microstructure is important to disclose the effect of those precipitates on the mechanical behaviour.

The study of the complex microstructures was carried out through different complementary techniques.

a. Scanning electron microscopy (SEM)

First approach to microstructure description was done by SEM. In this case, it was possible to accomplish this characterization with secondary electrons (SE) and backscattered one (BSE), which allows detected information about surface topography and composition of phases.

Four different equipment were used with energy dispersive spectroscopy (EDX):

- Zeiss EVO MA15 (Jena, Germany) system equipped with Energy Dispersive Spectroscopy (EDX) Oxford INCA 350.
- FEI Talos F200X
- FEI TENE0
- Philips XL-3 with Tungsten filament with EDX DX-4 analyser.

b. Transmission electron microscopy (TEM)

The size of the precipitates requires a higher resolution technique such as TEM, which could reveal the morphology and composition of those precipitates. As an example, TEM was needed to get precise images of γ/γ' distribution, that requires a special fabrication of TEM lamella by focused ion beam (FIB).

A FEG S/TEM microscope (Talos F200X, FEI) which combines outstanding high-resolution S/TEM and TEM imaging with an energy dispersive X-ray spectroscopy (EDS) was used. The S/TEM mode allows a system to distinguish the composition of the precipitates, being the brighter ones composed by the heavier elements and the darker precipitates are formed by the lighter elements.

On the other hand, the high-resolution could reveal the atom position when were found an axis zone orientation and the thickness and surface of the sample are perfect prepared. Maintaining this orientation, it is possible to obtain the diffraction pattern of the oriented area/precipitate. In the case of γ/γ' areas this diffraction pattern is composed by two overlapped lattices shifted. To reveal the belonging of each lattice were used the bright field mode. After selecting a reflexion of the diffraction pattern, the image is dark and bright, where the bright areas produce the selected reflexion.

a.1 FIB Lamella preparation

In this work, the TEM samples preparation was carried out by FIB milling due to the hardness and the complex microstructure of the samples did not allow to find the optimal electropolishing method.

The FIB operation is similar to SEM being the difference the uses of ions instead of electrons. The ion source is a fine tungsten pin covered with liquid Gallium (Ga). The advantages of Ga are the low melting point and the accuracy to a very fine probe size. The accuracy of the Ga ion via electrostatic lenses is controlling by the aperture sizes.

When a Ga^+ is accelerated in the range of 0.5 – 50 keV toward the sample generating a cascade of collision events that results in the emission of secondary electrons plus the ejection of sputtered particles and/or the creation of point and line defects. Therefore, the FIB could be used for imaging, removing material and ion beam assisted chemical vapour deposition in selected locations. But, it should be kept in mind that this method can lead to ion implantation, thermal stresses and defect formation.

The additional scanning electron column allows the in situ monitoring the ion beam damage on the surface during the test. Referring to the TEM lamella preparation, the method used for this propose was the lift-out technique, where a thin membrane was removed from the bulk and pleased in a TEM Cu-grid (Figure 3-8).

Figure 3-8. Lamella preparation steps by FIB-FEGSEM.

After the selection of the interested area, it is important the deposition of a metal strip by conventional FIB method to protect the surface of the sample. Two rectangular holes were dug at each edge of the interested area and then the lamella were thinned carefully to damage the surface as less as possible. To extract the lamella, the first step is cutting the sample around it, the second one is glue it to the PT needle and after cutting the last part, the lamella could be extract and mount on the TEM Cu-grid.

The final milling to the electron transparency, which is around 50 nm, is performed using low ion beam currents with the lamella mounted on the TEM Cu-grid. This last thinning step is the most important in order to remove the damage introduced during the high current milling and to have the surface as smoother as it is possible without any damage.

3.4. Mechanical properties

The high temperature application of the Co-based superalloys requires the study of their mechanical response. A compromise between high strength and strain is a requisite. The mechanical properties were measured in the consolidated samples to verify or redesign the manufacturing process. Hence, different tests were carried out, at different level of precision, micro and nano-hardness and compression tests.

3.4.1. Tests at microstructural level.

The tests at microstructural level allow to have an idea of the material behaviour without preparing a specific specimen. This tests are critical when the material quantity is small. Also, they measure a local material response, which sometimes, when the microstructure is complex, could help to understand the effect of each phase.

3.4.1.1. Micro-hardness testing

Considering the size of the microstructure features developed in the processed materials, with microhardness, the indentation mark (with a pyramidal shape) can affect to several microstructure constituents. The value of the indentation could provide an idea of the mechanical behaviour on a quickly and easy test. The hardness calculation follows the Equation 3-5.

Equation 3-5. Vickers hardness equation.

$$HV = \frac{1.8514 \cdot F}{d^2}$$

where F is the force in kgf and d is the average of the measurements of the diagonal' indentations.

The testes were carried out in a Vickers tests equipment (ZHV μ -Zwick Roell-) with 0.1 kgf force during 10s and with a quadrilateral diamond pyramid indenter.

3.4.1.2. Nano-mechanical testing

Nanoindentation improves the micro-indentation approach by indenting on a smaller scale (nano). For doing this, the test has a precise tip shape with high spatial resolutions to place the tip and perform the measurement. Considering the family of processed materials in this investigation, this technique allow to have the mechanical characteristics depending the formed microconstituent.

The nano-indentaton tests were performed using two different equipments, both with a Berkovich tip. This shape achieves that the elastoplastic deformation induced by the indenter is independent of indentation depth and is easier to grind to a sharp point.

- Nanoindenter XP and a G200 (Keysight Technologies), using the CSM mode (45Hz) and a final indentation depth of 150nm.
- Nano TestTM platform III (Micro Materials). It has a horizontal loading configuration with pendulum based loading system and the maximum load was 50 mN.

a. Hardness and Modulus calculation

The hardness and Yung's modulus were calculated by the indenter program following the Olivier and Pharr method [80]. The loading-unloading curve drawn in Figure 3-9 is explained with the parameters that it is possible to obtain from it. The P_{max} is the peak indentation load, h_{max} is the displacement at peak load and h_f is the final depth of the contact impression after unloading. S is the contact stiffness which is calculated from the derivate of load with respect to displacement at the maximum displacement point (the slope at the beginning of unloading curve) and A is the projected area of the elastic contact, calculated from the area function of the indenter tip $A=f(h_c)$ which relates area with contact depth h_c . The area function is calibrated from indentations into a fused silica reference sample of known elastic modulus.

Figure 3-9. Nano-indentation curve schematic representation of load – nanoindenter displacement curve.

The equations for calculating the hardness and modulus are Equation 3-6 and Equation 3-7 [81].

Equation 3-6. Hardness equation.

$$H = \frac{P_{max}}{A(h_c)}$$

where P is the load and $A(h_c)$ is the cross-sectional area of the indenter at a distance h_c from its tip. On the other hand, the modulus was calculated by:

Equation 3-7. Modulus equations.

$$E_r = \frac{\sqrt{\pi}}{2\sqrt{A(h_c)}} S$$

$$\frac{1}{E_r} = \frac{1 - \nu^2}{E} + \frac{1 - \nu_i^2}{E_i}$$

where S is the initial slope of the unloading curve and E_r the reduced modulus that accounts for the elastic deformation of both the specimen and the indenter. In the second of Equation 3-7, E_i and E are the elastic modulus and ν_i and ν are the Poisson's ratio of the indenter and the specimen, respectively.

3.4.2. Compression tests.

Compression test results display the mechanical behaviour of the bulk materials depending on the thermal history: as sintered, homogenised or aged. For high temperature applications is required a compromise between high strength and high ductility. The compression curves show the stress and strain of the materials as well as it is possible to calculate the Yield Strength, which is the stress value at 0.02% of strain.

The compression tests were carried out from RT up to 850 °C controlled by thermocouples in two different equipments.

-
- Instron 4505 equipped with extensometer. The specimens for this machine were prepared with cylindrical shape and the dimensions of 3 mm of diameter and 4 mm of high. The temperatures of the testes were RT, 400, 600, 700 and 850 °C and the compression speed was $1 \cdot 10^{-4} \text{ s}^{-1}$.
 - Instron 3384 with a 30 KN load cell. In this case the specimens were a quadrangular shape with 2x2x4 mm of dimensions. The tests temperatures were RT, 600, 700 and 750 °C.

Chapter 4:

Results

Chapter 4: Results

This chapter will follow the general scheme drawn in Figure 4-1, where each section collects the main results of a processing step. The first one is the powder manufacturing process, followed by nearly full dense consolidation of the samples and their heat treatments. This is the critical step since determines the microstructure of the processed alloys. The last section is devoted to verify the behaviour and performance of the alloys through the mechanical properties from room temperature to high temperature.

Figure 4-1. General scheme of Co-based superalloys processing route.

4.1. Manufacturing of Co based alloys

Two PM methods have been used to produce the Co base alloys: mechanical alloying from elemental Co, Al and W powders and gas atomizing. Based on previous studies (see Annex I) two compositions have been selected for being processed by PM (Table 4-1).

Table 4-1. Nominal compositions of Co-based alloys produced by PM route.

Material Composition (% at.)			Manufacturing process		Powder Tag
Co	Al	W			
84	8	8	High energy milling	FAHP	Co-8-8-MA
					Co-9-9-MA
82	9	9	Gas atomisation	SPS	Co-9-9-At

The powder features are tightly connected with the final microstructure developed and hence, with the mechanical behaviour of the alloys. For this reason, it is important to study the powder features before the consolidation process.

4.1.1. Mechanical alloyed Co based powders

The mechanical alloying process was monitored by X-Ray Diffraction patterns in order to control the phase evolution with milling time. For doing this, a sample of milled powder was extracted from the vessel at different milling times. As an example, the Co-8-8-MA evolution is represented in Figure 4-2 a..

The XRD of the initial powder mixture shows the stable phases in the initial elemental powders. Co has two phases, hcp and fcc; Al has a fcc structure and W presents a bcc one. All those phases will remain or disappeared as a function of the milling time. After 2 h, Co-hcp totally transform to

Co-fcc due to the plastic deformation, and Al-fcc peaks disappear forming a solid solution into the Co-fcc phase. As milling time progress, the increase of lattice defects become wider and shifted to higher θ values the XRD peaks. Besides, W peaks do not disappear even for longer milling times. At the end of the high energy milling process, the results indicate that MA makes possible the formation of a supersaturated solid solution of Al and W in the Co-fcc (γ phase), although free W-bcc coexist. The evolution of Co-9-9-MA is analogous to Co-8-8-MA, getting the same phases after 30 h of milling. Therefore, the final phases do not depend on the nominal composition as is shown in Figure 4-2 a and b.

Figure 4-2. a. Monitoring of Co-8-8-MA milling process by XRD. b. XRD phase study of Co-9-9-MA milled powder after 30 h milling.

Other way to study the powder evolution is through the calculation of structural features (crystallite size and microstrain level) of Co- γ -fcc on the (1 1 1) plane for each alloy. The results will be compared to pure Co-fcc powder (Table 4-2). As it is expected, the crystallite sizes decrease and the microstrains increases regardless of the composition. The high energy milling process produces particles heavily deformed, with an increase in lattice defects that distort the order and the unit cell. The level of distortion gives the increase in the microstrain value, and the decrease in crystallite size. The increase in the unit cell parameter is also linked to the formation of the solid solution.

Although the Al has been introduced as a solid solution, W, which is a bigger atom and could distort more the lattice, remains partially undissolved for both compositions. This is the reason why lattice parameters are similar to pure Co-fcc phase.

Table 4-2. Structure features of Co-fcc and MA powders after 30 h of milling.

Powder	γ -phase (1 1 1)		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Elemental Co	12.2	0.005	3.540
Co-8-8-AM	6.0	0.010	3.542
Co-9-9-AM	4.8	0.013	3.543

Additionally, the Curie T, which is affected by the composition and structural features, was measured by TGA to verify the alloying degree (Table 4-3). Two phenomena have to be considered to understand the evolution of this parameter. As the content of solute increases, Al and W, Curie T can be reduced. However, the lattice defects produced during milling by severe plastic deformation make the diamagnetic moment alignment harder and the Curie T should increase.

In Co-8-8-MA case, the Curie T is lower than pure Co due to the alloy degree and the lattice defects promoted during milling are smaller than in Co-9-9-MA milled powders, (according to the values of Table 4-2 where a higher deformation degree has achieved). This is the reason why the Co-9-9-MA Curie T is higher than in Co-8-8-MA and pure Co. In both cases, the effect of the induced plastic deformation by high energy milling is stronger than the alloy degree, making Curie T higher after 30 h of milling that it could expect if only the alloying effect occurs.

Table 4-3. Curie temperature of initial Co, Co-8-8-MA and Co-9-9-MA powders measured by TGA.

Powders	Curie T (°C)
Initial elemental Co	470
Milled Co-8-8-MA	460
Milled Co-9-9-MA	490

b. Microstructural evolution of milled powders.

Shape, size and morphology of powders after 30 h milling were studied by SEM. Figure 4-3 a. and b. show the rounded particles shape achieved after 30 h milling and their size varies from 10 to 200 μm . This distribution of particle size will favour the packing density attainable in a certain volume, leaving a low amount of porosity on green compacts. This will be a good starting point for achieving almost full density after consolidation.

Cross-section of powders allows to characterize the powder microstructure, a γ -Co matrix with W-free homogeneously distributed (the white spots marked with a yellow circles in Figure 4-3 c. and d.). These findings are in accordance with XRD diffraction pattern results (Figure 4-2).

Figure 4-3. SEM images of Co-8-8-MA and Co-9-9-MA after 30 h of milling, a. and c. are surface powder and b. and d. are transversal section powder.

TEM micrographs show a heavily deformed structure with nanostructured grain size and two types of white precipitates well dispersed throughout the bulk and with different morphologies (Figure 4-4). Some of them present a big and angular shape and some an elongated shape, which are highlighted with a yellow circle and orange square respectively.

Figure 4-4. TEM images of Co-8-8-MA (a.) and Co-9-9-MA (b.) powder after 30 h milling.

Among white precipitates composition, the small size of them demands the use of EDS coupled with TEM instead of EDS coupled with SEM. The composition mapping shows that the composition of both precipitates are different due to the elements distribution (Figure 4-5).

Figure 4-5. Co-8-8-MA white particle analysed by TEM-EDX.

The W distribution is clearly defined on the white particles. But, the C distribution is detected only on the angular white particles. This finding suggests that the angular white particles are WC and the elongated particles are plain W. Those WC particles could come from the contamination of the milling tools as it is reported in [82].

In the same way, an area in the Co-9-9-MA powder was selected to perform an equivalent general TEM-EDX analysis (Figure 4-6). Apart from white particles, a dark precipitates were detected and marked with white squares. The white precipitates in this image are elongated, mainly formed by W. On the other hand, dark precipitates are formed by Al and O, it can deduced that are Al_2O_3 since is the most stable compound.

Figure 4-6. TEM-EDX of powder area with black and white precipitates of: a. Co-8-8-MA and b. Co-9-9-MA.

4.1.2. Gas atomised Co based powders

The gas atomised powders were selected to compare the effect of initial powder homogenization on the final microstructure and hence, on mechanical properties. The comparison requires to

Figure 4-7. Co-9-9-At powder X-ray diffraction pattern.

choose between Co-8-8 or Co-9-9 compositions because were the milled alloys. Co-9-9 composition was selected due to is the most divulgated alloy and based on the reported phase diagrams [1, 18, 83] is the equilibrium composition to precipitate γ' .

To begin with, the XRD pattern of the Co-9-9-At powder is drawn in Figure 4-7 with a single phase, γ -fcc. The absence of W or Al peaks confirms the formation of complete solid solution.

Table 4-4 gathers the γ -fcc crystal parameters calculated for (1 1 1) plane by XRD pattern of atomized Co-9-9 powder. The fully prealloyed grade obtained by atomization is translated into a homogeneous composition and microstructure –base on Co-fcc- and therefore, presents the biggest crystallite size and cell parameter and the lower strain level compared to the milled Co-9-9 and pure Co powder.

Table 4-4. Co-9-9 powder, crystal parameters comparison.

Powder	γ -phase (1 1 1)		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Elemental Co-fcc	12.2	0.005	3.540
Co-9-9 AM	4.8	0.013	3.543
Co-9-9-At	26.6	0.002	3.567

As it was mentioned in a previous section, the Curie T is affected by the alloy grade and the deformation. Table 4-5 shows the Curie T of pure Co powder, Co-9-9-MA and Co-9-9-At. As the atomized powder is fully prealloyed without plastic deformation, exhibit the lowest Curie T. Only the alloy degree is affecting this property in this type of powder.

Table 4-5. Curie temperature of initial Co, Co-9-9-MA and Co-9-9-At powders measured by TGA.

Material	Curie T (°C)
Initial Co-fcc	470
Co-9-9-MA	490
Co-9-9-At	260

The SEM images of the transversal powder section are depicted in Figure 4-8 a. and verify the XRD results, where the fully prealloyed gas atomised powder has one phase, γ -fcc (Figure 4-8). Figure 4-8 b. shows the different grain size, as well as the preferential spherical shape of the powders.

Figure 4-8. SEM images of Co-9-9-At powder of: a. transversal section and b. surface section.

4.1.2.1. Harmonic structure powder

The harmonic structure is usually used to produce a bimodal distribution of grain size, a “shell-core” structure that could enhance the behaviour of the material [71, 73]. With this aim, the atomized powders were submitted to a low energy milling process (LEM) where the powder surface is deformed plastically slightly and the core of the powder remains free from deformation.

Once the powder is consolidated, the deformed grains activates the surface of the particles improving the densification during the consolidation process. Besides the differences in the deformation induces differences in recrystallization and hence the bimodal grain size is promoted.

This low energy milling (LEM) process does not affect to any possible phase transformation, it is important to keep the γ phase as the unique phase. Additionally, the low milling speed allows to avoid the milling tools contamination, even after 60 h of milling.

The possible phase evolution of LEM process is shown in Figure 4-9 a., after 60 h of milling the γ -fcc phase remains stable. As the milling time progress, all peaks are shifted to higher θ values and have a wider profile, in other words, the γ lattice is being distorted. In the Figure 4-9 b. is drawn the FWHM (*Full-Width at Half-Maximum*) with the milling time, which shows the lattice distortion of the (1 1 1) plane in γ -fcc phase. Also, the relative intensity of the (1 1 1) and (2 0 0) reflexion are changing when the milling time increase.

Figure 4-9. Co-9-9-At powder evolution during low energy milling.

Table 4-6 shows the γ -phase lattice distortion in (1 1 1) plane after low energy milling process, where the crystallite size decreases and the microstrain increases. Also, the lattice parameter increases due to the defects formation in the γ lattice.

Table 4-6. Co-9-9-At powders, crystal parameters comparison.

Material	γ -phase (1 1 1)		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Co-9-9- At	26.6	0.002	3.567
Co-9-9- At-harmonic	12.6	0.005	3.588

Measuring Curie T on Co-9-9-At-harmonic powders is possible to detected the effect of deformation on this parameter when is compared to Co-9-9-At (Table 4-5). As it is expected, the increase on lattice defects due to the LEM process increases the Curie T as the deformation of the structure makes more difficult the alignment of the diamagnetic moments (Table 4-7).

Table 4-7. Curie temperature of initial Co, Co-9-9-MA, Co-9-9-At and Co-9-9-At-harmonic powders measured by TGA.

Material	Curie T (°C)
Initial Co-fcc	470
Co-9-9-MA	490
Co-9-9- At	260
Co-9-9- At-harmonic	350

The morphology of the powders has evolved to a more angular shape or a flat shape in the case of the smaller particles (Figure 4-10 a.). As it was expected after LEM process, the surface is deformed (Figure 4-10 b.). Then, the sintering process could favours a full dense bulk.

Figure 4-10. SEM images of Co-9-9-Atharmonic powder: a. surface and b. transversal section.

4.1.2.2. Ti and Ta γ' stabilisers addition

There are elements that could help the γ' precipitation, according to the literature review [2, 22, 28, 53, 84, 85]. In this case Ti and Ta have been chosen as γ' stabilisers. Thus the addition of Ti and Ta to the atomised powder would promote the precipitation of γ' structure with, theoretically, bigger size and cuboidal shape.

To add 2 % of Ti and 2% of Ta (in % at.) to the nominal composition, the atomised powder were high energy milled with Ti and Ta elemental powders. Figure 4-11 a. shows the phase evolution of the milling process by XRD, where the most intense peak is moved to smaller 2θ due to the Ti and Ta solution into the γ -fcc phase. The final phases after 10 h of milling are γ -fcc and WC, which came from milling tools contamination.

The evolution of the microstrain and crystal size follows the expected tendency as the milling time increased (Figure 4-11 b) [86]. It was achieved a fast stabilization of the crystallite size just after 2 h of milling.

Figure 4-11. XRD pattern evolution of Co-9-9-At- alloyed with 2 % of Ti and 2% of Ti by high energy milling.

The Ti and Ta addition promotes a bigger lattice parameter because of the high deformation and the alloying degree after the milling process (Table 4-8).

Table 4-8. Co-9-9-At powders, crystal parameters comparison.

Material	γ -phase (1 1 1)		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Co-9-9- At	26.6	0.002	3.567
Co-9-9-At-harmonic	12.6	0.005	3.588
Co-9-9-At-2Ti-2Ta	5.8	0.011	3.606

Table 4-9 shows how the effects of the deformation and the alloy degree on the Curie T are competing when is considered the Co-9-9-At-Ti-Ta powder. As it was mentioned, the plastic deformation effects increase the Curie T and the alloy grade works in the opposite direction. In the case of 2Ti-2Ta powders, comparing to Co-9-9-At powders the Curie T is higher due to the increase on lattice defects after milling process. However, the attained solid solution of Ti and Ta into γ -fcc makes lower the Curie T compared to the results for Co-9-9-At-harmonic powders.

Table 4-9. Curie temperature of initial Co, Co-9-9 powders measured by TGA.

Material	Curie T (°C)
Initial Co-fcc	470
Co-9-9-MA	490
Co-9-9- At	260
Co-9-9- At-harmonic	350
Co-9-9- At-2Ti-2Ta	300

To corroborate the XRD results, the microstructure study by SEM is presented in Figure 4-12. The powder morphology get an irregular and rounded shape that suggests some level of deformation of the powder that has lost the spherical shape (Figure 4-12 a.). The transversal image shows a homogeneous distribution of white precipitates throughout the γ -fcc matrix, which are marked with yellow circles. As it has been studied in the Co-9-9-MA powder (Figure 4-5), those white particles suggest the same shape than WC, which has been detected by XRD.

Also, the green square remarks a high deformation area of the powder, which confirms the hardening of the powder. This type of waves are typical from high energy alloying powder.

Figure 4-12. SEM images of Co-9-9-Al powders after Ti and Ta adding by high energy milling.

4.1.3. Partial remarks

After the study of the manufacturing powder by mechanical milling, some ideas can be underlined:

- The final phases on powders are function of the manufacturing process.
- High energy milling process produce harder powder than the gas atomising process. The MA final microstructure is conditioned by the contamination from milling tools (particularly WC carbides enrichment) and in all the cases, some W-free particles finely distributed into the Co-fcc matrix remain.
- The gas atomised powder is entirely γ -fcc phase, which is a complete solid solution of Al and W into Co-fcc.
- The LEM process activated the powder keeping the γ -fcc phase and could favour the consolidation to a fully dense material.

4.2. Microstructural features of Co-based superalloys

Without losing the objective of this work, which is to get γ/γ' dual phase alloys, the different powders manufactured by different PM routes were consolidated and heat treated. The microstructural changes will be studied focusing in the hardening mechanism that occurs in each stage.

The sintering process heats the powder surface by Joule effect activating the atom diffusion. But the consolidation process has been selected carefully to maintain the nanograin size and to avoid the secondary precipitates, this is the reason of using fast sintering techniques (such as FAHP and SPS). On the other hand, the heat treatments were carry out to promote γ' precipitates, but the high temperature could also promote the atom diffusion making possible to precipitate new compounds, the dissolution of existing precipitates or some reactions between the alloying elements.

4.2.1. Designing γ/γ' from MA powders

The use of milled powders have the advantage of the nanoscale grain size as well as the hardening structure due to the lattice distortion. The evolution of the alloys produced from milled powder after consolidation and heat treatments are parallel, as it was disclosed in the 4.1.1 section. Then, the discussion of the results of Co-8-8-MA and Co-9-9-MA alloys will be made at the same time.

Figure 4-13 depicts the XRD diffraction patterns where have been identified the phases in each alloy. There are two phases that appear in all stages, the γ -fcc, which is the matrix formed by a Al and W solid solution in a Co lattice, and $\text{Co}_6\text{W}_6\text{C}$, which is designed as η -phase hereinafter. After ageing heat treatment, a new phase is identify as γ' -fcc phase.

Taking into account the evolution of the most intense peak of each phase. The γ phase peak, at 44° approx., becomes thinner, especially after the consolidation process and a little more after the heat treatments due to a larger crystallinity.

Following the reaction proposed in [4], the η phase could be formed as a decomposition product of the MC carbide reaction with the matrix alloy:

In the current work, MC is WC that comes from contamination of the milling tools, and M is the tag for W and Co. The consolidation temperature (1250°C) promotes the MC decomposition to M_6C due to the fact that this reaction occurs at 1140°C [87]. The presence of those precipitates activate a new hardening mechanisms promoted by complex carbides.

Figure 4-13. XRD of Co-8Al-8MA and Co-9-9-MA produced from milled powder in AS, solubilised and aged stages.

Table 4-10 collects the crystalline parameters of γ -fcc phase in the (1 1 1) plane where the phase changes could happen and could be predicted the distortion that favour the hardening mechanisms. The thermal activation by Joule effect promotes the atom movements during the sintering process and the short holding time maintains the fine grain size and the distortion in the lattice.

Table 4-10. Structural features changes calculated in the (1 1 1) plane of γ -fcc of Co-8-8-MA and Co-9-9-MA alloys from AS to aged states through solubilised heat treatment.

Material from MA	γ -phase (1 1 1)		
	Crystallite size (nm)	$\langle \varepsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Co-8-8_powder	7.0	0.0100	3.542
Co-8-8_AS	28.3	0.0030	3.574
Co-8-8_solubilised	450.4	0.0002	3.587
Co-8-8_aged	356.7	0.0003	3.581
Co-9-9_powder	8.8	0.0130	3.543
Co-9-9_AS	25.7	0.0040	3.576
Co-9-9_solubilised	208.7	0.0004	3.585
Co-9-9_aged	158.4	0.0006	3.597

As it was expected, the AS and solubilised samples increase their crystallite size and the lattice parameter. Especially the solubilisation heat treatment gets a greater increment due to the η decomposition, which makes increase the amount of W in the γ matrix.

The aged heat treatment keeps the microstrain and lattice parameter but the crystallite size decreases. The γ' precipitation makes that the matrix could be considered as a dual phase formed by γ and γ' , and the precipitation and size of γ' could decrease the γ crystallite size.

In order to clarify the phase changes, a detail of the most intense peaks from the principal phases are plotted in Figure 4-14 a. and b. To begin with, the η peak disappears after solubilisation due to the dissolution of the precipitates. Only in Co-9-9-MA sample the η phase reprecipitate after ageing heat treatment. This peak has shifted to smaller 2θ , because after the solubilisation treatment the η composition has changed. The atom activation movement during the consolidation process promotes the W dissolution into the γ -fcc.

On the other hand, the overlapped γ and γ' peaks suggest that their lattice parameters are similar. The Figure 4-14 reveals that the solution heat treatment promotes the γ' precipitation. Although there is an overlapping of γ' and γ peaks as W dissolves into the matrix. In the Co-9-9-MA sample, the (111) peaks are well defined, but in the case of Co-8-8-MA only the unsymmetrical geometry of the peak indicates that it is formed by two phases.

It is after ageing when the γ/γ' peaks have a different evolution in Co-8-8-MA and Co-9-9-MA. The reprecipitation of η phase in the Co-9-9-MA could limit the W content in the γ , shifting the peaks of the η carbide and those of γ and γ' . The precipitation of γ' requires a minimum amount of W, therefore the η phase composition after ageing should be different, probably it should have less W content.

Figure 4-14. XRD 2θ enlarged graphs of most intense peaks of final phases, γ and γ' -fcc and $\text{Co}_6\text{W}_6\text{C}$.

The effect of γ' precipitates in the γ matrix is studied by misfit parameter $-\delta-$, which is the relation between a_γ and $a_{\gamma'}$ and represents the coherence between γ and γ' phases. When the δ value is smaller, the coherence is higher and the hardening mechanisms are less effective as well as the shape of the precipitate is less cuboidal (Equation 1-3).

For Co-8-8-MA heat treated samples (solubilised and aged) the δ value is constant, as well as the a_γ parameter, which indicates the size and shape is similar for both heat treatments.

In contrast, the δ increases up to 0.28 % after ageing treatment and it could be due to the fact of the γ' grown and the change into a more cuboidal shape (see Figure 4-16). According to Pollock

et. al [88], in Ni-based superalloys when δ is closer to 0.3 % means that the γ' has a more cuboidal shape.

Comparing misfit values from PM Co-alloys to equivalent cast alloys, values are close. To have an idea, a Co-9Al-8W produced by arc melting and solubilised during 100 h at 1130 °C following by ageing at 900 °C for 100 h has a δ value of 0.30 % [10], in this study 0.28.

Table 4-11. Lattice parameter calculated in (1 1 1) plane of fcc structure and misfit evolution of Co-8-8-MA and Co-9-9-MA alloys.

Material from MA	$a_{(111)} (\text{\AA})$		δ (%)
	γ	γ'	
Co-8-8_AS	3.574	--	--
Co-8-8_solubilised	3.587	3.596	0.24
Co-8-8_aged	3.581	3.590	0.23
Co-9-9_AS	3.576	--	--
Co-9-9_solubilised	3.585	3.594	0.25
Co-9-9_aged	3.597	3.607	0.28

The δ evolution is verified by the microstructural study presented in Figure 4-15, which shows the evolution of Co-8-8-MA and Co-9-9-MA by SEM. In the AS stage, the samples has two phases, the white particles, η phase, homogeneously distributed throughout the grey matrix, which is γ -fcc.

The solubilisation heat treatment partially dissolved the η carbides. In the same way, a new precipitate appears in Co-8-8-MA, preferentially at the grain boundaries with stick shape. Besides these precipitates, peaks concur with γ and η phases in XRD (Figure 4-13), their shape suggests that could be Co_3W [18]. After ageing, the sticks precipitates have grown, and even some of them have precipitated in the middle of the grain.

In the case of Co-9-9-MA sample, there are not sticks precipitates, but the η phase is placed at the grain boundaries with more angular shape. The shape changes could be a different composition effect of the η dissolution after heat treatments.

Focusing on γ' phase precipitation, which occurs after solubilisation according to XRD patterns, the microstructural study by SEM do not reveal the precipitates. It is after ageing (Figure 4-15) when the γ' is visible in the middle of the grain.

Grain size evolution with thermal heating can be studied by TEM (Figure 4-15). The AS samples has an average of 50 nm grain size, which grown up to 150 nm after solubilisation and again grown up to 500 nm after ageing. This grain growth decreases the Hall-Petch hardening mechanism; however, the carbides or intermetallics hardening mechanisms can keep the properties of the materials.

Figure 4-15. SEM and bright field TEM images of Co-8-8-MA and Co-9-9-MA in the different stages: As, Solubilisation and ageing

The HAADF TEM images mode could illustrate the γ' precipitates in Figure 4-16, where the γ' precipitates are massively throughout the matrix. In those images, the contrast of the precipitates are function of their composition. The brightest precipitates get more heavy elements and the darkest areas are rich in the lightest elements. The brighter γ' precipitates prove that are enriched with W.

The γ' size is 20 nm in solubilised samples and in aged samples there are a bimodal γ' size, where the smallest ones are around 20 nm and the biggest 150 nm. The bimodal γ' size after ageing could occur due to a slow cooling in the furnace according with the carbide the secondary γ' formation mechanism described in [89–91]. During the slow cooling the energy is not enough for growing the γ' precipitates because the atoms movements are not activated. So the nucleation is favoured against growth, and this is the reason why there are more amount of small precipitates.

Figure 4-16. HAADF TEM images of Co-8-8-MA and Co-9-9-MA in the different stages: As, Solubilisation and ageing.

c. Chemical partitioning among the MA alloys microstructure

EDX-TEM analysis could disclose the composition of each precipitate verifying the XRD and image findings presented previously. An example of each precipitate has been chosen in order to show the elemental distribution for this area. The precipitates composition are similar regardless the nominal alloy.

A γ/γ' area in the aged sample was chosen due to the greater γ' precipitates (Figure 4-17) to show the elements distribution. The γ' precipitates are rich in W, since Co and Al is homogeneously distributed throughout all the area. The MA alloys has C that come mainly from the milling tools contamination (part of it from the atmosphere). According to [92], C plays an important role in γ' stabilization forming Co_3AlC stoichiometry. When heat treatments dissolve η the phase, as it was mentioned before, the W content in the matrix increases as well as the C content. This amount of C could favours the γ' precipitation, but C there are not the principal element that forms γ' , the precipitates should be darker than they are in Figure 4-16 or Figure 4-17.

Figure 4-17. STEM-EDX mapping analysis example of γ/γ' area in Co-8-8-MA aged sample.

The AS matrix is analysed in Figure 4-18 a. and b., where the elements are homogeneously distributed in the selected area. Al and O are preferentially distributed on black precipitates. The most likely stoichiometry of those precipitates is Al_2O_3 , which could not be detected by XRD due to their amount, crystallinity or small size, around 50 nm (Figure 4-18 b.). On the other hand, Co and W seems to draw the brighter areas.

The Table inset in Figure 4-18 a. shows the concentration of Co, Al and W in the matrix. There are O and C content due to inevitable contamination from the atmosphere and the milling tools, respectively. Both, Al and W content are below the nominal composition due to the Al_2O_3 and η phases.

Figure 4-18. STEM-EDX mapping analysis example of matrix in: a. Co-9-9-MA AS and b. Co-8-8-MA solubilised samples.

According to the XRD results, the samples have two types of secondary precipitates that are η and Co_3W . Those precipitates have different shapes, the η phase is rounded while Co_3W has a stick shape (Figure 4-19 a. and b., respectively). The elements distribution is similar, in both precipitates. W is clearly defined on the precipitates, since Al is homogeneously distributed on the all selected area. Whereas Co is more concentrated on the Co_3W precipitates (sticks) than in η , C is highly concentrated in η phase.

Figure 4-19. STEM-EDX mapping analysis example of a. η -phase in Co-8-8-MA AS and b. Co_3W precipitates in Co-8-8-MA solubilised samples.

Additionally, a line scan of those precipitates is drawn in Figure 4-20, where the concentration of Co and W in each phase is easily distinguished. The η phase has the same Co and W at. % (Figure 4-20 a.) since in Figure 4-20 b. the Co and W at. % is more or less 75 % and 25 % respectively, which is the stoichiometry of Co_3W .

Figure 4-20. STEM-EDX line-scan analysis example of a. η phase in Co-9-9-MA AS and b. Co_3W precipitates in Co-8-8-MA solubilised samples.

4.2.2. Designing γ/γ' from Atomised powders

The XRD patterns represented in Figure 4-21 a. verify that the C contamination come from only the milling tools contamination and not from the consolidation process, due to the samples have two phases in each stage, γ -fcc and γ' -L1₂. Thus, the use of atomised powder avoid the secondary phase precipitation, as $\text{Co}_6\text{W}_6\text{C}$ and Co_3W that had been found in MA alloys.

A detail of the most intense peak of γ and γ' phases is drawn in Figure 4-21 b., where it is possible to follow the evolution of both phases with thermal treatments. In the case of AS sample, the peak is not symmetric since there are two overlapped peaks.

After heat treatments, homogenisation and ageing, the peaks overlap but in those cases, the maximum of each peak is clearly defined. Furthermore, after homogenisation treatment the peaks moved to lower 2θ ; in other words, the lattice parameters grown. Due to the high temperature, the atomic activation movement during homogenisation could make increase the lattice parameters. In contrast, the aged treatment makes the peaks to split to lower 2θ and the lattice parameters decreased. During ageing heat treatment, the temperature is not enough to favour the atoms movement but the γ' could grow instead of γ phase.

The relative intensity of each peak suggests that the γ' has grown after homogenisation because its intensity is greater. The opposite way occurs for γ phase, which decreases the intensity due to the γ' growth and then the intensity increase because the ageing treatment stabilized the lattice of both phases.

Figure 4-21. a. XRD of Co-9-9-At patterns of AS, homogenised and aged stages. b. 2θ enlarged graphs of most intense peaks of final phases, γ and γ' -fcc.

To study the δ evolution, the maximum of the peaks were taken to calculate the lattice parameter in (1 1 1) plane of γ and γ' phases (Figure 4-21 b.). The δ gained 0.24 % after being homogenised from 0.07 % after consolidation, what it means that the lattices of γ and γ' lost coherency and the γ' growth boosting the lattice tensions. Focusing in the steady value of δ after ageing, it could forecast that the γ' and the hardening mechanism is similar in both stages.

The difference of the δ value with the Co-9-9-MA alloys (0.24 % and 0.28 % after solubilising and ageing, respectively) could be due to the W that comes from WC contamination. This W could form η or γ' phase modifying the lattice parameter of γ' and increasing the δ value.

Table 4-12. Lattice parameter calculated in (1 1 1) plane of fcc structure and misfit evolution of Co-9-9-At alloys.

Material from Atomised powder	$a_{(1\ 1\ 1)} (\text{\AA})$		$\delta (\%)$
	γ	γ'	
Co-9-9_AS	3.590	3.592	0.07
Co-9-9_homogenised	3.589	3.598	0.24
Co-9-9_aged	3.583	3.592	0.24

Taking into account the δ results, the heat treatments effect in the γ' precipitate morphology should be studied by microstructural study (Figure 4-22). In AS stage, the sample has a massive γ' precipitation, due to their small size, the TEM analysis displayed the γ' morphology (Figure 4-22 b.). The γ' has around 20 nm size with a rounded shape and non-preferential precipitation orientation, this is the reason why δ gets a small value in the AS sample (Table 4-12).

Figure 4-22. SEM (a., c. and e.) and TEM (b., d. and f.) images of alloys from atomised powder: AS, Homogenised and Aged stages.

After homogenisation treatment, the γ' precipitates are well defined by SEM (Figure 4-22 c.) because the γ' has grown, which was predicted by δ value. Figure 4-22 d. shows the TEM image where the γ' has around 50 to 100 nm size and cuboidal shape with random precipitation. Additionally, this sample has a secondary γ' precipitates between the primary γ' . The precipitation of those secondary γ' precipitates with less than 10 nm size could occur during cooling furnace (~ 100 °C/min) following the precipitation mechanism described in [89–91]. Despite the energy needed for growing is higher than the energy needed for nucleating, both were accomplished during the heat treatment. But during the cooling step the nucleation is promoted rather than the growth.

In the aged sample, the γ' is oriented according to the previous grain orientation. As an example, in Figure 4-22 e. there are three different γ' orientation, which concur with different grains. In the grain boundaries there are some chaotic precipitation due to the precipitate reorientation. The TEM image (Figure 4-22 f.) shows this perfect γ' orientation, where the γ' precipitates are perfectly organised with around 100 nm size and cuboidal shape. The size of the γ' is similar to the solubilised sample, and the effect of ageing is the γ' orientation. Additionally, the space

between primary γ' is bigger than in the homogenised sample, and in this space have found secondary γ' precipitates with less space in between and less than 10 nm size.

With the aim to verify the cubic structure of γ and γ' , the area presented in Figure 4-23 were oriented in the $[1\bar{1}\bar{2}]$ zone axis. The diffraction pattern of this area is presented in Figure 4-23 upper right, where there are two lattices with different intensity in the reflexions. This two shifted lattices are a typical diffraction pattern from γ/γ' dual phase because of γ' precipitates coherently with γ matrix. In order to disclose the belonging of each lattice, the reflexion marked with a red circle was chosen to take an image in the bright field mode (Figure 4-23 bottom right). The brighter areas are the ones that produce the chosen reflexion, so the reflexions with less intensity belong to γ' precipitates due to they have the white contrast in the image. The upper part of this image (Figure 4-23 bottom right) is the top of the sample, which belongs to the Pt protection layer from the lamella preparation (see 3.3.5 section).

Figure 4-23. γ/γ' area in Co-9-9-At aged samples that was oriented to obtain the diffraction pattern in $[1\bar{1}\bar{2}]$ zone axis (upper right image) and a bright field TEM image belongs to the marked reflexion (bottom right image).

The similarity of γ and γ' lattice parameters makes difficult their calculation by TEM results due to the fact that this technique has not enough accuracy to distinguish between both.

a. Chemical partitioning among the microstructure

The element distribution among γ/γ' dual phase may give an idea of the hardening due to the alloying effect. Figure 4-24 illustrates an example of γ/γ' area mapping analysis, where the W is preferentially concentrated in γ' phase whereas Co is in γ phase.

Figure 4-24. EDX-TEM of γ/γ' dual phase mapping analysis in Co-9-9-At sample after ageing heat treatment.

Although Al is more or less homogeneously distributed through the whole area, but it may seem that the γ' precipitates have more intensity. The γ' enrichment of W could improve the mechanical properties of these alloys favouring the γ' hardening mechanism.

This elements distribution is similar in the AS and homogenised samples, where the γ' size and distribution make vague the elemental analysis.

4.2.2.1. Effect of harmonic structure in atomised alloys.

As it was mentioned in the 4.1.2.1 section, the LEM activates the powder surface and creates the harmonic structure, which compromises a shell-core structure. After consolidation process of those powders, the structure are composed by γ -fcc and γ' -L1₂ phases (Figure 4-25 a.). In addition, those alloys are free of secondary precipitates. The evolution of the phases is parallel to the alloys that have been described in 4.1.2.1, but the relative intensity of the γ' peaks are greater, for example in the homogenised samples. The reason could be that the precipitates are bigger or there are more amount of them.

Figure 4-25 b. shows the most intense peak, which is the (1 1 1) plane in both phases. Each sample has the γ/γ' dual phase. Here, the peak in the AS sample is thinner than in Figure 4-25 b., so the LEM process generates a heist deformed lattice making easier the γ' precipitation. After the heat treatments, the maximum of the peaks are defined, although the peaks are always overlapped due to the coherency of the phases and the lattice is similar.

Figure 4-25. a. XRD of Co-9-9-At after LEM patterns of AS, homogenised and aged stages. b. 2θ enlarged graphs of most intense peaks of final phases, γ and γ' -fcc.

The coherency of those phases is analysed in Table 4-13 for each stage. At first sight, the δ is increases from the AS stage and after homogenisation and ageing treatments. The gain causes a loss of coherency and subsequently the lattice deformation of the alloys, which could improve the mechanical response of the alloys due to γ' hardened mechanism.

Table 4-13. Lattice parameter calculated in (1 1 1) plane of fcc structure and misfit evolution of Co-9-9-At after LEM alloys.

Material from Harmonic powder	$a_{(1\ 1\ 1)} (\text{\AA})$		$\delta (\%)$
	γ	γ'	
Co-9-9_AS	3.588	3.590	0.05
Co-9-9_homogenised	3.575	3.584	0.24
Co-9-9_aged	3.580	3.593	0.38

In agreement with the XRD results, the microstructure of harmonic alloys is formed by two phases, γ and γ' , as Figure 4-26 shows. The AS samples get γ' randomly precipitate throughout the bulk with around 20 nm size and rounded shape, which is similar to the alloys produced from atomised powder directly (Figure 4-26 a. and b.).

It is during the homogenisation treatment when the microstructural evolution is different to the previous material (Figure 4-26 c. and d.). Comparing to the alloys described in 4.1.2.1 section, the current γ' size is bigger, around 50-100 nm, and the shape is more cuboidal. In the same way, the distance in between primary γ' is bigger too, and in this space, the secondary γ' precipitated with less than 10 nm size. The alloys from the harmonic powder get more twins due to the LEM process, and the γ' precipitates preferentially along those twins.

Figure 4-26 e. and f. gather the ageing heat treatment pictures, where the primary γ' precipitates grown up to 100-150 nm in the same way that δ increases (Table 4-13). The space between primary γ' is bigger and the secondary γ' precipitates in these areas with around 20 nm size. This increases in the primary γ' distance could be due to a higher atoms movements during ageing that promote an elemental concentration gradient [89–91].

Figure 4-26. SEM (a., c. and e.) and TEM (b., d. and f.) images of alloys from LEM atomised powder: AS, Homogenised and Aged stages.

In order to reveal if there is a gradient in the concentration of Co, Al or W, an EDX-TEM mapping analysis is displayed in Figure 4-27. Nevertheless, due to the small size of the γ' and the sensitivity of the EDX-TEM, it was not possible to distinguish a gradient in the elemental concentration. However, the elemental distribution in the γ/γ' area is illustrated in Figure 4-27. Both the primary and the secondary γ' are enriched in W, instead Co is preferentially concentrated in γ phase. And Al is homogeneously distributed in the analysed area with a lightly more intense on the γ' precipitates.

Figure 4-27. EDX-TEM of γ/γ' dual phase mapping analysis in harmonic Co-9-9-Al sample after ageing heat treatment.

4.2.2.2. Effect of Ti and Ta addition as γ' stabilisers.

The case of the alloys with γ' stabilisers is different due to the powder manufacturing process (described in 4.1.2.2 section), and the effect of Ti and Ta. The manufacturing process makes this alloys similar to MA alloys explained in 4.2.1. To begin with, the WC contamination favours the complex carbide precipitation, two complex carbide were founded $\text{Co}_6\text{W}_6\text{C}$ and TiTaC_2 (Figure 4-28 a.).

Figure 4-28. a. XRD of Co-9-9-Al-2Ti-2Ta after HEM patterns of AS, homogenised and aged stages. b. 2θ enlarged graphs of most intense peaks of final phases, γ and γ' -fcc.

On the other hand, the Ti and Ta effect in γ' precipitation is because the higher relative intensity of the γ' peaks when it is compared to the previous alloys (Figure 4-28 a.). Figure 4-28 b. shows the most intense peaks of γ and γ' phases ((111) plane), which are overlapped. Peaks have shifted to greater 2θ values and then lattice parameters will be smaller. In this case, the maximum of the peaks are not well defined due to the similar lattices.

It will be easier to understand the Ti and Ta effect with the δ values that are collected in Table 4-14. The δ is more stable after each stage and they are smaller than the δ obtained in the previous alloys. Ti and Ta alloying play a stabiliser role that promotes the γ' precipitation reducing

the energy requires for nucleation and growth. Moreover, the Ti and Ta increase the solvus temperature extending the γ' stabilization area in the ternary diagram.

Table 4-14. Lattice parameter calculated in (1 1 1) plane of fcc structure and misfit evolution of Co-9-9-Ta after HEM alloys.

Material from Atomised+2Ti-2Ta powder	$a_{(111)} (\text{\AA})$		$\delta (\%)$
	γ	γ'	
Co-9-9_AS	3.596	3.598	0.07
Co-9-9_homogenised	3.596	3.599	0.06
Co-9-9_aged	3.578	3.580	0.05

As XRD diffraction patterns reveal, the microstructure of 2Ti-2Ta alloys is more complex because of the secondary precipitates. In the AS samples there are three types of precipitates: γ , γ' and the white circle precipitates (Figure 4-29 a.), which could belong to TiTaC_2 precipitates according to XRD results and the γ' precipitates are greater due to the Ti and Ta effect (Figure 4-28 a.).

The γ' size is around 50 nm with a perfect cuboidal shape (Figure 4-29 b). In the TEM image, two new precipitates are found, the small circular white precipitates marked with an orange triangle and the black precipitates. Those new precipitates could not be detected by XRD due to their small size and the small amount of them. In addition, TEM image illustrates that this sample has a high amount of twins due to the manufacturing powder process.

The γ' grown considerably after homogenised heat treatment, up to 250 nm, with a perfect cuboidal shape and without preferential orientation (Figure 4-29 c.). Besides, the circular white precipitates are kept with similar shape and size. In this case, the STEM image discloses a new precipitate with stick shape that did not appear in the AS sample precipitates (Figure 4-29 d.). The black precipitates, the grey precipitates and the small white precipitates presented in the AS sample are still in the homogenised sample. In the picture inset in Figure 4-29 d. depicts an area with primary, secondly and thirdly γ' precipitates.

After ageing, treatment all precipitates have been grown being visible by SEM (Figure 4-29 e.). The inset TEM image illustrates the primary and secondly γ' precipitates with 150 and 25 nm respectively (Figure 4-29 f.)

The precipitation of the new phases are promoted by the milling contamination as well as the dissolution of the precipitates during the heat treatments. When a precipitate is dissolved, the elements react with the other elements and form the most stable compound.

Figure 4-29. SEM (a., c. and e.) and TEM (b., d. and f.) images of alloys from HEM atomised powder with 2Ti-2Ta (at. %) content: AS, Homogenised and Aged stages.

To verify the XRD results with the precipitates composition, the Figure 4-30 illustrate the elements distribution in γ/γ' area after homogenisation (a.) and ageing (b.). In both cases the elemental distribution is similar, Co have more affinity for γ whereas W, Ti and Ta are more concentrated on γ' phase. On the other hand, Al, C and O are homogeneously distributed throughout the γ/γ' area. Additionally, Figure 4-30 a. depicts the element distribution in the secondary γ' that is similar to the primary γ' .

Figure 4-30. EDX-TEM of γ/γ' dual phase mapping analysis in harmonic Co-9-9-At-2Ti-2Ta samples: a. after homogenised and b. after ageing heat treatments.

However, Al and O get a higher intensity on the black precipitates being the most probable stoichiometry Al_2O_3 . These nano-oxides could pinning the dislocations and improve the mechanical properties at high temperature, contributing to hardening mechanisms.

To verify the XRD result and disclose the composition of each precipitate in Co-9-9-At-2Ti-2Ta a mapping analysis is shown in Figure 4-31, where there are two precipitates, the white one and the grey circles.

Both of them are carbides because of the C gets more intensity on those precipitates, as Figure 4-31 illustrate in orange colour being the different the rest of the elements. The white precipitates are carbides enriched with W and Ta and the grey precipitates are carbides with Ti and Ta, which could be TaTiC_2 defined by XRD (Figure 4-28 a.).

Figure 4-31. STEM-EDX mapping analysis of carbides in Co9-9-2Ti-2Ta in AS stage.

Furthermore, the stick precipitates has a composition enriched with W, Ta and Ti, since Co and C is homogeneously distributed on the area. Those precipitates are compounds formed by W, Ta, Ti and Co, and could be an intermetallic with some dissolution of alloying elements but the composition is not possible to be defined by the available techniques.

Figure 4-32. STEM-EDX mapping analysis of stick precipitate in Co9-9-At-2Ti-2Ta in homogenised stage.

4.2.3. Partial remarks.

The γ' phase precipitates in PM alloys regardless of the manufacturing powder processing, being similar the elements distribution in γ/γ' dual phase. The slow cooling rate promotes the secondary or even tertiary γ' precipitation with similar composition to the primary ones. Those γ' precipitates could activate the high temperature hardening mechanism improving the material's mechanical behaviour.

Regarding the MA-alloys:

- The MA manufacturing powder process promote the precipitation of secondary phases that are rich in W.
- The solubilisation heat treatment dissolves the η phase promoting the W dissolution in the matrix to favour the γ' precipitation.
- The δ misfit value in PM alloys is similar to the alloys manufactured by casting (verified by scientific literature).
- Considering the microstructure developed, two hardened mechanisms could improve the mechanical properties at high temperature, the carbides formation and the γ' effects.

Regarding the At-alloys:

- When atomised powder was used, γ' is formed during the consolidation process, without subsequently heat treatments.
- The use of atomised powder avoids the precipitation of secondary phases, attaining a fully dual γ/γ' microstructure.
- The ageing heat treatment change the γ' orientation according to the prior γ grain orientation.
- The energy needed to precipitate γ' phase is easily raised after low energy milling due to the activation of the distorted matrix; to get the harmonic structure promotes the γ' precipitation.
- The δ misfit value increment on the aged harmonic samples could means an effective hardening mechanism.
- The low energy milling also promotes a γ/γ' microstructure free of secondary phases.
- Ti and Ta favour the γ' precipitation which promote a bigger cuboidal size with a lower misfit value, since less energy is necessary to form that phase.
- The addition of Ti and Ta by high energy milling promotes a secondary phases (mainly carbides) that add the carbide hardening mechanism to the γ' precipitation hardening mechanism.

4.3. Mechanical Behaviour

In the previous chapters a deep microstructural analysis was made to determine the best processing route in order to obtain a suitable microstructure based on the γ/γ' structure. After the microstructural analysis, the mechanical behaviour study is critical to ensure the PM route feasibility as a Co-based superalloys manufacturing method.

A first attempt to the knowledge of the mechanical behaviour has been made through micro and nano-hardness, giving also information about the local mechanical response. After this first approach the global material behaviour by compression test was carried out.

Moreover, the previous results concurs in this section with the hardened mechanisms as the principal guiding thread. Additionally, the mechanical properties will be correlated with the different manufacturing process ways that have been described in 4.1 section, which are closely related to the mechanical behaviour.

The powder manufacturing process promotes different microstructures (see 4.2.1 and 4.2.2 sections), therefore the alloys have different hardening mechanisms. In general, the common hardening mechanisms in PM alloys is the ultra-fine grain size and solid solution, additionally mechanical alloying promote the solid solution formation in a high deformed lattice which could help boost the material hardness. As it was studied by Curie Temperatures, the solid solution was achieved through the different powder manufacturing methods (see 4.1 section). Also the PM alloys are hardened by the precipitation mechanism strengthening the matrix, this mechanism could be composed by precipitates such as carbides and γ' phases.

4.3.1. γ' precipitation hardening mechanism.

The first hardening mechanism studied was the one due to the γ' precipitation, which are the main objective of this research.

The plain dual γ - γ' microstructure of Co-9-9-At free from secondary precipitates is the best example for studying the γ' strengthening mechanisms alloys. The absence of secondary precipitates makes the γ' as the main hardening mechanism, also the small grain size will play an important role in PM alloys. The hardness of Co-9-9-At were tested by Vickers micro-hardness Co-9-9-At solubilised sample has the highest hardness due to the growing of γ' phase from 20 nm in AS up to 100 μm size. The γ' orientation after ageing has decreased the hardness slightly. However, the Co-9-9-At keeps their hardness constantly after heat treatments (Figure 4-33).

Figure 4-33. Vickers HV_{0.1} results of Co-9-9-At alloy at AS, homogenised and aged stages.

The Figure 4-34 shows the Co-9-9-At nano-hardness and E modulus, where the nano-hardness of the material has a similar tendency than micro-hardness (Figure 4-34). In this case, the indents affect to smaller area than in micro-hardness,

On the other hand, the Modulus values shows the real plastic behaviour of the material. The Co-9-9-At achieves similar values for AS, better values for homogenised and worst for aged samples.

Figure 4-34. Co-9-9-At alloys nano-indentation hardness (a.) and modulus (b.) results at RT.

The global response of the materials have been studied by compression test and the results are displayed in Figure 4-35 where the alloy is compared in as sintered state vs. aged. In accordance with the hardness results, the compression test shows that the Co-9-9-At-AS material has achieved less stress and strain than Co-9-9-Aged. Also, the stress is maintained with the temperature in Co-9-9-At.

When the alloys are tested at high temperature, although ultimate compression strength has decreased, the strain values are close to those obtained at RT. In case of as sintered alloy the values are between 15-20 %, and in case of aged material there is an increment to 25-35 %. This is an evidence of the positive effect of γ' growth on mechanical properties

Figure 4-35. Compression test curves of Co-9-9 alloys from RT up to 850 °C: a. and b. Co-9-9-MA and c. and d. Co9-9-At.

The Yield Stress (Y.S.) values help to understand the mechanical behaviour of the materials with the temperature, making easier the comparison among Co-based alloys manufactured by different methods. Figure 4-36 reveal the better behaviour of Co-9-9-At alloys than the Co-based alloys reported such as MAR-509 [93] and Co-9Al-9W [2], and even more when the samples were heat treated.

The MAR-509 is a commercial Co-based superalloy with alloying elements (Cr: 22.5 - 24.35, Ni: 9 - 11, W: 6.5 - 7.5, C (max): 0.55 - 0.65, other (Ti, Ta, B, Zr...) and Co ball) and produced by ingot casting. This alloy has carbides as hardening mechanism. Whereas the alloy produced by Suzuki et. al has Co-9Al-9W composition and was manufactured by induction melting. In this case, the alloy was heat treated at 1350 °C during 12 h followed by ageing at 900 °C during 150 h to precipitate γ' .

The Co-9-9-At in the AS stage keeps the Y.S. with the temperature overcoming the [93] and [2] alloys Y.S. values. When the samples were heat treated, both homogenised and aged, the Y.S. increased considerably getting the highest results. As it was

happened in hardness results, the γ' growth has improved the material behaviour even at high temperature but the γ' orientation lightly reduce the Y.S. values.

Figure 4-36. Co9-9- MA and At alloys Yield Stress at 0.2 % compared to Co-9-9 studied by Suzuki et al [22] and MAR-509 [93] commercial Co-based superalloy.

In the alloys processed from atomised powders, it has been detected the anomalous behaviour at high temperature typical in Co-based alloys reported by Suzuki et al. [2]. It occurs at 700 °C in AS and homogenized stages, where the γ' high temperature hardening mechanism is activated.

The presence of γ' precipitates without performing any heat treatment in the atomised powder provides a better strengthening mechanism overcoming the carbide hardening mechanism present in MAR-509 alloy.

4.3.1.1. Harmonic microstructure effect in the γ' hardening mechanism.

In this section two alloys from atomised powder and free of secondary precipitates will be compared. The difference is the deformation induced in the lattice of Co-9-9-At-Harmonic alloys after LEM and hence over the grain size.

Both materials have the same hardness tendency (Figure 4-37), the As Sinter samples has the lowest and the homogenised samples gets the highest hardness due to the γ' growth. In the case of aged samples, the harmonic keep more or less the hardness with less uncertainty. The Co-9-9-At-Harmonic samples get higher hardness than Co-9-9-At due to the lattice deformation induced during LEM process.

The dual γ' size (20 and 150 nm aprox., see 4.2.2.1 section) precipitated in Co-9-9-At-Harmonic samples could conserve the hardness of the material due to the smallest γ' size, that could block the dislocation movement.

The Co-9-9-At-Harmonic compression curves reveal a more ductile behaviour of this material in comparison with Co-9-9-At alloys (Figure 4-37).

The compression curves in Figure 4-38 mirror the effect of the distorted matrix and the γ' size.

Figure 4-37. Vickers HV_{0.1} results of Co-9-9-At and At-Harmonic alloy at AS, homogenised and aged stages.

The Co-9-9-At-Harmonic samples get a higher stress and strain values. The harmonic structure could be the reason why the Harmonic AS samples are more ductile. This structure is composed by small grain size in the edge and bigger grains in the core of the powder particles improving the stress and the strain respectively.

On the other hand, the ageing heat treatment increases the stress of the materials, but the Harmonic samples have lost strain capacity due to the hardening effect of the secondary γ' precipitates.

In the same way than Co-9-9-At alloys, the ultimate compression strength is stable with the temperature due to the γ' hardened mechanism and the fine grain size.

Figure 4-38. Compression test curves of Co-9-9-At alloys from RT up to 850 °C: a. and b. At and c. and d. At-Harmonic.

The Y.S. of Co-9-9 from atomised powder samples exceed the reported Co-based alloys ([93] and [22]) attaining after heat treatments more than twice of the reported Y.S. (Figure 4-39) for those “as cast” alloys.

The final microstructure free from secondary phases and ultra-fine grain size makes possible to keep the mechanical properties with the temperature and make this alloys strong candidates for high temperature applications.

The Co-9-9-At-Harmonic material achieve higher Y.S. than Co-9-9-At alloys as the hardness results shown (Figure 4-37).

The “so call” anomalous behaviour in Harmonic samples occurs at 750 °C approximately. This anomalous behaviour without alloying elements at higher temperature is an improvement due to the range of material used could be higher than other reported Co base superalloys [2, 21, 22, 48, 93–95].

Figure 4-39. Co9-9- At and At-Harmonic alloys Yield Stress at 0.2 % compared to Co-9-9 studied by Suzuki et al [22] and MAR-509 [93] commercial Co-based superalloy.

4.3.2. Carbides and high deformation hardening mechanisms.

The effect of the composition has been studied over Co-8-8-MA and Co-9-9-MA alloys. According to the 4.2.1 section, their evolution along the powder production, sintering and heat treatments were parallel then, it is expected that the behaviour of both alloys will be similar. In those materials, the main contribution to the strengthening should be the carbides formation, after heat treatment the γ' precipitation hardening mechanism was added. In addition, the solid solution and the ultra-fine grain size effects will be important in the final mechanical properties.

The hardness of Co-8-8-MA and Co-9-9-MA are shown in Figure 4-40 following a similar tendency. The indents marks of the 0.1 HV cover all the microstructural constituents reflecting the hardening mechanisms.

The hardest material is the AS and the softest is the solubilised due to the dissolution of the η phase during solubilisation heat treatment [87].

In this later treatment, the material hardness drops even having in the microstructure nano-grain size and nano- γ' precipitates. After ageing, the γ' growth as well as the Co_3W precipitates, those hardened mechanisms increased the hardness of the material but the grain growth and the η dissolution did not allow to get the AS hardness. This fact confirm the carbide precipitates and the small grain size as the main hardened mechanisms in the MA AS samples.

In the same way than micro-hardness, nano-indentation marks cover all the microstructural constituents even when the indent is smaller. This is why the tendency of the nano-hardness and modulus are similar to micro-hardness (Figure 4-41).

The hardness values are in accordance with those from Povstugar et al. [85] results for Co-9Al-9W alloy, where the author has measured the γ and γ' hardness separately being 7.6 and 9.7, respectively, with a 150 μN of load. On the other hand, the values for modulus (Figure 4-41) are similar to those alloys obtained by similar processing in [96]. Those alloys were manufactured by powder metallurgy with more amount of Al and W (Co-12Al-10W at. %), which promote the precipitation of bigger γ' .

Figure 4-40. Vickers $\text{HV}_{0.1}$ results of MA alloys at AS, homogenised and aged stages.

Figure 4-41. MA alloys nano-indentation hardness and Young's modulus (results at RT) comparison.

Compression tests will help to assess the hardening mechanisms in each alloy from RT up to 850 $^{\circ}\text{C}$ in the AS and Aged states. The evolution of the compression curves with the temperature is similar for all MA samples as it happened in the hardness tests (Figure 4-42). The curves show a continuous strain hardening with the temperature, having a maximum stress at RT and 400 $^{\circ}\text{C}$ followed by a drop in the stress. This stress decrease could occur due to the η phase dissolution during the test, which is acting as main hardening mechanism.

On the other hand, the γ' precipitates could make the material more ductile at RT and 400 °C maintaining the stress with the temperature. Even after heat treatments, when two collaborative strengthening mechanism are acting, an increase on temperature decreases the compression resistance. However, the true plastic stress increases in more than 30% compared to that in as sintered state.

Figure 4-42. Compression test curves of MA alloys from RT up to 850 °C: a. and b. Co-8-8-MA and c. and d. Co9-9-MA.

Figure 4-43 shows the Y.S. of Co-8-8-MA and Co-9-9-MA alloys in each stage as a function of the temperature. Those alloys are compared to MAR-509 [93] and the Co-9Al-9W alloy produced by Suzuki et al. [2].

The MA alloys have a good Y.S. from RT up to 600 °C because the hardening mechanisms are dominated by the carbides formation. However, when the temperature increases the carbides are dissolved losing their effect and the properties of the materials fall down. Moreover, the Y.S. of the MA-alloys is twice of the Co-based alloys produced by cast methods. The presence of nano-oxides (Al_2O_3), reported in 4.2.1 section, and nano-carbides on the grain boundary are pinning the grain boundary that could improve the creep.

The collaborative effect of the different hardening mechanisms, such as carbides and nano-carbides, nano-oxides, ultra-fine grain size and γ' , became evident in the heat treated samples, where at 600 °C the Y.S. is kept at 700 MPa (aprox.) and at 700 °C the values are similar to the Co-9Al-9W reported in [22]. Even with the γ' hardening effect, which delay the mechanical behaviour fall, the Y.S. has a continuous decreasing value due to the carbides transformation with the temperature.

The presence of γ' should produce an anomalous behaviour at high temperature as it was reported in [1, 22], but the rest of operating hardening mechanisms could mask the anomalous behaviour that occurs at 700 °C approximately.

Figure 4-43. MA alloys Yield Stress at 0.2 % compared to Co-9-9 studied by Suzuki et al [22] and MAR-509 [93] commercial Co-based superalloy.

It is possible to say that in the current work, the mechanical behaviour is not affected by the nominal composition. Even the production of both alloys have been made carefully and with the same process the difference between Co-8-8-MA and Co-9-9-MA is due to the amount and distribution of carbides, the fine microstructure of each alloy and the amount and size of γ' precipitates.

4.3.3. Ti and Ta effect on the hardening mechanism.

The complex microstructure of Co-9-9-At-2Ti-2Ta alloys, which have been described in 4.2.2.2 section, combine the effect of the hardening mechanisms described in the previous alloys. In this case the alloys have γ' , carbides, nano-oxides and a high deformed matrix as hardening mechanisms and also the common ones, ultra-fine grain size and solid solution. The cooperative or competitive hardening mechanisms will be disclosed by hardness measurements

Figure 4-44. Co-9-9- At and At-2Ti-2Ta alloys 0.1 Kg Vickers micro-hardness at RT.

and compression tests from RT up to 750 °C.

The presence of carbides in the alloy from As Sinter to Aged stages produce the highest hardness among the alloys produced from atomised powder (Figure 4-44). The hardness tendency in this material is more close to MA alloys than to At ones. Therefore, it could be expected that the main hardening mechanism could be the carbides formation. The AS samples are the hardest, decreasing this value after homogenisation treatment. Nevertheless, the aged alloy holds the hardness value, due to the carbides dissolution and the γ' growth.

The stress of Co-9-9-At-2Ti-2Ta alloys are higher than the studied alloys, (Figure 4-45). Those materials still get a great strain, from 0.1 up to 0.45 at RT and 750 °C respectively. As it could be expected from the hardness results (Figure 4-44), the stress of Co-9-9-At-2Ti-2Ta is higher than Co-9-9-At alloys.

Figure 4-45. Compression test curves of Co-9-9-At alloys from RT up to 850 °C: a. and b. At and c. and d. At-2Ti-2Ta.

Figure 4-46 displays the Y.S. values of the Co-9-9-At and Co-9-9-At-2Ti-2Ta in AS and ageing states, with the reported alloys MAR-509 [93] and Co-9Al-9W [22]. The secondary precipitates in Co-9-9-At-2Ti-2Ta alloy, which were described in section 4.2.2.2 (TiTaC_2 and intermetallics enriched in W, Ti and Ta), promote a Y.S. decreasing with the temperature, making their behaviour similar to the MA alloys due to the carbide hardening mechanism contribution. However, even with this Y.S. drop at high temperature, the values are more than three times higher than the reported ones and higher than the Co-9-9-At alloys.

The effect of carbides strengthening is superimposed to the effect of γ' precipitation, blinding the “so call” anomalous Co-based superalloys behaviour at high temperature. At 600 °C some changes

could occur to those carbides losing their hardened effect. It is true that the sample after ageing keep, in a large extent, the properties due to the stabilisation of the phases and the γ' growth.

Figure 4-46. Co-9-9- At and At-2Ti-2Ta alloys Yield Stress at 0.2 % compared to Co-9-9 studied by Suzuki et al [22] and MAR-509 [93] commercial Co-based superalloy.

4.3.4. Partial remarks

The PM method improves the reported Co-based superalloys Y.S. results, being in the order of three times higher than many reported alloys, when γ' stabilisers were obtained.

- The free secondary alloys produced from atomised powders keeps the mechanical properties at high temperature showing the “so call” anomalous behaviour at around 700 °C.
- The alloys produced from atomised powders have high strain values and secondary strengthened mechanism in compression tests typical from ductile alloys.
- The deformation lattice produced by LEM increases the mechanical properties considerably, even the anomalous behaviour appear at higher temperature, around 750 °C.
- The γ' orientation, which occurs after ageing heat treatment, decreased slightly the material hardness.
- The nominal composition of the studied alloys does not affect the mechanical behaviour, at least when is a ternary alloy with low alloying elements.
- The great mechanical properties of Co-8-8-MA alloys open the possibility of obtaining alloys with less amount of W with competitive properties at high temperature if the manufacturing process is powder metallurgy.
- The carbides solubilisation dismissed the material strength but allows the γ' precipitation improving the mechanical properties at high temperature
- The carbides strengthened superimposed to the γ' effect at high temperature blinded the “so call” anomalous behaviour of Co-based superalloys at high temperature.
- The addition of Ti and Ta provide the precipitation of γ' achieving bigger size and secondary and ternary γ' precipitates.
- The complex microstructure of the Co-9-9-At-2Ti-2Ta alloys composed by high deformed lattice with complex carbides and γ' precipitates, vested the highest mechanical properties at high temperature in alloys produced from atomised powders

Chapter 5: Conclusions

Chapter 5: Conclusions

The main goal established in this research work was to design by PM Co based superalloys through the composition design and tailoring the capability that PM and heat treatments can offer, to optimize the performance at high temperature. Considering this goal, in this study it have been demonstrated that PM route as manufacturing process, is a suitable processing route to produce Co-based superalloys with successful properties at high temperature. The obtained Yield Stress at compression in this investigation has been overcome more than three times compared to cast Co-based alloys. This improvement in compression, even at high temperature, is due to the combination of the different hardening mechanisms developed in the PM Co-based superalloys: solid solution, γ' and carbides precipitation, and refinement of the grain size.

Considering the different PM alternatives followed, the use of atomised powder assure the γ' precipitates from the powder state, avoiding secondary precipitates, being the γ' precipitation the main strengthened mechanism and hence, increasing the relevance of the γ/γ' microstructure. Also, the possibility of precipitating γ' without subsequently heat treatments is the most important achievement. In this case, the heat treatments were used in order to control the size and shape of γ' in the alloys.

The alternative powder route to manufacture the Co base alloys, the mechanical alloying, sustain the strengthening mechanisms in the distortion of the structure that basically increase the hardness. The carbides formation during high energy milling also contribute to increase the material hardening.

In view of the manufacturing alternatives followed in this work, it can be remarked as general conclusion that through PM route it can be promoted a wide range of possible compositions that allows, through different PM manufacturing routes, improved properties for high temperature applications. PM also has been demonstrated an efficient way to develop a γ/γ' structure, which

is the main strengthening mechanism for these superalloys especially to maintain the properties at high temperature.

This general conclusion can be split in some partial ones if we divided the analysis into the different manufacturing routes considered.

Taking into account the different powder manufacturing approach, the following conclusions can be highlighted:

- The intrinsic mechanism related with the milling phenomenon makes hardening the main mechanism related to this process. Also contamination is linked with high energy milling. That means that an extra strengthening mechanism can be found due to carbides finely dispersed in the Co matrix.
- On the other side, the gas atomizing route avoids contamination and extra hardening in the base powder, but, on the other side, promote and assure, from the beginning, the γ/γ' structure (which is the main hardening mechanism at high temperature in these alloys).
- The low energy milling process, also followed in this work, introduce a higher level of activation in the system and could favour the consolidation to get a full dense material.

Besides, some different microstructural approaches depending on the manufacturing processes can be made.

When using the mechanical alloying route:

- Secondary phases (mainly rich in W) can easily promote in the microstructure.
- The solubilisation heat treatment dissolves the η phase promoting the W dissolution in the matrix to favour the γ' precipitation.

When the atomized powders are used:

- γ' phase is easily formed during the consolidation process, without subsequently heat treatments.
- The use of atomised powder avoids the precipitation of secondary phases, attaining a fully dual γ/γ' microstructure.

When using the production of the harmonic powders:

- The γ' precipitation is more easily promote due to the activation of the distorted matrix.
- Aging the harmonic materials, the hardening mechanism improves and the δ misfit value increases.
- The low energy milling also promotes a γ/γ' microstructure free of secondary phases.

By the addition of Ti and Ta (γ' -stabilizers) over the atomized powders by mechanical alloying, γ' phase precipitation is promoted:

- Since less energy is necessary to form it, cuboidal size is bigger but it has lower misfit value.
- Secondary phases (mainly carbides) are favoured, adding the carbide hardening mechanism to the γ' precipitation hardening mechanism.

PM Co-based Superalloys have improved the Yield Strength results of conventional Co-based Superalloys. The increment was in the order of three times higher than many reported alloys

when γ' stabilisers were added. These results can be explained by analysing different aspect of the microstructural development:

- In the atomized powders the net γ/γ' microstructure keeps the mechanical properties at high temperature showing the “so call” anomalous behaviour at around 700 °C.
- The deformation lattice produced by LEM increases the mechanical properties considerably, even the anomalous behaviour appear at higher temperature, around 750 °C.
- After ageing the solubilized materials from atomized powders, the induced γ' orientation slightly decreased the material hardness.
- The carbides solubilisation dismissed the material strength but allows the γ' precipitation improving the mechanical properties at high temperature
- The addition of Ti and Ta provide the precipitation of γ' achieving bigger size and secondary and ternary γ' precipitates.
- The complex microstructure of the Co-9-9-Al-2Ti-2Ta alloys composed by high deformed lattice with complex carbides and γ' precipitates, conferred the highest mechanical properties at high temperature in alloys produced from atomised powders

Chapter 6:

Annex I

Chapter 6: Annex I

6.1.1. Optimization study of Co based composition and mechanical parameters

The optimization of the mechanical milling parameters is critical to achieve the optimal powder microstructure and composition, and to get full densification after consolidation process. Also, the nominal composition is important to have the expected final phases and properties of the current material. For this reason, several trials were performed with different compositions and changing some milling parameters.

Considering the results gathered by Sato et. al [1], different compositions of Co base alloys were produced (Table 6-1). Selected alloying systems respond to the intention of scanning the vicinity of L_{12} considering the phase diagram proposed by Cui et al. [14] (Figure 6-1).

Figure 6-1 Isothermal ternary diagram
Co/Al/W 900°C. Cui et al [14]

Table 6-1 Nominal composition of Co-base alloys produced by MA.

	Co	Al	W	PCA	
Co-12.5-12.5	75	12.5	12.5		(%wt.)
	62.6	4.8	32.5	0.5	(%at.)
Co-8-12.5	79.5	8	12.5		(%wt.)
	65.1	3	31.9	0.5	(%at.)
Co-12.5-8	79.5	12.5	8		(%wt.)
	72.2	5.2	22.6	0.5	(%at.)
Co-8-8	84	8	8		(%wt.)
	74.6	3.2	22.2	0.5	(%at.)

In order to understand the contamination due to the material selected for balls & bowls, the milling process was accomplished in two different ways. In that sense, two grinding media (balls & bowls) were used: stainless steel (316L) –SS- and hard metal (Co-WC) –HM- (Table 6-2).

Table 6-2 Processed MA powders depending on milling tool material.

Stainless Steel balls & Bowls	Hard Metal balls & Bowls
Co-12.5-12.5-SS	
Co-8-12.5-SS	Co-8-12.5-HM
Co-12.5-8-SS	
Co-8-8-SS	

The process parameters were selected according to the literature review, previous works and the discussion from the different milling trials, the studied systems where gathered in Table 6-3. For each trial, the amount of powder was calculated keeping constant the ball-to-powder ratio at 10:1, and considering that the filling volume never exceeded the 1/3 of bowl volume. The process temperature was controlled with the time of milling and pause cycles; the pause time was the double of the milling time. To assess the evolution of the alloying degree, milling time was varied from 30 to 100 hours (Table 6-3). The milling speed is lower in case of HM process, because the energy involved during the process is higher since the material is harder.

Table 6-3 Parameters of milling process.

Materials Tags	SS	HM
Milling media material	Stainless Steel - 316L	Hard Metal –Co-WC
Ball:Powder	10:1	10:1
Atmosphere	Static Ar	Static Ar
Speed (rpm)	400	300
PCA	Stearic Acid	Free

6.1.2. SS-Alloys: Influence of milling time and alloying system.

One of the major influence on the alloying degree is the milling time. Therefore, to monitor the evolution of the alloy, samples of few grams were taken to analyse the evolution of the powder as function of the milling parameters (specially the milling time).

The X-ray diffraction results show the evolution of the powder during the milling process. Figure 6-2 displays, as an example, the evolution of the Co-12.5-12.5-SS alloy.

In the raw material, different stable phases are detected. As can be seen in the XRD pattern for 0h, Co is in its allotropic forms, α (hcp) and β (fcc) phases. All those phases will be maintained or disappeared as function of the milling time during the mechanical alloying process. After 9h of milling time, as Al is introduced into the Co- β as solid solution, Al- α (fcc) peaks disappear. In this point, Co is found only as Co- β due to different possible reasons: the dissolution of other alloying elements present in the process (as Ni and Fe from the bowl that behaves as β -stabilizers) and the distortion of the cell by the high energy milling effect.

By 30 h of milling, the peak start to split into two peaks and after 50h is converted in the γ -FCC phase. Fifty hours of milling time is necessary to decreases the crystallinity of W. Nevertheless, this element remains even after 103h of milling time. Therefore the final phases are γ -FCC and W-BCC.

Figure 6-2 XRD result of Co-12.5-12.5-SS alloy during milling process.

Figure 6-3 collects the X-Ray patterns of the four alloying systems processed by MA. Two milling times were selected: 30 and 100 hours, (main changes in between the present phases occur before the 30 hours, but some slightly changes also occurs after this milling time). The evolution of the phases were similar during all the studied milling processes, so it was not necessary to take samples during the milling process, when we reach the final time of 30h (Figure 6-3). The final phases were the same at both milling times (30 and 100h): W-BCC and γ -FCC. But at 30h the peaks of γ -FCC are tighter so the crystal size is smaller.

Figure 6-3 XRD results of Co-base alloys with selected composition at different milling times, 30 and 100 milling hours.

Although there is no difference on the detected final phases, the structural changes are detected linked to a progressive reduction in crystallinity as milling time increases (Table 6-4).

Table 6-4 Structural parameters of γ -phase of MA powders depending on milling time.

Material	Milling time (h)	γ -phase		
		Crystallite size (nm)	$\langle \varepsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a(Å)
Co-12.5-12.5-SS	30h	14.2	0.01	3.591
	100 h	9.1	0.01	3.497
Co-8-12.5-SS	30h	14.0	0.01	3.589
	100 h	10.5	0.01	3.508
Co-12.5-8-SS	30h	16.8	0.008	3.568
Co-8-8-SS	30h	16.1	0.009	3.579

Furthermore, the Oxygen, Carbon, Sulphur and Nitrogen contents were analysed in all the studied compositions (Table 6-5). It is worthy of mention that the content of Oxygen is higher at 100h than at 30h of milling time. The Nitrogen has the same tendency. It is difficult to avoid the contamination due to the atmosphere, but can be minimized when the milling times is lower. The amount of Carbon depends strongly on the use of PCA (processing controller agent), which was used in all the cases. The employed PCA was Stearic Acid and most of the Carbon contamination comes from it. On the other hand, the Sulphur content is low enough and it does not affect the final phases.

Table 6-5 Contents of Oxygen, Carbon, Sulphur and Nitrogen at milling powder.

Material	Milling time (h)	O	C	S	N
Co-12.5-12.5-SS	30	$0.46 \pm 9 \cdot 10^{-2}$	$0.21 \pm 1 \cdot 10^{-2}$	$0.020 \pm 3 \cdot 10^{-3}$	$0.125 \pm 3 \cdot 10^{-3}$
	103	$5.9 \pm 7 \cdot 10^{-1}$	$0.153 \pm 4 \cdot 10^{-3}$	$0.05 \pm 4 \cdot 10^{-2}$	$1.08 \pm 5 \cdot 10^{-2}$
Co-8-12.5-SS	30	$0.54 \pm 3 \cdot 10^{-2}$	$0.140 \pm 4 \cdot 10^{-3}$	$0.345 \pm 8 \cdot 10^{-3}$	$0.02 \pm 2 \cdot 10^{-2}$
	100	6 ± 1	$0.165 \pm 3 \cdot 10^{-3}$	$0.01 \pm 2 \cdot 10^{-2}$	$0.98 \pm 5 \cdot 10^{-2}$
Co-12.5-8-SS	30	$0.8 \pm 5 \cdot 10^{-1}$	$0.246 \pm 2 \cdot 10^{-3}$	$0.080 \pm 1 \cdot 10^{-3}$	$0.105 \pm 2 \cdot 10^{-3}$
Co-8-8-SS	30	$0.8 \pm 3 \cdot 10^{-1}$	$0.232 \pm 1 \cdot 10^{-3}$	$0.076 \pm 3 \cdot 10^{-3}$	$0.124 \pm 2 \cdot 10^{-3}$

To verify the morphological evolution and the chemical composition of the powder at the different milling times, the samples were analysed by SEM (Figure 6-4). At 1h of milling time, coalescence and agglomeration of hard particles (i.e. W) into some softer particles (i.e. Co) take place (Figure 6-4 a).

The circular shape of initial powder became to be more elongated after 5h milling (Figure 6-4 b), when the milling keeps the particles together among them and they form larger particles (Figure 6-4 c and d), due to the plastic deformation of the original particles, at the same time of the welding phenomena. After different steps of deformation/welding/fracture/deformation/welding the microstructure shown by the final particles are homogeneous (Figure 6-4 e).

Due to the hardening effect of the plastic deformation on these homogeneous particles, the process keep on and particles still been elongated, fractured and welded again till reach the final steady state and get rounded shape (Figure 6-4 f). In all the cases, the bright particles correspond to the W with higher atomic number (highlighted in BSE mode). The milling process clearly follows the typical steps of mechanical alloying process [86].

Figure 6-4 SEM images of Co-12.5-12.5-SS alloy at different times during the milling process.

To prove if any difference arrays when comparing the morphology of MA powders after 30 or 100 hours milling time a SEM images were taken (Figure 6-5). The microstructure is completely different, at 100h the particles begin to break because the strength is high. Whereas at 30h the particles have not yet experienced this hardening.

Figure 6-5 SEM images of the sample at final milling process of Co-12.5-12.5-SS alloys.

After those analyses regarding the chemical composition (the interstitial contamination) and the observed microstructure, the selected milling time for further processing was 30h. In the same sense and to avoid the presence of extra Carbon, the use of PCA will be avoided in the next milling processes.

6.1.3. SS-Alloys vs. HM Alloys: Effect of grinding media.

To demonstrate the evolution of the powder during the milling process depending on milling media, Figure 6-6 collects the X-ray diffraction patterns depending on selected material for balls & bowls.

However, phase transformation happens in less time for HM milling than for SS one. The Al peak disappeared before 2h of milling and the Co- α changes into Co- β phase after 5h of milling. The final phases were the same (W and γ -FCC) in both cases. It is very difficult to dissolve all Tungsten content only with the milling process, being needed further treatments.

Figure 6-6 XRD results of Co-8-12.5 alloy after 30h of milling time.

The calculation of the structural parameters is important to properly analyse the changes between the use of SS and HM bowl and balls (Table 6-6). The crystallite size was smaller when using HM tools and the microstrain higher due to the high energy involved into the HM system. The lattice parameter depends on others factors, like the contaminant elements. It can be assured that using SS grinding media (much softer than the HM grinding media) the powder will have higher amount of contamination (Fe and Ni especially, which are the contamination elements with higher atomic size); this can be confirmed with the larger lattice parameter measured in the powder obtained in the SS bowl. In the powder obtained in the HM bowl, Al and W dissolved in the Co matrix.

Table 6-6 Calculated from XRD results: Crystallite size, microstrain and lattice parameter.

Material	γ -phase		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Initial Co-FCC	12.7	0.005	3.547
Co-8-12.5-SS	6.9	0.009	3.597
Co-8-12.5-HM	5.1	0.012	3.558

Figure 6-7 shows the microstructure of the powder obtained in the two different milling media (SS and HM). Figure 6-7-a belongs to powder obtained by SS milling tools, it can be appreciated, in the middle of the powder, a big grey phase that corresponds to a region with high amount of Iron. This kind of areas does not appear in the powder obtained in the HM bowl (Figure 6-7 b). In

both images, the bright small particles, which are well dispersed in the matrix Co- γ -FCC, are related to the unsolved W-BCC phase.

Figure 6-7 Images of Co-8-12.5 powder alloy after 30h milling in SS and HM milling media.

To finish the comparison of both milling media processes, the content of Oxygen, Nitrogen, Carbon and Sulphur were analysed (Table 6-7). The Carbon content at HM came from the bowl and the balls, which were made with WC-6%Co (hard metal), because in the HM process the PCA did not add. The high Oxygen content measured in the HM materials, must be came from an incorrect manipulation of the milling media.

Table 6-7 LECO analyses of Co-8-12.5 alloy after 30h milling in SS and HM milling media.

Material	O	C	S	N
Co-8-12.5-SS	$0.54 \pm 3 \cdot 10^{-2}$	$0.140 \pm 4 \cdot 10^{-3}$	$0.345 \pm 8 \cdot 10^{-3}$	$0.02 \pm 2 \cdot 10^{-2}$
Co-8-12.5-HM	$0.8 \pm 5 \cdot 10^{-1}$	$0.246 \pm 2 \cdot 10^{-3}$	$0.080 \pm 1 \cdot 10^{-3}$	$0.105 \pm 2 \cdot 10^{-3}$

The HM tools avoid the Iron and Nickel contamination from the bowl and balls in the case of the SS. The Oxygen control in the process must be improved in further HM processes, taking more care in the manipulation of the milling media and the maintenance of the Ar atmosphere.

Chapter 7:

Annex II

Chapter 7: Annex II

7.1.1. Optimization parameters study of consolidation process by FAHP and SPS

The compacts were obtained with a powder consolidation process, in which the temperature and the pressure were applied simultaneously. The MA powders were consolidated by FAHP (Field Assisted Hot Pressing) whereas the atomised powders were consolidated by SPS (Spark Plasma Sintering).

Several trials were needed to optimise the process changing some parameters, like temperature, holding time and protection foil. Certainly, the pressure is other parameter, but in this case is not as relevant as expected.

The most important is the temperature due to if the energy is not enough to produce a properly Joule effect, it will be impossible that the samples get full densification. Also, the phase transformation or the atomic movements need to reach the minimum temperature for taking place. The grain size and the phase stabilization depend on the holding time. Furthermore, the protection foil, which cover the powder, avoid the powder contamination from the matrix and punches and vice versa too.

7.1.2. Consolidation by FAHP

7.1.2.1. Optimization of consolidation parameters: Temperature and Time

In the next paragraphs will be detailed the selection of the different consolidation parameters in order to get the best final properties after the FAHP process. To choose the best combination of consolidation *Temperature-Time* by FAHP, various trials with the MA powders were made. As an example, in Figure 7-1 it can be observed the Co-12.5-12.5-SS alloy consolidated at different

temperatures and times. When the temperature and time increase, the densification is better, there are less pores. It was established that 10 minutes could be selected as common processing parameter, and it was used for all the processing temperatures. The consolidated time could be modifying in future processes.

Figure 7-1 Images of Co-12.5-12.5-SS alloy milled 100h and consolidated at different times and temperatures.

Once the time was fixed in 10 minutes, it was necessary to optimize the processing temperature. Using the Co-8-12.5-SS alloy milled for 30h as an example of the optimizing process, four different temperatures were chosen (900, 1000, 1100 and 1250 °C). The comparison of four different microstructures is in Figure 7-2: when the temperature increases, the amount of porosity in the microstructure is lower, and the expected densification higher. We can appreciate the same behaviour for the Co-12.5-12.5-SS alloy milled during 100h (Figure 7-1). In all the selected compositions can be appreciated a decrease of the porosity as the sintering temperature is increasing.

Figure 7-2 Images of Co-8-12.5-SS alloy milled 30h sintered at different temperatures during 10min by FAHP.

The density of all consolidated samples was measured with the Arquimedes' method (Figure 7-3). The tendency of current Co based alloys, independently of the composition, is to increase the density with the consolidation temperature.

Figure 7-3 Density of Co-base alloys after consolidation process with the set consolidation time specified.

The optimal consolidation temperature was from 1100 to 1250°C, being the high temperature the best, and the optimal consolidation time was 10min. These parameters could be modified for instance to improve the alloys properties.

7.1.3. Microstructural analysis: phase determination and distribution

7.1.3.1. SS-Alloys: Effect of amorphization degree and alloying composition

Once the consolidation of the five MA-alloys was accomplished by FAHP, the XRD results do not show significant differences (Figure 7-4). The final phases, in the Co based samples which were

milled during 30h in SS bowl, are a γ -FCC matrix with two types of carbides M_xC (Co_3W_3C and Fe_2W_2C) precipitates. The matrix and the precipitates type are the same in the Co based alloys samples milled during 100h, γ -FCC and M_xC respectively, but the specific precipitate is Fe_6W_6C .

Figure 7-4 XRD patterns of Co-base alloys with different composition, consolidation temperature and consolidation set time.

The crystalline parameters were calculated with XRD results and they show a decrease of microstrain with the consolidation process. The defects which were produced during mechanical alloying are combine or stack, and the microstrain is lower after consolidation (Table 7-1).

Table 7-1 Crystalline parameters of γ -phase after FAHP performed with different compositions milled during 30h.

		γ -phase		
		Crystallite size (nm)	$\langle \varepsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a(Å)
Co-12.5-12.5-SS	MA-SS-Powder	14.2	0.01	3.591
	FAHP-1000 °C	13.9	0.005	3.636
	FAHP-1100 °C	15.8	0.004	3.593
Co-8-12.5-SS	MA-SS-Powder	6.9	0.009	3.597
	FAHP-1000 °C	11.3	0.005	3.593
	FAHP-1100 °C	12.1	0.004	3.595
Co-12.5-8-SS	MA-SS-Powder	16.8	0.008	3.568
	FAHP-1000 °C	16.2	0.004	3.583
	FAHP-1100 °C	15.4	0.004	3.584
Co-8-8-SS	MA-SS-Powder	16.1	0.009	3.579
	FAHP-900 °C	15.8	0.004	3.588
	FAHP-1100 °C	16.2	0.004	3.588

In the process using SS milling media (bowl and balls), it was predicted a possible contamination (especially of iron and nickel). This contamination was confirmed in the semiquantitative analysis performed with the EDX in the SEM, and the samples were submitted to a fully quantitative analysis method. The results from the samples obtained by milling (30 h) and consolidated by FAHP (see Table 7-2) show a high level of Fe and Ni in the composition that change the status of the solid solution in comparison with materials obtained in HM bowl. This different composition has some consequences also in the obtained properties.

Table 7-2 Chemical analyses of Co-base consolidates samples at 1100 during 10min.

1100°C - 10min	Co (%)	Al (%)	W (%)	Fe (%)	Cr (%)	Ni (%)
Co12.5-12.5-SS	48 ± 2	3.1 ± 0.1	22.0 ± 0.5	20.0 ± 1.0	4.1 ± 0.2	2.1 ± 0.2
Co8-12.5-SS	39.7 ± .0	2.0 ± 0.3	23.9 ± 0.6	26.0 ± 1.0	6.1 ± 0.3	3.4 ± 0.3
Co12.5-8-SS	50.5 ± 1.0	2.1 ± 0.1	14.7 ± 0.3	25.0 ± 1.0	5.2 ± 0.3	2.9 ± 0.3
Co8-8-SS	52 ± 1	3.4 ± 0.1	16.0 ± 0.4	21.5 ± 1.0	4.8 ± 0.3	2.6 ± 0.3

The microstructure of Co- base alloys confirms the phases detected by XRD. To analyse the microstructure, the Co-8-12.5-SS milled during 30h has been selected as an example (Figure 7-5). The consolidated samples have two well defined areas. One of the areas, which has white precipitates, is formed by a γ -matrix with a fine dispersion of carbides ($\text{Co}_3\text{W}_3\text{C}$ and $\text{Fe}_2\text{W}_2\text{C}$). The second area, which are free of carbides, suggests the liquid phase formation during the consolidation process.

Figure 7-5 XRD and SEM images of Co-8-12.5-SS milled during 30h and consolidated by FAHP at 1000, 1100 and 1250°C.

Based on the binary diagram of Al-Co and in accordance with [21], there is a peritectic reaction close to the consolidation temperature that could justify the possible presence of a liquid phase during sintering (Figure 7-6).

Figure 7-6 Binary diagram of Co-Al [21].

In all the studied materials, the microstructure is similar independently of composition and consolidation temperature, composed by the two above mentioned areas with carbides or free of carbides. The unique difference between all of them is the amount of each area and the size and amount of precipitates. The morphology and distribution of the free precipitates areas surrounds the former one, suggesting a liquid phase formation during consolidated process (Figure 7-7).

Figure 7-7 SEM images of Co-base alloys consolidated at 1100°C during 10min by FAHP.

The milling time effect is a critical parameter, it produces important microstructural modifications on the developed Co based alloys. Figure 7-8 shows two examples of the studied alloys, Co-12.5-12.5-SS and Co-8-12.5-SS, which were milled during 30 h and 100 h.

The microstructure is different in both cases: at 30h of milling the microstructure has two well defined areas (the area with white precipitates and the area without precipitates). On the other hand, the microstructure of 100h milled samples has also two areas: one is the bright grey area without white precipitates and the other one is the black area with white precipitates. In this case the white precipitates are $\text{Fe}_6\text{W}_6\text{C}$. The black matrix area is rich in Fe, Ni and Cr (from the contamination of the bowl and balls) and the bright grey area is rich in Co, both of them we call γ -FCC phase because have a FCC structure.

Figure 7-8 SEM images of Co-12.5-12.5-SS and Co-8-12.5-SS consolidated at 1100 and 1000 °C and milled during 30h and 100h.

To clarify the composition of the precipitates that was found in the microstructure, TEM study was performed on the samples which were milled 30 h and were consolidated at 1100 °C during 10 min (Figure 7-9).

Figure 7-9 Transmission images of Co based alloys consolidated at 1100 °C during 10 min by FAHP. The a- and b- were made by TEM, the c- and d- were made by FIB.

In all pictures we can observe two types of precipitates, the black ones and the white ones with a rounded shape, they can be related to the $\text{Co}_3\text{W}_3\text{C}$ and $\text{Fe}_6\text{W}_6\text{C}$ carbides. Other white precipitates appear in all images (in the samples of Co-12.5-12.5-SS, Co-12.5-8-SS and Co-8-8-SS are a bigger white circular precipitates and in the Co-8-12.5-SS have a elongate shape) being Al_2O_3 . The size and distribution of all those precipitates influence the mechanical properties level and it can be adjusted with the milling media and time, and the consolidated temperature and time.

7.1.3.2. SS-Alloy vs. HM Alloy

In Figure 7-10 are collected the XRD patterns of the pressed samples at 1000, 1100 and 1250 °C. Despite the milling media or the consolidation temperature, it can be detected new phase precipitation. The final phases are in accordance with the isothermal ternary diagram proposed by Cui et al [14]. If MA in SS media has led to Fe enrichment (Co-8-12.5-SS material), a new $\text{Fe}_2\text{W}_2\text{C}$ carbide is formed, as well as complex $\text{Co}_3\text{W}_3\text{C}$ carbide. This amount of carbides is possible thanks to the carbon combined content after milling. Co-8-12.5-HM processed material exhibits different phases due to the different final composition of MA powders.

Figure 7-10 X-ray diffraction patterns of consolidated Co-8-12.5-SS (left) and Co-8-12.5-HM (right) alloys at different temperatures.

The effectiveness in precipitation strengthening can be analysed by comparing the structural parameters depending on temperature of FAHP and MA powder. For Co-8-12.5-SS alloys, the highest sintering temperature has led to sharp γ peaks ratio, which means an increasing in crystallite size (Table 7-3). Co-8-12.5-SS alloy has experienced continuous growth with temperature, that means that precipitation pinning is less effective. The effect of Fe content in Co-8-12.5SS can be noted in the evolution of cell parameters values with the consolidation temperature.

Table 7-3 Crystalline parameters of γ -phase after FAHP performed at different temperatures ($^{\circ}\text{C}$).

		Crystallite size (nm)	$\langle \varepsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a(Å)
Co-8-12.5 SS	MA-SS-Powder	6.9	0.009	3.597
	FAHP-1000 $^{\circ}\text{C}$	11.3	0.005	3.593
	FAHP-1100 $^{\circ}\text{C}$	12.1	0.004	3.595
	FAHP-1250 $^{\circ}\text{C}$	12.1	0.005	3.657
Co-8-12.5 HM	MA-HM-Powder	5.1	0.012	3.558
	FAHP-1000 $^{\circ}\text{C}$	8.7	0.006	3.577
	FAHP-1100 $^{\circ}\text{C}$	10.5	0.005	3.576
	FAHP-1250 $^{\circ}\text{C}$	12.2	0.004	3.576

To measure the amount of Fe into the Co-8-12.5-SS studied alloys, a quantitative chemical analysis was carried out by means of OSS-ICP (Table 7-4). Taking into consideration these values, not only the presence of Fe is confirmed, but also Cr and Ni content due to the mass transfer during milling. This makes that the initial composition, Co-8Al-12.5W (at. %), had been fully modified. As a result, the stabilization of Co-FCC phase will be enhanced and therefore the mechanical response will be different. For Co-8-12.5-HM alloys, the slightly increase in W measured, would mean that some mass transfer has occurred also. Even if a hard material is set for the milling tools. The advantage in this case, is the chemical compatibility with the processed powders.

Table 7-4 Chemical analysis (wt %) made by OSS-ICP in Co-8-12.5-SS and by EDS in Co-8-12.5-HM alloys. Nominal composition 79.5Co-8Al-12.5W (at. %) corresponding to 65.1Co-3.0Al-31.9W (wt. %).

	Co	Al	W	Fe	Cr	Ni
Co-8-12.5-SS	39.70	2.00	23.90	26.00	6.10	3.40
Co-8-12.5-HM	57.16	22.16	20.23	-	-	-

TEM analyses were accomplished to confirm the presence of Fe and the formation of carbides detected by XRD (Figure 7-11). Three types of precipitates are identified: type I: black and irregular in shape is in agreement with $\text{Co}_3\text{W}_3\text{C}$; type II: white and round agrees with $\text{Fe}_2\text{W}_2\text{C}$; and type III white sticks corresponding to Al_2O_3 .

Figure 7-11 TEM images of Co-8-12.5-SS consolidated by FAHP at 1100 $^{\circ}\text{C}$.

The microstructure of both alloys confirms the phases detected by XRD. The consolidated samples have two well defined areas (Figure 7-12). The area with white precipitates is formed by a γ matrix decorating with carbides (in case of Co-8-12.5-SS: $\text{Co}_3\text{W}_3\text{C}$ and $\text{Fe}_2\text{W}_2\text{C}$, for Co-8-12.5-HM: $\text{Co}_6\text{W}_6\text{C}$).

In case of Co-8-12.5-SS the temperature in which complex carbides is formed determine the morphology and distribution. Considering the X-Ray diffraction patterns collected depending on consolidation temperature (Figure 7-10, left), it can be noted how peaks of carbides become sharper and more narrow as temperature increase.

Besides, it should be a link between carbon content, alloying system and processing temperature, since precipitates for Co-8-12.5-HM seems smaller than in alloys where the amount of γ -stabilizers are higher. This microstructure should lead to a harder material.

Figure 7-12 SEM images after consolidation by FAHP.

In summary, the MA powder consolidation will take place at 1250 °C with 10 min as a holding time, 50 MPa and W foil as matrix, punches and samples protection from C diffusion. The selected composition for a depth study was Co8-8 because of it was the composition with better mechanical behaviour at room temperature. Also, the Co8-8 is closer to the Co9Al-9W alloy (at. % aprox.), which is the most reported composition, and some authors affirm that this is the L1₂ composition according to ternary diagram.

7.1.3.3. Consolidation by SPS: phase determination and distribution

The SPS consolidation technique was used for pre-alloyed powder, which was manufactured by gas atomisation with Co-9Al-9W (at. %) nominal composition, which will be denominated Co9-9_Al hereafter. This composition allow us the comparison of Co based alloys manufactured by powder metallurgy route with traditional cast methods.

The pressure will be constant for SPS trials, 80 MPa, due to change it is not critical for getting full

Figure 7-13 Co9-9_Al powder heating behaviour study in the SPS machine before consolidation process.

density. As well as, it is completely necessary to do a thermal behaviour study of this material before consolidation to the powder, which was heated until a temperature close to melting point and without pressure (Figure 7-13). The movement of the punches were monitored in order to know the displacement of them when increase the temperature. If there are some phase changes that involves volume changes, the punches moves according to the volume necessity. These phase changes could impede the full densification of the sample and limit the

consolidation temperature. Figure 7-13 represents the absolute punches movement and temperature for Co9-9_Al powder according to the process time, so the temperature that the maximum pressure should be apply is when the slope has the maximum value. In this case, the temperature will be around 1000 °C (aprox., the black line in Figure 7-13).

7.1.3.4. Effect of consolidation holding time and protecting foil on the microstructure.

SPS achieve a full densification with short holding time, which enables to maintain the nanostructured grain size obtained by PM route. Figure 7-14 shows the XRD results of consolidated samples at 1100 °C with 80MPa and graphite foil during 5 min and 1 h. The phase formation after consolidation process is not function of the holding time, at least when the powder was manufactured by gas atomization. The final phases are γ -fcc and it is seem that could be some γ' in both samples, but it is not possible to confirm the presence of γ' with XRD results.

Figure 7-14 XRD results of Co9-9_Al consolidated by SPS at 1100 °C with 80 MPa and graphite foil during different holding time.

The structural features changed after consolidation process, the crystallite size decrease and the microstrain increase as well as the lattice parameter (Table 7-5). The reorganization of W and Al during consolidation and the formation of some new nanophases, could make increase the lattice

parameter and the microstrain, respectively. The crystallite size decrease due to the deformation and recrystallization occur during consolidation process.

Table 7-5 Structural features of γ -fcc in atomised powder and samples after consolidation process with different holding time.

Material	γ -phase		
	Crystallite size (nm)	$\langle \varepsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Co-9-9_At_Powder	38.9	0.002	3.567
Co9-9_At_5'	22.5	0.004	3.590
Co-9-9_At_1h	20.8	0.004	3.590

The real differences between the samples with 1 h or 5 min of holding time are in microstructure study. Figure 7-15 reveals that in the middle of the sample there are not different phases, as XRD revealed the only phase is γ -fcc. But the porosity is smaller in 1 h than in 5 min of holding time, 0.4 % and 1.3 % respectively. On the other hand, the carbon diffusion in the sample with 1 h of holding time is bigger, in distance and in amount, than in the sample with 5 min, the percentage of carbides are 10 % for 1 h and 4% for 5 min. After EDX-SEM analysis, these carbides have the $\text{Co}_6\text{W}_6\text{C}$ stoichiometry.

Figure 7-15 SEM images of Co9-9_At consolidated by SPS at 1100 °C with 80 MPa and graphite foil during different holding time. On the left is 5 min and on the right is 10 min.

Insofar as the carbon diffusion was avoided, the microstructure control will be easy because the carbide formation could be under control. The XRD results of samples consolidated by SPS at 1100 °C during 5 min with 80 MPa and different protecting matrix foil (graphite and W), do not reveal the presence of carbides. The XRD measurements were taken in the middle of the sample while the carbides are in the edge of the sample, this is why the carbide peaks do not appear.

The structural features of γ -fcc phase, Table 7-6, show that the use of W foil does not affect in the consolidation process. Obviously, the crystallite size is more or less in the same range and the microstrain and lattice parameter is constant. Admittedly, the W electrical conduction is as good as graphite one, additionally W foil avoid the carbon contamination during consolidation process.

The microstructure study, which were made in the edge of the sample, shows the carbide presence in the samples that the protecting foil was graphite (Figure 7-17). On the other hand, the samples with W foil do not have the carbides in the edge of the sample.

Therefore, the W foil avoid the carbon contamination during consolidation process, also if the holding time is smaller, this contamination will be least. In addition, the smaller holding time keeps the nanostructured grain size obtained by PM route.

Structural features of γ -fcc in atomised powder and samples after consolidation process with different protecting foil.

Table 7-6. Structural features of γ -fcc in atomised powder and samples after consolidation process with different protecting foil.

Material	γ -phase		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Co-9-9_At_Powder	38.9	0.002	3.567
Co9-9_At_Graphite	22.5	0.004	3.590
Co-9-9_At_W	24.4	0.004	3.589

Figure 7-16 XRD results of Co9-9_At consolidated by SPS at 1100 °C during 5 min with 80 MPa and different protecting foil.

7.1.3.5. Effect of consolidation temperature on the microstructure.

The last consolidation parameter to optimise is the temperature, which could impair porosity and phase formation. Figure 7-18 depicts the XRD results of three samples consolidated at different temperatures, 1100, 1200 and 1250 °C, but with constant holding time (5 min), pressure (80 MPa), and graphite foil. It is truth that the W foil was the best option in order to avoid the carbon contamination, but the temperature variation was made with graphite foil. Following the same behaviour than the holding time and the protecting foil optimization, the phase formation at different temperatures are the same, γ -fcc, according to XRD results.

Figure 7-17 SEM images of Co9-9_At consolidated by SPS at 1100 °C during 5 min with 80 MPa and different protecting foil.

Figure 7-18 XRD results of Co9-9_At consolidated by SPS during 5 min with 80 MPa and Graphite foil at different temperatures.

The temperature does not affect to the structural features after consolidation, though the crystallite size decreased and the microstrain and lattice parameter increased compared to powder structural features (Table 7-7). The lattice parameter and the microstrain are constant when the consolidation temperature increase. However, the crystallite size shows decrease after consolidation, and when the consolidation temperature increase due to the new phase formation or the growth of the grain size, the crystallite size decrease a little.

Table 7-7 Structural features of γ -fcc in atomised powder and samples after consolidation process with different temperature.

Material	γ -phase		
	Crystallite size (nm)	$\langle \epsilon^2 \rangle^{1/2} \cdot 10^{-3}$	a (Å)
Co-9-9_At_Powder	38.9	0.002	3.567
Co9-9_At_1100 °C	22.5	0.004	3.590
Co-9-9_At_1200 °C	21.4	0.004	3.591
Co9-9_At_1250 °C	19.4	0.005	3.591

The greatest different between consolidation temperatures is the porosity in the samples. When the temperature increase, the porosity is less, the 1100 °C samples has 1.3% vol. porosity, the 1200 °C reduced its porosity until 0.7 % vol. and when the temperature was 1250 °C, the porosity was 0.4 % vol.. Furthermore, the carbon diffusion is higher when the temperature increased.

Figure 7-19 SEM images of Co9-9_At consolidated by SPS at different temperatures during 5 min with 80 MPa and graphite foil.

To summarise the optimum parameters to consolidate by SPS the Co based superalloys produced by PM route are 1200 °C with 5 min of holding time, 80 MPa of pressure and W foil as samples and graphite matrix protection.

Chapter 8:

Papers and Congress

Chapter 8: Papers and Congress

8.1. Papers

“On the role of processing parameters in sintered new Co-based (W,Al) alloys”

M. Cartón-Cordero, B. Srinivasarao, M. Campos, A. García-Junceda, J.M. Torralba

Publisher: Journal of Alloys and Compounds (Elsevier), Volume 674, 25 July 2016, Pages 406-412

DOI: <https://doi.org/10.1016/j.jallcom.2016.03.077>

Abstract: The demand for enhanced material performance and efficiency in high-temperature applications has motivated the development of novel Co-based superalloys. Co-Al-W-based superalloys with the γ/γ' structure have suitable properties for use at high temperature and are good candidates for replacing Ni-based superalloys in some applications. The current generation of Co-Al-W-based alloys has superior wear, corrosion, and oxidation resistance. The poor precipitation strengthening of these alloys compared to that of Ni-based superalloys can be overcome by designing the alloying system to promote γ' -Co₃(Al, W) precipitation. In this work, the compositions of the selected Co-Al-W-based alloys were chosen because they improve the precipitation strengthening of the alloys. Starting from powders, the materials were fabricated by mechanical alloying (MA) and subsequently consolidated by field assisted hot pressing (FAHP). The prepared Co-Al-W superalloys have a large amount of well-dispersed nanoprecipitates in their microstructures and have nearly full density. The effects of the MA and consolidation

process (FAHP) conditions on the microstructures and mechanical properties of selected samples are determined by comparing the samples.

“Microstructure and compression strength of Co-based superalloys hardened by γ' and carbide precipitation”

Marta Cartón-Cordero, Mónica Campos, Lisa P. Freund, Markus Kolb, Steffen Neumeier, Mathias Göken, José M. Torralba

Publisher: Materials Science and Engineering: A (Elsevier), Volume 734, 12 September 2018, Pages 437-444

DOI: <https://doi.org/10.1016/j.msea.2018.08.007>

Abstract: A Co-based superalloy, Co-9Al-9W (at%), was processed by mechanical alloying by high-energy milling of elemental powders and consolidated by field assisted hot pressing (FAHP). The milled powder particles mainly consist of undissolved bcc-W as well as WC and an Al and W rich fcc- γ Co solid solution. After consolidation and heat treatment a fine grained microstructure with a high fraction of carbides and a γ/γ' microstructure was obtained. The compressive yield strength at room temperature was found to be 45% higher than that of previously reported results for Co-based superalloys. A similar level of strength was found at 700 °C. These extraordinary properties can be explained due to the multitude of hardening mechanisms that sintered Co-based superalloys possess: γ' precipitation, carbide formation and the ultra-fine γ -grain size promoted by the fast consolidation technique.

8.2. Congress Contributions

- **M. Cartón-Cordero**, B. Srinivasa Rao, M. Campos, J. M. Torralba, "Microstructure and mechanical properties of Co-base $\gamma - \gamma'$ composites by mechanical alloying and field assisted hot pressing", Intermetallics 2013, Educational Center Kloster Banz, Germany. (Oral Presentation)

Abstract:

Co-base alloys strengthened by $L_{12} - \gamma'$ ($\text{Co}_3(\text{Al,W})$) particles are envisioned to be very promising materials for high temperature applications. In the current study the microstructure evolution of $\text{Co}_{75}\text{Al}_{12.5}\text{W}_{12.5}$ and $\text{Co}_{79.5}\text{Al}_8\text{W}_{12.5}$ alloys during mechanical alloying, after compaction by field assisted sintering and its relation to the mechanical properties were investigated. During initial periods of milling Co-hcp phase transformed to the supersaturated fcc phase containing aluminum and partial amount of tungsten and later transformed in to a metastable disordered B2-bcc solid solution. The formation of metastable phase is found to be due to the enhanced defect density, formation of nano grain size, heavy dissolution of tungsten and contamination from the milling media. Sintering resulted in the decomposition of disordered B2 solid solution to the stable phases containing Co-fcc, Co_3W , Co_7W_6 , CoAlW and L_{12} phases depending on the sintering conditions. By choosing proper sintering temperature and thereby controlling the amount of phases and grain size, a high compressive strength of 1.5 GPa was achieved.

- Bonta Srinivasa Rao, **Marta Cartón-Cordero**, Mónica Campos, Jose Manuel Torralba Castelló, "On the role of alloying composition and processing parameters in Co-Base γ - γ' composites", 2014 TMS Annual Meeting and Exhibition, USA. (Oral Presentation)

Abstract:

The microstructure/mechanical properties evolution of various Co base alloys during mechanical alloying and after compaction by field assisted hot pressing were investigated. During initial periods of milling Co-hcp phase transformed to the supersaturated fcc phase containing aluminium and partial amount of tungsten and later transformed into a metastable disordered B2-bcc solid solution. The formation of metastable phase is found to be due to the enhanced defect density, formation of nano grain size, heavy dissolution of tungsten and contamination from the milling media. Two milling conditions were chosen for making compacts at different temperatures. Powders containing disordered B2 solid solution decomposed to the stable phases containing Co-fcc, Co₃W, Co₇W₆, CoAlW and L1₂ phases depending on the sintering conditions. Whereas powders containing undissolved tungsten reacted with fcc cobalt and formed Co₃W phase. The compressive mechanical strength of the sintered compacts ranged between 2GPa to 1.3GPa with 0.5 to 15% plasticity respectively.

- **Marta Cartón-Cordero**, Bonta Srinivasa Rao, Andrea García-Junceda, Mónica Campos, Jose Manuel Torralba Castelló, "Development of new Co-bas superalloys by milling process and consolidation by Field-Assisted Hot Pressing", 2014 Sintering, Dresden, Germany. (Oral Presentation)

Abstract:

Co-base alloys with γ/γ' structure seem to be good candidates to replace Ni-base superalloys in high temperature applications due to their good strength, excellent and better wear resistance and high oxidation resistance. These alloys have been obtained by a milling process and compacted by means of field assisted hot pressing (FAHP). Co-base alloys are usually obtained by an arc-melting process, whereas milling processes have been rarely reported in the literature. In this study, the composition of Co-base alloys was adjusted to obtain the L1₂ structure. Thus, Co-base alloys were developed changing the relation Co/Al/W and using different milling parameters and field assisted hot pressing conditions. Depending on the former parameters, phases such as Co₇W₆- μ -, CoAl-BCC-, Co₃W-DO19-, CoAlW, W-BCC- were found in the Co matrix. The novel Co-base alloys obtained in this investigation have achieved high compression strength (between 2 to 1.3 GPa), although the ductility at room temperature can change from 15 to 0.5%.

- **Marta Cartón-Cordero**, Mónica Campos, Bonta Srinivasa Rao, Jose Manuel Torralba, *"Primera aproximación en la obtención de las nuevas aleaciones base Co por vía pulvimetalúrgica"*, 2015 National PM, Gerona, Spain. (Oral Presentation)

Abstract:

Las aleaciones base Co con estructura γ - γ' presentan unas propiedades excelentes para aplicaciones a alta temperatura, incluso podrían llegar a sustituir a las aleaciones base Ni de similar estructura utilizadas en la actualidad. Con estas nuevas aleaciones base Co se consigue una mejora en el comportamiento a desgaste, corrosión y oxidación, en comparación con las aleaciones base Ni. En este trabajo, para su obtención se ha seguido una ruta pulvimetalúrgica comenzando por el desarrollo del polvo utilizando la molienda de alta energía (MAE). Con el fin de minimizar los fenómenos de difusión durante la consolidación y conseguir un material denso, se ha explorado la viabilidad de la consolidación con presión y temperatura simultáneos (FAHP, *Field Assisted Hot Presing*). El objetivo es valorar esta ruta como alternativa al método más utilizado, la fusión por arco (Arc-melting). Para el desarrollo de este trabajo, se seleccionó una composición que posibilitara la formación de la fase γ' : Co-8Al-12.5W (at. %). El parámetro que ha demostrado ser más influyente en la aleación mecánica, es el material de los cuerpos moleadores. Por ello, se evalúa las consecuencias en la microestructura, analizando no sólo las fases y su distribución, sino como su relación con las propiedades mecánicas. El comportamiento mecánico de estas aleaciones es muy prometedor, ya que tienen un valor elevado de resistencia a compresión a temperatura ambiente (cercano a 2 GPa) proporcionado en parte por la buena distribución de carburos complejos nano-precipitados con estequiometría M_xC (siendo $M=Fe$ y W , or Co and W).

- **Marta Cartón-Cordero**, Mónica Campos, Jose Manuel Torralba, *"Mechanical Behaviour at high temperature of novel sintered Co-Al-W alloys"*, 2016 World PM, Hamburg, Germany. (Oral Presentation)

Abstract:

The industry demands a significant improvement of materials for high temperature applications. This is the reason why Co-based alloys have been studied looking for good strength at high temperature, excellent wear and high temperature oxidation resistance. In this work, Co-Al-W alloys have been designed by high-energy milling for high temperature applications. These alloys were consolidated by field assisted hot pressing (FAHP) avoiding long sintering times to promote low diffusivity to maintain the ultrafine grain size microstructure (UGS) and improving the mechanical properties. The mechanical properties were assessed from room temperature up to 800 °C by compression tests. These results from room temperature compression tests exceed 45% of the results reported in literature. The sintered Co-Al-W alloys show a similar behavior to other Co-based alloys.

- **Marta Cartón-Cordero**, Mónica Campos, Luis Antonio Díaz, Jose Manuel Torralba, *"Desarrollo de aleaciones de Co-Al-W sinterizadas por SPS"*, 2016 Materials, Oviedo, Spain. (Oral Presentation)

Abstract:

La elevada exigencia en los requisitos que deben reunir los materiales utilizados en aplicaciones a altas temperaturas, ha impulsado el desarrollo de nuevas aleaciones. Así, surgen aleaciones de Co-Al-W con estructura tipo γ/γ' que consiguen mejorar el comportamiento a desgaste, corrosión y oxidación en comparación con las aleaciones base Ni y presentan propiedades mecánicas prometedoras, pudiendo incluso superar a las aleaciones actualmente utilizadas. En este trabajo se propone una ruta alternativa al método más utilizado (Arc-melting), la tecnología de polvos. Las primeras aproximaciones a la tecnología de polvos se han realizado utilizando la molienda de alta energía para generar por aleación mecánica la composición final definida. Uno de los objetivos de este trabajo es demostrar las ventajas de partir de un polvo obtenido por atomización en gas. La consolidación del polvo prealeado se hará usando métodos en los que se apliquen presión y temperatura simultáneamente con el fin de minimizar los fenómenos de difusión además de obtener un material denso. En este caso, se partió de un polvo prealeado de composición Co-9Al-9W (at. %) que se consolidó por dos métodos: FAHP (Field Assisted Hot Presing) y SPS (Spark Plasma Sintering). En la optimización del proceso de consolidación se evalúan los efectos que producen los parámetros de consolidación (temperatura, tiempo de estancia o el recubrimiento de la matriz) tanto en la microestructura como en las propiedades mecánicas. Se demuestra que con esta nueva ruta es posible la obtención de materiales con buena densificación además de unas propiedades mecánicas altamente competitivas.

- **Marta Cartón-Cordero**, Mónica Campos, Eric Macia-Rodríguez, Luis Antonio Díaz, Jesús Cano, Andrea García-Junceda, José M. Torralba, *"Estudio microestructural de aleaciones de Co-9Al-9W producidas por SPS con Ti Ta como aleantes"*, 2017 Materials, Ciudad Real, Spain. (Oral Presentation)

Abstract:

Co base superalloys with γ/γ' dual phase microstructure are considered a good alternative for high temperature in extreme environmental conditions applications due to their good strength, wear behavior and high oxidation resistance. In this work a fully prealloyed gas atomized powder with the nominal composition of Co-9Al-9W (at%) has been used. With the aim of promoting the γ' phase precipitate, 2 at% of Ti and 2 at% of Ta have been added through mechanical alloying to the original powder. In order to reach a high level of densification maintaining an ultrafine grain size in the microstructure, the powder has been consolidated through Spark Plasma Sintering (SPS). The γ' phase precipitate is obtained after subsequent heat treatments, first a solution treatment and then aging. By X ray diffraction (XRD) technique and scanning and transmission electron microscopy (SEM/TEM), the structural and microstructural changes produced after the heat treatments from the as obtained material have been monitored. The addition of Ti and Ta to the base alloy improves the γ' phase precipitation process, and also affect to its thermal stability, improving the high temperature performance of the alloy. To characterize this influence on the γ' solution temperature, a thermo-gravimetric analysis has been performed for different compositions and heat treatments.

- **Marta Cartón-Cordero**, Mónica Campos, José M. Torralba, "*Microstructural changes on Co-9Al-9W alloy produced by SPS and Ti and Ta additions*", 2017 Sintering, San Diego, USA. (Oral Presentation)

Abstract:

The Co-based superalloys are strong candidates for high temperature and extreme conditions applications, due to their good strength, excellent and better wear resistance and high oxidation resistance. In this work, a pre-alloyed atomised powder -Co-9Al-9W (at%)- was used as precursor to produce alloys for high temperature applications. In order to enhance the formation of the γ' phase, 2% Ti and 2% Ta (at%) were added by mechanical alloying to the Co-9Al-9W atomised powder. Afterwards, with the aim of obtaining a fully dense material with an improved mechanical properties, processed alloys were consolidated by spark plasma sintering (SPS) to hold the ultrafine grain size microstructure (UGS). To precipitate γ' , it was study the microstructural changes promoted after heat treatments (solubilisation + ageing) in relation to the added alloying elements. The effect of quinary elements on γ' solvus temperature of the CoAlW base alloy was investigated through thermal analysis.

- **Marta Cartón-Cordero**, Mónica Campos, SJ Hong, José M. Torralba, "*Performance of Co-base Superalloys depending on alloying method*", 2018 EuroPM, Bilbao, Spain, (Oral presentation)

Abstract:

The Co-based γ - γ' superalloys produced by PM route have been verified as strong candidates for high temperature and extreme conditions applications. In this work, fabrication of Co alloy powders from mechanical milling and gas atomizing have been evaluated. The powder production method will determine the alloying distribution which is critical to promote the desired γ' precipitation (nominal composition was set as Co-9Al-9W, (at%). To obtain fully dense samples with ultrafine grain size (UGS) powders have been consolidated by field assisted sintering techniques, FAHP and SPS. Heat treatments have been designed to optimize the strengthening by γ' precipitation. The lattice misfits of two phases γ - γ' - were measured by XRD and found to be positive and dependant on composition and homogenization of W and Al. Therefore, powder processing route showed a clearly impact in the strengthened mechanism and in the mechanical response, that was evaluated by nanoindentation and compression test from RT up to 750 °C.

References

- [1] J. Sato, T. Omori, K. Oikawa, I. Ohnuma, R. Kainuma, and K. Ishida, "Cobalt-Base High-Temperature Alloys," vol. 90, no. 2006, 2007.
- [2] A. Suzuki, G. C. DeNolf, and T. M. Pollock, "Flow stress anomalies in γ/γ' two-phase Co-Al-W-base alloys," *Scr. Mater.*, vol. 56, no. 5, pp. 385–388, 2007.
- [3] R. F. Decker, C. T. Sims, and C.T. Sims, "The superalloys," *The superalloys*, pp. 145–174, 1972.
- [4] C. T. Sims, N. S. Stoloff, and W. C. Hagel, "superalloys II," 1987.
- [5] H. Li, Y. Liang, L. Zhao, J. Hu, S. Han, and J. Lian, "Mapping the strain-rate and grain-size dependence of deformation behaviors in nanocrystalline face-centered-cubic Ni and Ni-based alloys," *J. Alloys Compd.*, vol. 709, pp. 566–574, Jun. 2017.
- [6] N. J. Petch, "The Cleavage Strength of Polycrystals," *J. Iron Steel Inst.*, vol. 173(5), pp. 25–28, 1953.
- [7] C. A. Schuh and T. G. Nieh, "Hardness and Abrasion Resistance of Nanocrystalline Nickel Alloys Near the Hall-Petch Breakdown Regime," *MRS Proc.*, vol. 740, p. 11.8, Jan. 2002.
- [8] P. J. Bocchini, C. K. Sudbrack, R. D. Noebe, D. C. Dunand, and D. N. Seidman, "Microstructural and creep properties of boron- and zirconium-containing cobalt-based superalloys," *Mater. Sci. Eng. A*, vol. 682, pp. 260–269, Jan. 2017.
- [9] J. Blendell, "The Wright Flyer Crankcase: Precipitation Hardening in the First Aerospace Aluminum Alloys," 2013.
- [10] C. H. Zenk, S. Neumeier, H. J. Stone, and M. Göken, "Mechanical properties and lattice misfit of γ/γ' strengthened Co-base superalloys in the Co-W-Al-Ti quaternary system," *Intermetallics*, vol. 55, pp. 28–39, 2014.
- [11] T. Grosdidier, A. Hazotte, and A. Simon, "Precipitation and dissolution processes in γ/γ' single crystal nickel-based superalloys," *Mater. Sci. Eng. A*, vol. 256, no. 1–2, pp. 183–196, Nov. 1998.
- [12] C. S. Lee, "Precipitation-Hardening Characteristics of Ternary Cobalt - Aluminum - X Alloys," 1971.
- [13] R. c. Reed, *The superalloys, fundamentals and applications*, vol. 53, no. 9. 2006.
- [14] Y. F. Cui, X. Zhang, G. L. Xu, W. J. Zhu, H. S. Liu, and Z. P. Jin, "Thermodynamic assessment of Co-Al-W system and solidification of Co-enriched ternary alloys," *J. Mater. Sci.*, vol. 46, no. 8, pp. 2611–2621, 2011.
- [15] Q. Yao, H. Xing, and J. Sun, "Structural stability and elastic property of the L12 ordered Co₃(Al,W) precipitate," *Appl. Phys. Lett.*, 2006.
- [16] C. Jiang, "First-principles study of Co₃(Al,W) alloys using special quasi-random structures," *Scr. Mater.*, vol. 59, no. 10, pp. 1075–1078, 2008.
- [17] K. Ishida, "2009-Ishida- Intermetallic compounds in co-based alloys-phase stability and.pdf." *Mater. Res. Soc. Symp. Proc.*, pp. 358–368, 2008.
- [18] S. Kobayashi *et al.*, "Determination of phase equilibria in the Co-rich Co-Al-W ternary system with a diffusion-couple technique," *Intermetallics*, vol. 17, no. 12, pp. 1085–1089,

- 2009.
- [19] A. Bauer, S. Neumeier, F. Pyczak, and M. Göken, "Microstructure and creep strength of different γ/γ' -strengthened Co-base superalloy variants," *Scr. Mater.*, vol. 63, no. 12, pp. 1197–1200, 2010.
 - [20] S. Miura, K. Ohkubo, and T. Mohri, "Mechanical Properties of Co-Based L12 Intermetallic Compound $\text{Co}_3(\text{Al,W})$," *Mater. Trans.*, vol. 48, no. 9, pp. 2403–2408, 2007.
 - [21] K. Shinagawa, T. Omori, K. Oikawa, R. Kainuma, and K. Ishida, "Ductility enhancement by boron addition in Co-Al-W high-temperature alloys," *Scr. Mater.*, vol. 61, no. 6, pp. 612–615, Sep. 2009.
 - [22] A. Suzuki and T. M. Pollock, "High-temperature strength and deformation of γ/γ' two-phase Co-Al-W-base alloys," *Acta Mater.*, vol. 56, no. 6, pp. 1288–1297, 2008.
 - [23] F. Pyczak *et al.*, "The effect of tungsten content on the properties of L12-hardened Co–Al–W alloys," *J. Alloys Compd.*, vol. 632, pp. 110–115, 2015.
 - [24] E. A. Lass, R. D. Grist, and M. E. Williams, "Phase Equilibria and Microstructural Evolution in Ternary Co-Al-W Between 750 and 1100°C," *J. Phase Equilibria Diffus.*, vol. 37, no. 4, pp. 387–401, 2016.
 - [25] L. Zhu, C. Wei, H. Qi, L. Jiang, Z. Jin, and J. C. Zhao, "Experimental investigation of phase equilibria in the Co-rich part of the Co-Al-X (X = W, Mo, Nb, Ni, Ta) ternary systems using diffusion multiples," *J. Alloys Compd.*, vol. 691, pp. 110–118, 2017.
 - [26] N. V. Kazantseva *et al.*, "Phase diagram of the Co–Al–W system. structure and phase transformations near the $\text{Co}_3(\text{Al, W})$ intermetallic composition range," *Phys. Met. Metallogr.*, vol. 117, no. 7, pp. 701–709, 2016.
 - [27] K. Shinagawa *et al.*, "Phase Equilibria and Microstructure on γ' Phase in Co-Ni-Al-W System," *Mater. Trans.*, vol. 49, no. 6, pp. 1474–1479, 2008.
 - [28] T. Omori *et al.*, "Partition behavior of alloying elements and phase transformation temperatures in Co-Al-W-base quaternary systems," *Intermetallics*, vol. 32, pp. 274–283, 2013.
 - [29] S. Neumeier *et al.*, "Diffusion of solutes in fcc Cobalt investigated by diffusion couples and first principles kinetic Monte Carlo," *Acta Mater.*, vol. 106, pp. 304–312, 2016.
 - [30] T. L. Achmad, W. Fu, H. Chen, C. Zhang, and Z. G. Yang, "First-principles calculations of generalized-stacking-fault-energy of Co-based alloys," *Comput. Mater. Sci.*, vol. 121, pp. 86–96, 2016.
 - [31] C. Cui, D. Ping, Y. Gu, and H. Harada, "A New Co-Base Superalloy Strengthened by γ' Phase," *Mater. Trans.*, vol. 47, no. 8, pp. 2099–2102, 2006.
 - [32] D. H. Ping, C. Y. Cui, Y. F. Gu, and H. Harada, "Microstructure of a newly developed γ' strengthened Co-base superalloy," *Ultramicroscopy*, vol. 107, no. 9, pp. 791–795, Sep. 2007.
 - [33] A. Suzuki, H. Inui, and T. M. Pollock, "L1₂-Strengthened Cobalt-Base Superalloys," *Annu. Rev. Mater. Res.*, vol. 45, no. 1, pp. 345–368, 2015.
 - [34] F. Xue *et al.*, "Creep behavior in a γ' strengthened Co–Al–W–Ta–Ti single-crystal alloy at 1000 °C," *Scr. Mater.*, vol. 97, pp. 37–40, Mar. 2015.
 - [35] L. Zhang *et al.*, "Microstructural formation in novel Co-base ODS alloys produced by

- mechanical alloying," *Adv. Mater. Res.*, vol. 417, pp. 1136–1139, 2012.
- [36] X. F. Ding, T. Mi, F. Xue, H. J. Zhou, and M. L. Wang, "Microstructure formation in γ - γ' Co-Al-W-Ti alloys during directional solidification," *J. Alloys Compd.*, vol. 599, pp. 159–163, 2014.
- [37] H. J. Zhou, H. Chang, and Q. Feng, "Transient minimum creep of a γ' strengthened Co-base single-crystal superalloy at 900 °C," *Scr. Mater.*, vol. 135, pp. 84–87, Jul. 2017.
- [38] M. Ooshima, K. Tanaka, N. L. Okamoto, K. Kishida, and H. Inui, "Effects of quaternary alloying elements on the γ' solvus temperature of Co-Al-W based alloys with fcc/L12 two-phase microstructures," *J. Alloys Compd.*, vol. 508, no. 1, pp. 71–78, 2010.
- [39] A. Mottura, A. Janotti, and T. M. Pollock, "A first-principles study of the effect of Ta on the superlattice intrinsic stacking fault energy of L12-Co₃(Al,W)," *Intermetallics*, vol. 28, pp. 138–143, Sep. 2012.
- [40] A. Mottura, A. Janotti, and T. M. Pollock, "Alloying effects in the gamma prime phase of Co-base superalloys," *Superalloys 2012 12th Int. Symp. Superalloys.*, p. 685, 2012.
- [41] F. Xue, M. Wang, and Q. Feng, "Alloying Effects on Heat-Treated Microstructure in Co-Al-W-Base Superalloys at 1300°C and 900°C," *Superalloys 2012*, pp. 813–821, 2012.
- [42] E. A. Lass, D. J. Sauza, D. C. Dunand, and D. N. Seidman, "Multicomponent γ' -strengthened Co-based superalloys with increased solvus temperatures and reduced mass densities," *Acta Mater.*, vol. 147, pp. 284–295, Apr. 2018.
- [43] F. Zhong, F. Fan, S. Li, and J. Sha, "High-temperature oxidation behaviour of novel Co-Al-W-Ta-B-(Mo, Hf, Nb) alloys with a coherent γ/γ' -dominant microstructure," *Prog. Nat. Sci. Mater. Int.*, vol. 26, no. 6, pp. 600–612, 2016.
- [44] F. Zhong, Y. X. Yu, S. S. Li, and J. B. Sha, "In-situ SEM and TEM tensile observations of novel Co-Al-W-Mo-Ta-B-Ce alloys with a coherent γ -Co SS / γ' -Co₃ (Al,W) microstructure at room temperature," *Mater. Sci. Eng. A*, vol. 696, pp. 96–103, Jun. 2017.
- [45] H. Inui, T. Ohashi, N. L. Okamoto, K. Kishida, and K. Tanaka, "Physical and Mechanical Properties of Co₃(Al,W) with the L12 Structure in Single and Polycrystalline Forms," *Key Eng. Mater.*, vol. 465, pp. 9–14, 2011.
- [46] L. Klein, A. Bauer, S. Neumeier, M. Göken, and S. Virtanen, "High temperature oxidation of γ/γ' -strengthened Co-base superalloys," *Corros. Sci.*, vol. 53, no. 5, pp. 2027–2034, 2011.
- [47] L. Klein and S. Virtanen, "Electrochemical characterisation of novel γ/γ' -strengthened Co-base superalloys," *Electrochim. Acta*, vol. 76, pp. 275–281, Aug. 2012.
- [48] S. Neumeier, L. P. Freund, and M. Göken, "Novel wrought γ/γ' cobalt base superalloys with high strength and improved oxidation resistance," *Scr. Mater.*, vol. 109, pp. 104–107, 2015.
- [49] L. Klein, A. Zendegani, M. Palumbo, S. G. Fries, and S. Virtanen, "First approach for thermodynamic modelling of the high temperature oxidation behaviour of ternary γ' -strengthened Co–Al–W superalloys," *Corros. Sci.*, vol. 89, pp. 1–5, 2014.
- [50] A. Bauer, S. Neumeier, F. Pyczak, R. F. Singer, and M. Göken, "Creep properties of different γ' -strengthened Co-base superalloys," *Mater. Sci. Eng. A*, vol. 550, pp. 333–341, 2012.

-
- [51] M. S. Titus, A. Suzuki, and T. M. Pollock, "High Temperature Creep of New L1 2 - containing Cobalt-base Superalloys," *Superalloys 2012*, pp. 823–832, 2012.
 - [52] A. Bauer, S. Neumeier, F. Pyczak, and M. Göken, "Creep Strength and Microstructure of Polycrystalline γ' - Strengthened Cobalt-Base Superalloys," *Superalloys 2012*, pp. 695–703, 2012.
 - [53] H.-Y. Yan, J. Coakley, V. A. Vorontsov, N. G. Jones, H. J. Stone, and D. Dye, "Alloying and the micromechanics of Co–Al–W–X quaternary alloys," *Mater. Sci. Eng. A*, vol. 613, pp. 201–208, Sep. 2014.
 - [54] H. Mughrabi, "The importance of sign and magnitude of γ/γ' lattice misfit in superalloys—with special reference to the new γ' -hardened cobalt-base superalloys," *Acta Mater.*, vol. 81, pp. 21–29, 2014.
 - [55] H. Y. Yan, V. A. Vorontsov, J. Coakley, N. G. Jones, H. J. Stone, and D. Dye, "Quaternary Alloying Effects and the Prospects for a New Generation of Co-Base Superalloys," *Superalloys 2012*, pp. 705–714, 2012.
 - [56] J. Coakley *et al.*, "Lattice parameter misfit evolution during creep of a cobalt-based superalloy single crystal with cuboidal and rafted gamma-prime microstructures," *Acta Mater.*, vol. 136, pp. 118–125, Sep. 2017.
 - [57] A. M. Jokisaari, S. S. Naghavi, C. Wolverton, P. W. Voorhees, and O. G. Heinonen, "Predicting the morphologies of γ' precipitates in cobalt-based superalloys," *Acta Mater.*, vol. 141, pp. 273–284, 2017.
 - [58] L. Zhang *et al.*, "Microstructural characterization of co-based ODS alloys," *J. Mater. Eng. Perform.*, vol. 21, no. 11, pp. 2487–2494, 2012.
 - [59] L. Zhang, X. Qu, M. Qin, Rafi-Ud-Din, X. He, and Y. Liu, "Microstructure and mechanical properties of γ' strengthened Co-Ni-Al-W-base ODS alloys," *Mater. Chem. Phys.*, vol. 136, no. 2–3, pp. 371–378, 2012.
 - [60] L. Zhang, X. Qu, X. He, D. Rafi-Ud, M. Qin, and H. Zhu, "Hot deformation behavior of Co-base ODS alloys," *J. Alloys Compd.*, vol. 512, no. 1, pp. 39–46, 2012.
 - [61] D. Locq, M. Martin, C. Ramusat, F. Fossard, and M. Perrut, " γ' Precipitation Study of a Co-Ni-Based Alloy," *Metall. Mater. Trans. A*, vol. 49, no. 9, pp. 3854–3864, Sep. 2018.
 - [62] S. A. J. Forsik *et al.*, "High-Temperature Oxidation Behavior of a Novel Co-Base Superalloy," *Metall. Mater. Trans. A*, 2018.
 - [63] C. H. Zenk *et al.*, "A novel type of Co–Ti–Cr-base γ/γ' superalloys with low mass density," *Acta Mater.*, vol. 135, pp. 244–251, 2017.
 - [64] M. Jin, N. Miao, W. Zhao, J. Zhou, Q. Du, and Z. Sun, "Structural stability and mechanical properties of $\text{Co}_3(\text{Al}, \text{M})$ ($\text{M} = \text{Ti}, \text{V}, \text{Cr}, \text{Zr}, \text{Nb}, \text{Mo}, \text{Hf}, \text{Ta}, \text{W}$) compounds," *Comput. Mater. Sci.*, vol. 148, pp. 27–37, Jun. 2018.
 - [65] P. Wang *et al.*, "Thermodynamic re-assessment of the Al-Co-W system," *Calphad*, vol. 59, pp. 112–130, Dec. 2017.
 - [66] L. Wang, M. Oehring, Y. Liu, U. Lorenz, and F. Pyczak, "Site occupancy of alloying elements in the L12 structure determined by channeling enhanced microanalysis in γ/γ' Co-9Al-9W-2X alloys," *Acta Mater.*, vol. 162, pp. 176–188, Jan. 2019.
 - [67] A. Epishin *et al.*, "Interdiffusion in the Face-Centered Cubic Phase of the Co-Al-W-Ta

- System Between 1090 and 1240 °C," *J. Phase Equilibria Diffus.*, pp. 1–10, 2018.
- [68] F. Xue, C. H. Zenk, L. P. Freund, M. Hoelzel, S. Neumeier, and M. Göken, "Double minimum creep in the rafting regime of a single-crystal Co-base superalloy," *Scr. Mater.*, vol. 142, pp. 129–132, Jan. 2018.
- [69] L. Feng *et al.*, "Shearing of γ' particles in Co-base and Co-Ni-base superalloys," *Acta Mater.*, vol. 161, pp. 99–109, 2018.
- [70] L. Zhang, S. Ukai, T. Hoshino, S. Hayashi, and X. Qu, "Y₂O₃ evolution and dispersion refinement in Co-base ODS alloys," *Acta Mater.*, vol. 57, no. 12, pp. 3671–3682, 2009.
- [71] S. K. Vajpai and K. Ameyama, "A novel powder metallurgy processing approach to prepare fine-grained Ti-rich TiAl-based alloys from pre-alloyed powders," *Intermetallics*, vol. 42, pp. 146–155, 2013.
- [72] C. Sawangrat, O. Yamaguchi, S. K. Vajpai, and K. Ameyama, "Application of Harmonic Structure Design to Biomedical Co-Cr-Mo Alloy for Improved Mechanical Properties," *Mater. Trans.*, vol. 55, no. 1, pp. 99–105, 2014.
- [73] S. K. Vajpai, C. Sawangrat, O. Yamaguchi, O. P. Ciuca, and K. Ameyama, "Effect of bimodal harmonic structure design on the deformation behaviour and mechanical properties of Co-Cr-Mo alloy," *Mater. Sci. Eng. C*, vol. 58, pp. 1008–1015, 2016.
- [74] Z. Zhang, S. K. Vajpai, D. Orlov, and K. Ameyama, "Improvement of mechanical properties in SUS304L steel through the control of bimodal microstructure characteristics," *Mater. Sci. Eng. A*, vol. 598, pp. 106–113, 2014.
- [75] Y. Yuan, Z. Wang, R. Zheng, X. Hao, K. Ameyama, and C. Ma, "Effect of mechanical alloying and sintering process on microstructure and mechanical properties of Al-Ni-Y-Co-La alloy," *Trans. Nonferrous Met. Soc. China*, vol. 24, no. 7, pp. 2251–2257, 2014.
- [76] Y. Suehiro and K. Ameyama, "Formation of a TiN/Ti₅Si₃ nano-grain composite by a non-equilibrium PM process," *J. Mater. Process. Technol.*, vol. 111, no. 1–3, pp. 118–121, 2001.
- [77] H. Fujiwara, R. Akada, A. Noro, Y. Yoshita, and K. Ameyama, "Enhanced Mechanical Properties of Nano/Meso Hybrid Structure Materials Produced by Hot Roll Sintering Process," *Mater. Trans.*, vol. 49, no. 1, pp. 90–96, 2008.
- [78] T. Sekiguchi, K. Ono, H. Fujiwara, and K. Ameyama, "New Microstructure Design for Commercially Pure Titanium with Outstanding Mechanical Properties by Mechanical Milling and Hot Roll Sintering," *Mater. Trans.*, vol. 51, no. 1, pp. 39–45, 2010.
- [79] D. Orlov, H. Fujiwara, and K. Ameyama, "Obtaining Copper with Harmonic Structure for the Optimal Balance of Structure-Performance Relationship," *Mater. Trans.*, vol. 54, no. 9, pp. 1549–1553, 2013.
- [80] W. C. Oliver and G. M. Pharr, "An improved technique for determining hardness and elastic modulus using load and displacement sensing indentation experiments," *J. Mater. Res.*, vol. 7, no. 6, pp. 1564–1583, Jun. 1992.
- [81] M. A. Monclús and J. M. Molina-Aldareguia, "High Temperature Nanomechanical Testing," in *Handbook of Mechanics of Materials*, Singapore: Springer Singapore, 2018, pp. 1–29.
- [82] M. Cartón-Cordero, B. Srinivasarao, M. Campos, A. García-Junceda, and J. M. Torralba, "On the role of processing parameters in sintered new Co-based (W,Al) alloys," *J. Alloys*

- Compd.*, vol. 674, pp. 406–412, 2016.
- [83] E. A. Lass, M. E. Williams, C. E. Campbell, K.-W. Moon, and U. R. Kattner, “ γ' Phase Stability and Phase Equilibrium in Ternary Co-Al-W at 900 °C,” *J. Phase Equilibria Diffus.*, vol. 35, no. 6, pp. 711–723, 2014.
 - [84] H.-Y. Yan, V. A. Vorontsov, and D. Dye, “Alloying effects in polycrystalline γ' strengthened Co-Al-W base alloys,” *Intermetallics*, vol. 48, pp. 44–53, 2014.
 - [85] I. Povstugar *et al.*, “Elemental partitioning and mechanical properties of Ti- and Ta-containing Co-Al-W-base superalloys studied by atom probe tomography and nanoindentation,” *Acta Mater.*, vol. 78, pp. 78–85, 2014.
 - [86] J. . Fogagnolo, F. Velasco, M. . Robert, and J. . Torralba, “Effect of mechanical alloying on the morphology, microstructure and properties of aluminium matrix composite powders,” *Mater. Sci. Eng. A*, vol. 342, no. 1–2, pp. 131–143, Feb. 2003.
 - [87] W. Gui, H. Zhang, M. Yang, T. Jin, X. Sun, and Q. Zheng, “The investigation of carbides evolution in a cobalt-base superalloy at elevated temperature,” *J. Alloys Compd.*, vol. 695, pp. 1271–1278, 2017.
 - [88] T. M. Pollock and S. Tin, “Nickel-Based Superalloys for Advanced Turbine Engines: Chemistry, Microstructure and Properties,” *J. Propuls. Power*, vol. 22, no. 2, pp. 361–374, 2006.
 - [89] M. Li, J. Coakley, D. Isheim, G. Tian, and B. Shollock, “Influence of the initial cooling rate from γ' supersolvus temperatures on microstructure and phase compositions in a nickel superalloy,” *J. Alloys Compd.*, vol. 732, pp. 765–776, 2018.
 - [90] A. R. P. Singh *et al.*, “Mechanisms related to different generations of γ' precipitation during continuous cooling of a nickel base superalloy,” *Acta Mater.*, vol. 61, no. 1, pp. 280–293, 2013.
 - [91] R. J. Mitchell, M. Preuss, M. C. Hardy, and S. Tin, “Influence of composition and cooling rate on constrained and unconstrained lattice parameters in advanced polycrystalline nickel-base superalloys,” *Mater. Sci. Eng. A*, vol. 423, no. 1–2, pp. 282–291, 2006.
 - [92] L. P. Freund, A. Bauer, L. Benker, S. Neumeier, and M. Göken, “Formation of Cuboidal Co₃AlC Precipitates in Carbon-Containing Co-Al-W-Based Superalloys,” *Adv. Eng. Mater.*, vol. 17, no. 8, pp. 1113–1118, 2015.
 - [93] J. R. Davis, *ASM Specialty Handbook Nickel, Cobalt, and Their Alloys*, First ed. ASM International, Materials Park, 2000.
 - [94] S. K. Makineni, B. Nithin, and K. Chattopadhyay, “Synthesis of a new tungsten-free γ - γ' cobalt-based superalloy by tuning alloying additions,” *Acta Mater.*, vol. 85, pp. 85–94, 2015.
 - [95] S. K. Makineni *et al.*, “A new class of high strength high temperature Cobalt based γ - γ' Co-Mo-Al alloys stabilized with Ta addition,” *Acta Mater.*, vol. 97, pp. 29–40, 2015.
 - [96] R. Casas, F. Gálvez, and M. Campos, “Microstructural development of Powder Metallurgy Cobalt-based superalloys processed by Field Assisted Sintering Techniques (FAST),” *Mater. Sci. Eng. A*, vol. 724, no. April, pp. 461–468, 2018.